

Paints and varnishes - Coating materials and coating systems for exterior wood - Part 5: Assessment of the liquid water permeability

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 927-5:2023 sisaldab Euroopa standardi EN 927-5:2023 ingliskeelset teksti.	This Estonian standard EVS-EN 927-5:2023 consists of the English text of the European standard EN 927-5:2023.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 07.06.2023.	Date of Availability of the European standard is 07.06.2023.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Paints and varnishes - Coating materials and coating systems for exterior wood - Part 5: Assessment of the liquid water permeability

Peintures et vernis - Produits de peinture et systèmes de peinture pour le bois en extérieur - Partie 5 : Détermination de la perméabilité à l'eau liquide

Beschichtungsstoffe - Beschichtungsstoffe und Beschichtungssysteme für Holz im Außenbereich - Teil 5: Beurteilung der Wasserdurchlässigkeit

This European Standard was approved by CEN on 30 April 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Test panels	6
5.1 Wood	6
5.2 Preparation and selection of test panels	7
5.3 Preparation of coated and sealed panels	7
5.3.1 Wood conditioning	7
5.3.2 Panel selection	7
5.3.3 Coating application	9
5.3.4 Sealing and conditioning	9
5.3.5 Dry film thickness	10
6 Apparatus	10
7 Procedure	10
7.1 Pre-conditioning	10
7.2 Absorption cycle	11
7.3 Optional testing of weathered panels	11
8 Calculation and expression of results	11
9 Precision	11
9.1 Repeatability (<i>r</i>)	11
9.2 Reproducibility (<i>R</i>)	11
10 Test report	12
Annex A (informative) Interpretation of test results and further calculation	13
Annex B (informative) Suggested form for specifying application parameters	14
B.1 General	14
B.2 Specifying complete coating system	14
B.3 Equipment	14
B.4 Process	14
B.5 Spreading rate	14
B.6 Flash-off	15
B.7 Drying and curing	15
B.8 Overcoating intervals	15
B.9 Sanding	15
Bibliography	19

European foreword

This document (EN 927-5:2023) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2023, and conflicting national standards shall be withdrawn at the latest by December 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 927-5:2006.

EN 927-5:2023 includes the following significant technical changes with respect to EN 927-5:2006:

- the selection and preparation of test panels has been clarified;
- Annex A has been rewritten to better describe the link between water absorption and end use categories.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

The treatment of exterior wood surfaces has both aesthetic and protective functions. A vital purpose of a coating system is to protect the wood against aesthetic deterioration (e.g. blue stain attack) and dimensional changes. Because such attacks are mainly caused by high moisture contents in the wood, a knowledge of the relative water permeability properties of coating materials applied to exterior wood is helpful in selecting products for particular end-use applications, as described in EN 927-1.

This document is a preview generated by EVS

1 Scope

This document specifies a test method for assessing the liquid water permeability of coating systems for exterior wood.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 2808:2019, *Paints and varnishes — Determination of film thickness (ISO 2808:2019)*

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

water absorption

ability of a coated or uncoated wood panel to absorb water from liquid or vapour

3.2

water permeability

ability of a coating system to allow the transmission of water as liquid or vapour

[SOURCE: EN 927-1:2013, 3.13]

3.3

stable mass

mass achieved when the difference between two subsequent weighings within 24 h does not exceed 0,2 %

4 Principle

Water permeability is assessed by measuring the water uptake over a 72 h period of a coated test panel exposed to liquid water.

The coating under test is applied to the face of a defined test panel where the remaining face and sides are carefully sealed using a sealer of a defined mandatory low permeability.

Results are expressed as water absorption of coated wood panels in grams per square metre test surface per 72 h.