

This document is a preview generated by EVS

Aluminium and aluminium alloys - Finstock - Part 2:  
Mechanical properties

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 683-2:2024 sisaldab Euroopa standardi EN 683-2:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 03.04.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 683-2:2024 consists of the English text of the European standard EN 683-2:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 03.04.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.120.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN 683-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2024

ICS 77.120.10

Supersedes EN 683-2:2006

English Version

## Aluminium and aluminium alloys - Finstock - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Bandes pour  
échangeurs thermiques - Partie 2 : Caractéristiques  
mécaniques

Aluminium und Aluminiumlegierungen - Vormaterial  
für Wärmeaustauscher (Finstock) - Teil 2: Mechanische  
Eigenschaften

This European Standard was approved by CEN on 27 February 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>		Page
<b>European foreword</b> .....		<b>3</b>
<b>1</b>	<b>Scope</b> .....	<b>4</b>
<b>2</b>	<b>Normative references</b> .....	<b>4</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>4</b>
<b>4</b>	<b>Tensile testing</b> .....	<b>4</b>
<b>5</b>	<b>Mechanical properties</b> .....	<b>6</b>
<b>6</b>	<b>Rounding of test results</b> .....	<b>6</b>
<b>Annex A (informative) Rules for rounding</b> .....		<b>11</b>
<b>Bibliography</b> .....		<b>12</b>

## European foreword

This document (EN 683-2:2024) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2024, and conflicting national standards shall be withdrawn at the latest by October 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 683-2:2006.

EN 683-2:2024 includes the following significant technical changes with respect to EN 683-2:2006:

- replacement of former and cancelled normative reference EN 10002-1 with replacing normative reference EN ISO 6892-1;
- addition of mandatory Clause 3 from the latest CCMC template;
- introduction of alloy EN AW-5052 in Table 2.

EN 683 comprises the following parts under the general title "*Aluminium and aluminium alloys — Finstock*":

- Part 1: Technical conditions for inspection and delivery
- Part 2: Mechanical properties
- Part 3: Tolerances on dimensions and form

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## 1 Scope

This document specifies the mechanical properties of wrought aluminium and wrought aluminium alloy finstock.

The chemical composition limits of these materials are specified in EN 573-3, unless otherwise agreed between supplier and purchaser.

The designations of wrought aluminium and wrought aluminium alloys and the temper designations used in this document are specified in EN 573-3, and the temper designations are defined in EN 515.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 683-1, *Aluminium and aluminium alloys - Finstock - Part 1: Technical conditions for inspection and delivery*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN 12258-1, *Aluminium and aluminium alloys - Terms and definitions - Part 1: General terms*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12258-1 apply. No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Tensile testing

The selection and number of specimens and test pieces shall be as specified in EN 683-1.

Tensile testing shall be carried out according to EN ISO 6892-1 noting the following:

- applies to gauges between 60  $\mu\text{m}$  and 400  $\mu\text{m}$ ;
- test pieces shall be either parallel-sided (see Figure 1) or with shoulders and a reduced parallel section.

Parallel sided test pieces shall be prepared using a double-bladed cutter (see Figure 2) or a precision ground sample shear of "punch and die" construction.

Shouldered test pieces shall have a similar sample shear or can be machined in packs using a milling-type cutter.

Parallel sided test pieces shall have a width of  $(15 \pm 0,1)$  mm and a gauge length of  $(50 \pm 1)$  mm or  $(100 \pm 1)$  mm.

Shouldered test pieces shall be in accordance with EN ISO 6892-1.