

Metallic and other inorganic coatings - Phosphate conversion coating of metals (ISO 9717:2024)

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 9717:2024 sisaldab Euroopa standardi EN ISO 9717:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 24.07.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 9717:2024 consists of the English text of the European standard EN ISO 9717:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 24.07.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.220.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 9717

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2024

ICS 25.220.20

Supersedes EN ISO 9717:2017

English Version

Metallic and other inorganic coatings - Phosphate conversion coating of metals (ISO 9717:2024)

Revêtements métalliques et autres revêtements inorganiques - Couches de conversion au phosphate sur métaux (ISO 9717:2024)

Metallische und andere anorganische Überzüge - Phosphatumschlammüberzüge auf Metallen (ISO 9717:2024)

This European Standard was approved by CEN on 30 June 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 9717:2024) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2025, and conflicting national standards shall be withdrawn at the latest by January 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9717:2017.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 9717:2024 has been approved by CEN as EN ISO 9717:2024 without any modification.

Contents

	Page
Foreword	iv
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Information to be supplied by the purchaser to the processor	1
5 Coating types and their importance	2
5.1 Coating types.....	2
5.2 Designation of phosphate conversion coating.....	2
5.3 Example for designation of phosphate conversion coating.....	3
6 Requirements	3
6.1 Appearance.....	3
6.2 Coating mass per unit area.....	3
6.3 Post treatment.....	3
6.4 Correlation of coating thickness and area related mass.....	4
7 Heat treatment	4
Annex A (normative) Determination of phosphate conversion coating resistance to neutral salt spray test	5
Annex B (informative) General information	8
Annex C (informative) Identification of phosphate conversion coating	11
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings, Subcommittee SC 8, Chemical conversion coatings*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 9717:2017), which has been technically revised.

The main changes are as follows:

- the introduction has been clarified (1 bracket shifted);
- [5.1 Table 1](#) formatted and for Znph second line added to describe types of Znph; new [Table 1](#) copied on [Table C.1](#)
- [5.2](#) and ff.: all terms are uniformed from “phosphate coating” or “conversion coating” to “phosphate conversion coating” (when applicable);
- [5.2](#) and ff.: “after-treatment” was changed to “post treatment”; other definitions and spelling changed according to ISO 2080;
- [6.3 Table 2](#): definition of T1 recharged, second sentence deleted (this is content of T2);
- [6.3](#): last sentence updated to describe impact of neutral salt spray test;
- [6.4](#): revision of [6.4](#), thickness measurement replaced by area related mass;
- [Annex B](#): last sentence of [B.1](#) deleted: [Table B.1](#) updated;
- [Annex B](#): [Table B.1](#) and [B.3](#) headlines updated;
- [Annex B](#): [Table B.4](#) headline updated;

- [Annex C](#): the element nickel has been added to [C.1](#), [C.2.3](#), [C.2.5](#) and [C.4](#); ICP was added as method to [C.2.3](#); XRF was added as method to [C.3](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This document is a preview generated by EVS

Introduction

Phosphate conversion coatings are produced by treating substrates with appropriate solutions. The main constituents of these solutions are the appropriate dihydrogen orthophosphates.

They are intended to

- impart corrosion resistance,
- improve adhesion to paints and other organic finishes,
- facilitate cold-forming operations, such as wire drawing, tube drawing and extrusion, and
- modify surface frictional properties to facilitate sliding.

Phosphate conversion coatings are produced by treatment with solutions, the main constituents of which are the appropriate dihydrogen orthophosphates. These phosphate conversion coatings are applied principally to ferrous materials and zinc, and differ in coating mass per unit area and apparent density, depending on

- the construction material and surface condition of the components,
- previous mechanical and chemical treatment of the components, and
- processing conditions for phosphating.

All phosphate conversion coatings are crystalline and porous but can be sealed substantially by subsequent sealant processes.

Metallic and other inorganic coatings — Phosphate conversion coating of metals

WARNING — This document calls for the use of substances and/or procedures that could be injurious to health if adequate safety measures are not taken. This document does not address any health hazards, safety or environmental matters associated with its use. It is the responsibility of the producers, purchasers and/or users of this document to establish appropriate health, safety and environmentally acceptable practices and take appropriate actions.

1 Scope

This document specifies the requirements for phosphate conversion coatings which are usually destined for application on ferrous materials, aluminium, zinc, and their alloys (see [Annex B](#)).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 3892, *Conversion coatings on metallic materials — Determination of coating mass per unit area — Gravimetric methods*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2080 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Information to be supplied by the purchaser to the processor

The following information shall be provided by the purchaser:

- a) a description of the phosphate conversion coating according to this document, i.e., ISO 9717 (see [5.2](#));
- b) in cases of phosphating steel parts with tensile strength $\geq 1\ 000$ MPa, also in locally restricted areas (e.g. for case-hardened or cold-formed structures or in weld seam areas) the safety against brittle fracture (hydrogen embrittlement) is of primary importance. The phosphating process shall be carried