

This document is a preview generated by EVS

Paints and varnishes - Standard panels for testing (ISO 1514:2024)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 1514:2024 sisaldab Euroopa standardi EN ISO 1514:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.07.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 1514:2024 consists of the English text of the European standard EN ISO 1514:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 17.07.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 1514

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2024

ICS 87.040

Supersedes EN ISO 1514:2016

English Version

Paints and varnishes - Standard panels for testing (ISO 1514:2024)

Peintures et vernis - Panneaux normalisés pour essai
(ISO 1514:2024)

Beschichtungsstoffe - Norm-Probenplatten (ISO
1514:2024)

This European Standard was approved by CEN on 3 July 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 1514:2024) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2025, and conflicting national standards shall be withdrawn at the latest by January 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1514:2016.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 1514:2024 has been approved by CEN as EN ISO 1514:2024 without any modification.

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Steel panels	2
4.1 Properties.....	2
4.2 Storage prior to preparation.....	2
4.3 Preparation by solvent cleaning.....	2
4.4 Preparation by aqueous cleaning (spray or immersion process).....	3
4.5 Preparation by abrasion.....	3
4.5.1 General.....	3
4.5.2 Hand abrasion.....	3
4.5.3 Circular mechanical abrasion.....	4
4.5.4 Linear grinding.....	4
4.6 Inspection and cleaning.....	4
4.7 Preparation by phosphate treatment.....	4
4.7.1 General.....	4
4.7.2 Amorphous iron phosphate treatment.....	4
4.8 Preparation by blast-cleaning.....	4
5 Tinplate panels	4
5.1 Properties.....	4
5.2 Preparation by solvent or aqueous cleaning.....	5
5.3 Preparation by abrasion.....	5
6 Zinc- and zinc-alloy-coated panels	5
6.1 Properties.....	5
6.2 Preparation by solvent cleaning.....	5
6.3 Preparation by aqueous cleaning.....	5
7 Aluminium panels	6
7.1 Properties.....	6
7.2 Preparation by solvent cleaning.....	6
7.3 Preparation by aqueous cleaning.....	6
7.4 Preparation by abrasion.....	6
8 Coil-coating panels of steel or aluminium	6
8.1 Properties.....	6
8.2 Coating.....	6
8.3 Substrate.....	7
8.4 Preparation by solvent cleaning.....	7
9 Plastics panels	7
9.1 Properties.....	7
9.2 Preparation by solvent cleaning.....	7
9.3 Preparation by detergent cleaning.....	7
9.4 Pre-treatment by flaming.....	7
10 Glass-fibre reinforced plastic composite panels (GRP)	7
10.1 Properties.....	7
10.2 Preparation by solvent cleaning.....	7
10.3 Preparation by detergent cleaning.....	7
11 Carbon-fibre reinforced plastic composite panels (CFRP)	8
11.1 Properties.....	8
11.2 Preparation by solvent cleaning.....	8

11.3	Preparation by detergent cleaning	8
12	Glass panels	8
12.1	Properties	8
12.2	Preparation by solvent cleaning	8
12.3	Preparation by detergent cleaning	8
13	Hardboard	8
13.1	Properties	8
13.2	Preparation	8
14	Gypsum plasterboards panels and gypsum boards with fibrous reinforcement panels	9
14.1	Properties	9
14.2	Preparation	9
15	Fibre-reinforced cement panels	9
16	Concrete	9
Annex A (informative) General guidelines on preparation of steel panels by blast-cleaning		10
Annex B (informative) Common substrate panels		11
Bibliography		12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This sixth edition cancels and replaces the fifth edition (ISO 1514:2016), which has been technically revised.

The main changes are as follows:

- [Clause 3](#) (terms and definitions) has been added;
- the preparation of plastics substrate including glass-fibre reinforced plastic composite panels (GRP) and carbon-fibre reinforced plastic composite panels (CFRP) has been updated;
- concrete test panels have been added;
- the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

For many of the most widely used test methods for paints and varnishes, the type of panel used and the particular way in which it is prepared for use can affect the test results to a significant degree. Consequently, it is important to standardize as carefully as possible both the panels and the procedures used to prepare the panels prior to painting.

It is not possible to include in this document all the types of panels and preparation needed for paint testing. Thus, this document describes preparation procedures that are known to be reproducible and gives additional guidance and requirements in instances where there can still be doubt, due to lack of international uniformity of the procedure.

Common substrate panels and the documents which specify their technical delivery conditions are listed in [Table B.1](#).

Paints and varnishes — Standard panels for testing

1 Scope

This document specifies several types of standard panels and provides guidance and requirements on the procedures for their preparation prior to painting. The standard panels described in this document are intended for use in general methods of test for paints, varnishes and related products.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1268-1, *Fibre-reinforced plastics — Methods of producing test plates — Part 1: General conditions*

ISO 1268-2, *Fibre-reinforced plastics — Methods of producing test plates — Part 2: Contact and spray-up moulding*

ISO 1268-3, *Fibre-reinforced plastics — Methods of producing test plates — Part 3: Wet compression moulding*

ISO 1268-4, *Fibre-reinforced plastics — Methods of producing test plates — Part 4: Moulding of prepregs*

ISO 1268-5, *Fibre-reinforced plastics — Methods of producing test plates — Part 5: Filament winding*

ISO 1268-6, *Fibre-reinforced plastics — Methods of producing test plates — Part 6: Pultrusion moulding*

ISO 1268-7, *Fibre-reinforced plastics — Methods of producing test plates — Part 7: Resin transfer moulding*

ISO 1268-8, *Fibre-reinforced plastics — Methods of producing test plates — Part 8: Compression moulding of SMC and BMC*

ISO 1268-9, *Fibre-reinforced plastics — Methods of producing test plates — Part 9: Moulding of GMT/STC*

ISO 1268-10, *Fibre-reinforced plastics — Methods of producing test plates — Part 10: Injection moulding of BMC and other long-fibre moulding compounds — General principles and moulding of multipurpose test specimens*

ISO 1268-11, *Fibre-reinforced plastics — Methods of producing test plates — Part 11: Injection moulding of BMC and other long-fibre moulding compounds — Small plates*

ISO 2409, *Paints and varnishes — Cross-cut test*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 4618, *Paints and varnishes — Vocabulary*

ISO 8336, *Fibre-cement flat sheets — Product specification and test methods*

ISO 11949, *Cold-reduced tinmill products — Electrolytic tinplate*

ISO 21920-2, *Geometrical product specifications (GPS) — Surface texture: Profile — Part 2: Terms, definitions and surface texture parameters*

EN 520, *Gypsum plasterboards — Definitions, requirements and test methods*

EN 622-1, *Fibreboards — Specifications — Part 1: General requirements*

EN 622-2, *Fibreboards — Specifications — Part 2: Requirements for hardboards*

EN 622-3, *Fibreboards — Specifications — Part 3: Requirements for medium boards*

EN 622-4, *Fibreboards — Specifications — Part 4: Requirements for softboards*

EN 622-5, *Fibreboards — Specifications — Part 5: Requirements for dry process boards (MDF)*

EN 1396, *Aluminium and aluminium alloys — Coil coated sheet and strip for general applications — Specifications*

EN 1766, *Products and systems for the protection and repair of concrete structures — Test methods — Reference concretes for testing*

EN 10205, *Cold reduced tinmill products — Blackplate*

EN 13523-1, *Coil coated metals — Test methods — Part 1: Film thickness*

EN 13523-22, *Coil coated metals — Test methods — Part 22: Colour difference — Visual comparison*

EN 15283-2, *Gypsum boards with fibrous reinforcement — Definitions, requirements and test methods — Part 2: Gypsum fibre boards*

EN 16245-1, *Fibre-reinforced plastic composites — Declaration of raw material characteristics — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Steel panels

4.1 Properties

Steel panels intended for general testing (as opposed to panels intended for testing particular applications and uses) shall be free from rust, scratches, staining, discoloration and other surface defects. The physical dimensions of the panel shall be as specified in the description of the test method, or as otherwise agreed.

4.2 Storage prior to preparation

Prior to preparation, panels shall be stored in a manner that protects them from corrosion.

4.3 Preparation by solvent cleaning

Wipe the panel to remove any excess oil and then wash it thoroughly with a suitable solvent to remove all excess of oil.

Ensure that any small fibres deposited by cleaning cloths are removed in the cleaning process and that cloths are changed at predetermined intervals to avoid redistribution of oily residues. Do not contaminate the cleaned panels. Suitable methods of drying include allowing the solvent to evaporate, lightly wiping the panels with a clean linen cloth and subjecting the panels to a stream of warm dry air. If necessary, lightly warm the panels to remove any traces of condensed moisture.