

This document is a preview generated by EVS

Copper and copper alloys - Wrought and unwrought forging stock

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 12165:2024 sisaldab Euroopa standardi EN 12165:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.10.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 12165:2024 consists of the English text of the European standard EN 12165:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 16.10.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.150.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 12165

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2024

ICS 77.150.30

Supersedes EN 12165:2016

English Version

Copper and copper alloys - Wrought and unwrought forging stock

Cuivre et alliages de cuivre - Barres corroyées et brutes pour matriçage

Kupfer und Kupferlegierungen - Vormaterial für Schmiedestücke

This European Standard was approved by CEN on 5 May 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Designations.....	7
4.1 Material.....	7
4.1.1 General.....	7
4.1.2 Symbol.....	7
4.1.3 Number	7
4.2 Material condition	7
4.3 Product.....	8
5 Ordering information	9
6 Requirements.....	10
6.1 Composition	10
6.2 Mechanical properties.....	10
6.2.1 General.....	10
6.2.2 Resistance to dezincification	10
6.3 Dimensions and tolerances	11
6.3.1 Diameter.....	11
6.3.2 Deviation from circular form.....	11
6.3.3 Length.....	11
6.3.4 Straightness.....	11
6.4 Surface quality.....	11
6.5 Internal inclusion.....	12
7 Sampling.....	12
7.1 General.....	12
7.2 Analysis.....	12
7.3 Hardness and dezincification resistance tests	12
8 Test methods	12
8.1 Analysis.....	12
8.2 Hardness test.....	12
8.2.1 General.....	12
8.2.2 Preparation of samples.....	13
8.2.3 Procedure for testing.....	13
8.3 Dezincification resistance test	13
8.4 Retests for analysis, hardness and dezincification resistance	13
8.5 Rounding of results	13
9 Certificate of compliance and inspection documentation.....	13
9.1 Certificate of compliance.....	13
9.2 Inspection documentation.....	14
10 Marking, packaging, labelling.....	14
Bibliography.....	27

European foreword

This document (EN 12165:2024) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by month year of April 2025, and conflicting national standards shall be withdrawn at the latest by April 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12165:2016

In comparison with EN 12165:2016, the following significant technical changes were made:

- a) Introduction in 6.4 of eddy current test parameters;
- b) Introduction of 6.5 Internal inclusion;
- c) Modified the definition of diameter at 6.3.1;
- d) Added a new Figure for straightness at 6.4.4 and modified values in Table 11;
- e) Introduction in the chemical composition Tables of a footnote to explain the meaning of elements for which no upper and lower limits are specified;
- f) CuSi4Zn4MnP (CW245E) and CuSi4Zn9MnP (CW246E) added in the new Table 3;
- g) Chemical composition of CuZn39Pb3 (CW614N), CuZn40Pb2 (CW617N), CuZn35Pb1,5AlAs (CW625N) and CuZn33Pb1,5AlAs (CW626N) modified in Table 8;
- h) Added a new alloy CuZn40Pb1 (CW627N) in Table 8;
- i) Chemical composition of CuZn33Pb1AlSiAs (CW725R) modified in Table 9;
- j) Added a new alloy CuZn36Si1P (CW726R) in Table 9;
- k) Removed Tables of Mechanical properties (old Table 9, Table 10, Table 11, Table 12, Table 13, Table 14, Table 15 and Table 16);
- l) Renamed Table 17 in Table 10, Table 18 in Table 11, Table 19 in Table 12;
- m) Added new Table 13.

This document is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- EN 12163, *Copper and copper alloys — Rod for general purposes*;
- EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
- EN 12166, *Copper and copper alloys — Wire for general purposes*;

- EN 12167, *Copper and copper alloys — Profiles and bars for general purposes*;
- EN 12168, *Copper and copper alloys — Hollow rod for free machining purposes*;
- EN 12420, *Copper and copper alloys — Forgings*;
- EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*;
- EN 13602, *Copper and copper alloys — Drawn round copper wire for the manufacture of electrical conductors*;
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wires for electrical purposes*.

Any feedback and questions on this document should be directed to the users' national standards body.

A complete listing of these bodies can be found on the CEN website. According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

The European Committee for Standardization (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the alloys CuSi₄Zn₄MnP (CW245E), CuSi₄Zn₉MnP (CW246E) and CuZn₃₆Si₁P (CW726R) given in 6.1.

CEN takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the CEN that he is willing to negotiate licenses either free of charge or under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with CEN.

- For CuSi₄Zn₄MnP (CW245E) and CuSi₄Zn₉MnP (CW246E) information may be obtained from:

Viega Technology GmbH & Co. KG
Viega Platz 1
57439 Attendorn
GERMANY

- For CuZn₃₆Si₁P (CW726R) information may be obtained from:

Luvata Oy
Kuparitie 5
28330 Pori
FINLAND

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN shall not be held responsible for identifying any or all such patent rights.

CEN and CENELEC maintain online lists of patents relevant to their standards. Users are encouraged to consult the lists for the most up to date information concerning patents (<ftp://ftp.cencenelec.eu/EN/IPR/Patents/IPRdeclaration.pdf>).

Due to developing legislation, the composition of a material may be restricted to the composition specified in this European Standard with respect to individual uses (e.g. for the use in contact with drinking water in some Member States of the European Union). These individual restrictions are not part of this European Standard. Nevertheless, for materials for which traditional and major uses are affected, these restrictions are indicated. The absence of an indication, however, does not imply that the material can be used in any application without any legal restriction.

1 Scope

This document specifies the composition, property requirements and dimensional tolerances for forging stock of copper and copper alloys.

The sampling procedures and the methods of test for verification of conformity to the requirements of this document are also specified.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1173, *Copper and copper alloys - Material condition designation*

EN 1412, *Copper and copper alloys - European numbering system*

EN 1976, *Copper and copper alloys - Cast unwrought copper products*

EN 10204, *Metallic products - Types of inspection documents*

EN 17263, *Copper and copper alloys - Eddy current testing on the outer surface of rods, bars, hollow rods and wires for the detection of defects by encircling test coil*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6509-1, *Corrosion of metals and alloys - Determination of dezincification resistance of copper alloys with zinc - Part 1: Test method (ISO 6509-1)*

ISO 1190-1, *Copper and copper alloys — Code of designation — Part 1: Designation of materials*