

Plastics piping systems for the supply of gaseous fuels
- Unplasticized polyamide (PA-U) piping systems with
fusion jointing and mechanical jointing - Part 2: Pipes
(ISO 16486-2:2024)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 16486-2:2024 sisaldab Euroopa standardi EN ISO 16486-2:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 13.11.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 16486-2:2024 consists of the English text of the European standard EN ISO 16486-2:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 13.11.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 75.200

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 16486-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2024

ICS 75.200

Supersedes EN ISO 16486-2:2020

English Version

Plastics piping systems for the supply of gaseous fuels -
Unplasticized polyamide (PA-U) piping systems with
fusion jointing and mechanical jointing - Part 2: Pipes (ISO
16486-2:2024)

Systèmes de canalisations en matières plastiques pour
la distribution de combustibles gazeux - Systèmes de
canalisations en polyamide non plastifié (PA-U) avec
assemblages par soudage et assemblages mécaniques -
Partie 2: Tubes (ISO 16486-2:2024)

Kunststoff-Rohrleitungssysteme für die Gasversorgung
- Rohrleitungssysteme aus weichmacherfreiem
Polyamid (PA-U) mit Schweißverbindungen und
mechanischen Verbindungen - Teil 2: Rohre (ISO
16486-2:2024)

This European Standard was approved by CEN on 10 August 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 16486-2:2024) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2025, and conflicting national standards shall be withdrawn at the latest by May 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 16486-2:2020.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 16486-2:2024 has been approved by CEN as EN ISO 16486-2:2024 without any modification.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
3.1 Terms related to geometrical characteristics.....	2
3.2 Terms related to material.....	2
3.3 Terms related to joints.....	2
3.4 Abbreviated terms.....	3
4 Compound	3
5 General characteristics	3
5.1 Appearance.....	3
5.2 Colour.....	3
5.3 Fusion compatibility.....	3
6 Geometrical characteristics	3
6.1 Measurement of dimensions.....	3
6.2 Mean outside diameters, out-of-roundness and their tolerances.....	3
6.3 Wall thicknesses and tolerances.....	4
6.3.1 Minimum wall thickness.....	4
6.3.2 Tolerances on wall thickness at any point.....	5
7 Mechanical characteristics	6
7.1 Conditioning.....	6
7.2 Requirements.....	6
8 Physical characteristics	9
8.1 Conditioning.....	9
8.2 Requirements.....	9
9 Marking	9
Annex A (normative) Squeeze-off technique	11
Annex B (informative) Examples of the water uptake over time as a function of the sample thickness	12
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 16486-2:2020), which has been technically revised.

The main changes are as follows:

- the references in the Introduction have been updated;
- a Note has been added in the Introduction providing information on the suitability of PA-U pipe systems for 100 % hydrogen and its admixtures with natural gas;
- the symbols that have been deleted in ISO 16486-1 (but that are used in this document) have been defined in this document;
- a reference to ISO 12176-5 has been added in the Note in [Clause 9](#);
- the Bibliography has been extended.

A list of all parts in the ISO 16486 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document specifies the requirements for a piping system and its components made from unplasticized polyamide (PA-U), which is intended to be used for the supply of gaseous fuels.

NOTE 1 Additional information about the suitability of PA-U pipe systems for hydrogen and its admixtures is given in ISO 16486-1:2023, Annex D.

Requirements and test methods for material and components of the piping system, are specified in ISO 16486-1, ISO 16486-3 and ISO 16486-4.

Characteristics for fitness for purpose of the system and generic fusion parameters are covered in ISO 16486-5.

Recommended practice for installation is given in ISO 16486-6, which will not be implemented as a European Standard under the Vienna Agreement.

NOTE 2 Recommended practice for installation is also given in CEN/TS 12007-6,^[5] which has been prepared by Technical Committee CEN/TC 234, *Gas infrastructure*.

Assessment of conformity of the system is covered by ISO/TS 16486-7.

Training and assessment of fusion operators is covered by ISO/TS 16486-8.

ISO 16486-1, ISO 16486-2, ISO 16486-3, ISO 16486-5, ISO 16486-6, ISO/TS 16486-7 and ISO/TS 16486-8 have been prepared by ISO/TC 138/SC 4. ISO 16486-4 has been prepared by ISO/TC 138/SC 7.

Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing —

Part 2: Pipes

1 Scope

This document specifies the physical and mechanical properties of pipes made from unplasticized polyamide (PA-U) in accordance with ISO 16486-1, intended to be buried and used for the supply of gaseous fuels.

It also specifies the test parameters for the test methods to which it refers.

The ISO 16486 series is applicable to PA-U piping systems, the components of which are connected by fusion jointing and/or mechanical jointing.

In particular, this document lays down dimensional characteristics and requirements for the marking of pipes.

Pipes conforming to this document are jointed typically by using mechanical, electrofusion or butt fusion techniques.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 307, *Plastics — Polyamides — Determination of viscosity number*

ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture*

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

ISO 2505, *Thermoplastics pipes — Longitudinal reversion — Test method and parameters*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method*

ISO 6259-3, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes*

ISO 11922-1, *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances — Part 1: Metric series*

ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test)*

ISO 13479, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes*

ISO 16486-1, *Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 1: General*

EN 12106, *Plastics piping systems - Polyethylene (PE) pipes - Test method for the resistance to internal pressure after application of squeeze-off*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16486-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Terms related to geometrical characteristics

3.1.1

out-of-roundness

<pipe or fitting> difference between the measured maximum outside diameter and the measured minimum outside diameter in the same cross-sectional plane of a pipe or spigot end of a fitting

3.1.2

minimum mean outside diameter

$d_{em,min}$

minimum value for the mean outside diameter as specified for a given nominal size

3.1.3

maximum mean outside diameter

$d_{em,max}$

maximum value for the mean outside diameter as specified for a given nominal size

3.1.4

nominal wall thickness

e_n

wall thickness, in millimetres, corresponding to the minimum wall thickness, e_{min}

3.2 Terms related to material

3.2.1

virgin material

material in a form such as granules or powder that has not been previously processed other than for compounding and to which no rework material or recyclable material has been added

3.3 Terms related to joints

3.3.1

squeeze-off

gas flow restricted by squeezing the pipe when compressed between two clamps in such a way that the distance between both clamps is less than twice the nominal wall thickness