

Aluminium and aluminium alloys - Cold drawn  
rod/bar and tube - Part 2: Mechanical properties

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 754-2:2024 sisaldab Euroopa standardi EN 754-2:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 27.11.2024.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 754-2:2024 consists of the English text of the European standard EN 754-2:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 27.11.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.150.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN 754-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2024

ICS 77.150.10

Supersedes EN 754-2:2016

English Version

## Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Barres et tubes  
étirés - Partie 2 : Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Gezogene  
Stangen und Rohre - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 26 August 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
European foreword.....	4
<b>1 Scope</b> .....	<b>6</b>
<b>2 Normative references</b> .....	<b>6</b>
<b>3 Terms and definitions</b> .....	<b>6</b>
<b>4 Mechanical property limits</b> .....	<b>6</b>
4.1 <b>General</b> .....	6
4.2 <b>Elongation</b> .....	6
4.3 <b>Detailed tables of mechanical properties</b> .....	7
<b>Table 1 — Aluminium EN AW-1050A [Al 99,5(A)]</b> .....	<b>7</b>
<b>Table 2 — Aluminium EN AW-1070A [Al 99,7(A)]</b> .....	<b>7</b>
<b>Table 3 — Aluminium EN AW-1200 [Al 99,0]</b> .....	<b>8</b>
<b>Table 4 — Aluminium EN AW-1350A [Al 99,5(A)]</b> .....	<b>8</b>
<b>Table 5 — Alloy EN AW-2007 [Al Cu4PbMgMn]</b> .....	<b>9</b>
<b>Table 6 — Alloy EN AW-2011 [Al Cu6BiPb]</b> .....	<b>10</b>
<b>Table 7 — Alloy EN AW-2011A [Al Cu6BiPb(A)]</b> .....	<b>11</b>
<b>Table 8 — Alloy EN AW-2014 [Al Cu4SiMg]</b> .....	<b>12</b>
<b>Table 9 — Alloy EN AW-2014A [Al Cu4SiMg(A)]</b> .....	<b>13</b>
<b>Table 10 — Alloy EN AW-2017A [Al Cu4MgSi(A)]</b> .....	<b>14</b>
<b>Table 11— Alloy EN AW-2618A [AlCu2Mg1,5Ni(A)]</b> .....	<b>14</b>
<b>Table 12 — Alloy EN AW-2024 [Al Cu4Mg1]</b> .....	<b>15</b>
<b>Table 13 — Alloy EN AW-2030 [Al Cu4PbMg]</b> .....	<b>16</b>
<b>Table 14 — Alloy EN AW-2033 [Al Cu2,5MnSiMgBi]</b> .....	<b>17</b>
<b>Table 15 — Alloy EN AW-2077 [Al Cu4,5MgMnSiBi]</b> .....	<b>17</b>
<b>Table 16 — Alloy EN AW-3003 [Al Mn1Cu]</b> .....	<b>18</b>
<b>Table 17 — Alloy EN AW-3103 [Al Mn1]</b> .....	<b>19</b>
<b>Table 18 — Alloy EN AW-4032 [Al Si12,5MgCuNi]</b> .....	<b>20</b>
<b>Table 19 — Alloy EN AW-5005 [Al Mg1]</b> .....	<b>20</b>
<b>Table 20 — Alloy EN AW-5005A [Al Mg1]</b> .....	<b>21</b>
<b>Table 21 — Alloy EN AW-5019 [Al Mg5]</b> .....	<b>22</b>
<b>Table 22 — Alloy EN AW-5049 [Al Mg2Mn0,8]</b> .....	<b>23</b>
<b>Table 23 — Alloy EN AW-5251 [Al Mg2Mn0,3]</b> .....	<b>24</b>
<b>Table 24 — Alloy EN AW-5052 [Al Mg2,5]</b> .....	<b>25</b>
<b>Table 25 — Alloy EN AW-5154A [Al Mg3,5(A)]</b> .....	<b>26</b>

<b>Table 26 — Alloy EN AW-5754 [Al Mg<sub>3</sub>]</b> .....	<b>27</b>
<b>Table 27 — Alloy EN AW-5083 [Al Mg<sub>4,5</sub>Mn<sub>0,7</sub>]</b> .....	<b>28</b>
<b>Table 28 — Alloy EN AW-5086 [Al Mg<sub>4</sub>]</b> .....	<b>29</b>
<b>Table 29 — Alloy EN AW-6005 [AlSiMg]</b> .....	<b>29</b>
<b>Table 30 — Alloy EN AW-6005A [Al SiMg(A)]</b> .....	<b>30</b>
<b>Table 31 — Alloy EN AW-6005B [Al SiMg(B)]</b> .....	<b>30</b>
<b>Table 32 — Alloy EN AW-6012 [Al MgSiPb]</b> .....	<b>31</b>
<b>Table 33 — Alloy EN AW-6023 [Al Si<sub>1</sub>Sn<sub>1</sub>MgBi]</b> .....	<b>31</b>
<b>Table 34 — Alloy EN AW-6026 [Al MgSiBi]</b> .....	<b>32</b>
<b>Table 35 — Alloy EN AW-6050 [Al Si<sub>1,5</sub>FeMgNi]</b> .....	<b>32</b>
<b>Table 36 — Alloy EN AW-6056 [Al Si<sub>1</sub>MgCuMn]</b> .....	<b>33</b>
<b>Table 37 — Alloy EN AW-6060 [Al MgSi]</b> .....	<b>33</b>
<b>Table 38 — Alloy EN AW-6061 [Al Mg<sub>1</sub>SiCu]</b> .....	<b>34</b>
<b>Table 39 — Alloy EN AW-6061A [Al Mg<sub>1</sub>SiCu(A)]</b> .....	<b>34</b>
<b>Table 40 — Alloy EN AW-6262 [Al Mg<sub>1</sub>SiPb]</b> .....	<b>35</b>
<b>Table 41 — Alloy EN AW-6262A [Al Mg<sub>1</sub>SiSn(A)]</b> .....	<b>35</b>
<b>Table 42 — Alloy EN AW-6063 [Al Mg<sub>0,7</sub>Si]</b> .....	<b>36</b>
<b>Table 43 — Alloy EN AW-6063A [Al Mg<sub>0,7</sub>Si(A)]</b> .....	<b>37</b>
<b>Table 44 — Alloy EN AW-6064A [Al Mg<sub>1</sub>SiBi]</b> .....	<b>38</b>
<b>Table 45 — Alloy EN AW-6065 [Al Mg<sub>1</sub>Bi<sub>1</sub>Si]</b> .....	<b>38</b>
<b>Table 46 — Alloy EN AW-6082 [Al Si<sub>1</sub>MgMn]</b> .....	<b>39</b>
<b>Table 47 — Alloy EN AW-7020 [Al Zn<sub>4,5</sub>Mg<sub>1</sub>]</b> .....	<b>39</b>
<b>Table 48 — Alloy EN AW-7022 [Al Zn<sub>5</sub>Mg<sub>3</sub>Cu]</b> .....	<b>40</b>
<b>Table 49 — Alloy EN AW-7049A [Al Zn<sub>8</sub>MgCu(A)]</b> .....	<b>40</b>
<b>Table 50 — Alloy EN AW-7075 [Al Zn<sub>5,5</sub>MgCu]</b> .....	<b>41</b>
<b>Annex A (informative) List of tempers used in Tables 1 to 50</b> .....	<b>42</b>
<b>Bibliography</b> .....	<b>44</b>

## European foreword

This document (EN 754-2:2024) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2025, and conflicting national standards shall be withdrawn at the latest by May 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 754-2:2016.

Within its programme of work, Technical Committee CEN/TC 132 entrusted CEN/TC 132/WG 5 “Extruded and drawn products” to revise EN 754-2:2016.

EN 754-2:2024 includes the following significant technical changes with respect to EN 754-2:2016:

- addition of EN AW-1070A, EN AW-1350A, EN AW-2618A, EN AW-2033, EN AW-2077, EN AW-4032, EN AW-6005, EN AW-6005A, EN AW-6005B, EN AW-6023, EN AW-6050, EN AW-6056 and EN AW-6061A alloys;
- addition of the terms required by the latest CCMC template;
- addition of Clause 3 compulsory from the latest CCMC template;
- deletion of former Clause 3.3 as part of the table of contents in this document.

EN 754 comprises the following parts under the general title “Aluminium and aluminium alloys — Cold drawn rod/bar and tube”:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*

CEN/TC 132 affirms its policy that if a patentee refuses to grant licenses on standardized products under reasonable and not discriminatory conditions, this product will be removed from the corresponding document.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

This document is a preview generated by EVS

## 1 Scope

This document specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy cold drawn rod/bar and tube.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 754-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 754-1:2016, *Aluminium and aluminium alloys — Cold drawn rod/bar and tube — Part 1: Technical conditions for inspection and delivery*

## 3 Terms and definitions

No terms and definitions are listed in this document.

## 4 Mechanical property limits

### 4.1 General

The mechanical properties shall be in conformity with those specified in Table 1 to Table 50 or those agreed upon between supplier and purchaser and stated in the order document.

Definitions of tempers are provided at Annex A of this document. For all alloys the condition F (as fabricated) can be used, but without guaranteed mechanical properties.

Table 1 to Table 50 contain limits of mechanical property values obtained by tensile testing according to EN ISO 6892-1. Test pieces sampling, location in the specimen and preparation shall be as given in EN 754-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this document.

Brinell hardness values given in Table 1 to Table 50 expressed as HBW values are for information only.

### 4.2 Elongation

If not otherwise agreed, the  $A$  value shall be used.

The  $A$  value for elongation is the % elongation measured over a gauge length of  $5,65\sqrt{S_0}$  (where  $S_0$  is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on  $A_{50\text{mm}}$ . Consequently, values for the  $A_{50\text{mm}}$  are included in the following tables.

The  $A_{50\text{mm}}$  value is the elongation measured over a gauge length of 50 mm and expressed in percent.