

Corrosion of metals and alloys - Corrosion in artificial atmosphere - Accelerated corrosion test involving exposure under controlled conditions of humidity cycling and intermittent spraying of a salt solution (ISO 16701:2025)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 16701:2025 sisaldab Euroopa standardi EN ISO 16701:2025 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 25.06.2025.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 16701:2025 consists of the English text of the European standard EN ISO 16701:2025.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 25.06.2025.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.060

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 16701

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2025

ICS 77.060

Supersedes EN ISO 16701:2015

English Version

Corrosion of metals and alloys - Corrosion in artificial atmosphere - Accelerated corrosion test involving exposure under controlled conditions of humidity cycling and intermittent spraying of a salt solution (ISO 16701:2025)

Corrosion des métaux et alliages - Corrosion en atmosphère artificielle - Essai de corrosion accélérée comprenant des expositions sous conditions contrôlées à des cycles d'humidité et à des vaporisations intermittentes de solution saline (ISO 16701:2025)

Korrosion von Metallen und Legierungen - Korrosion in künstlicher Atmosphäre - Beschleunigte Korrosionsprüfungen unter zyklischer Einwirkung von Luftfeuchte und intermittierendem Versprühen einer Salzlösung unter kontrollierten Bedingungen (ISO 16701:2025)

This European Standard was approved by CEN on 7 June 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 16701:2025) has been prepared by Technical Committee ISO/TC 156 "Corrosion of metals and alloys" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2025, and conflicting national standards shall be withdrawn at the latest by December 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 16701:2015.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 16701:2025 has been approved by CEN as EN ISO 16701:2025 without any modification.

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	2
4.1 General.....	2
4.2 Basic properties of the climate test chamber.....	3
4.3 Supporting requisites and accessories.....	3
5 Test method	4
5.1 Test exposure conditions.....	4
5.2 Requirements on salt solution.....	10
5.3 Precipitation rate of salt solution.....	10
5.4 Start and end time of test.....	11
5.5 Duration of test.....	11
6 Test object conditions	11
6.1 Requirements on geometry and distribution.....	11
6.1.1 Test object orientation.....	11
6.1.2 Distribution of test objects.....	11
6.1.3 Mass and total exposed surface of test objects.....	11
6.1.4 Test object support.....	12
6.1.5 Test object exposure to salt spray.....	12
6.2 Test object preparation.....	13
6.2.1 Painted and scribed panels.....	13
6.2.2 Other test object geometries.....	13
6.2.3 Additional test conditions.....	13
7 Requirements on quality control and calibration	13
7.1 Overview.....	13
7.2 Climate control and calibration procedures.....	14
7.2.1 Definition of a climate deviation.....	14
7.2.2 Control procedure for basic compliance of test chamber.....	15
7.3 Control of salt solution precipitation.....	16
7.3.1 General.....	16
7.3.2 Spray rack according to the example in Annex B	16
7.3.3 Other configurations for salt solution downfall.....	17
7.3.4 Visual control of spray patterns.....	17
7.4 Recommended schedule for quality control.....	18
7.4.1 Control before test start.....	18
7.4.2 Workday inspection.....	18
7.4.3 Weekly inspection.....	18
7.4.4 Six-month controls.....	18
7.4.5 Annual calibration and verification.....	18
7.5 Deviation handling.....	19
7.5.1 General.....	19
7.5.2 Test interruption.....	19
8 Evaluation of results	19
9 Test report	19
Annex A (normative) Requirements on test equipment	21
Annex B (informative) Example of a device for spraying a precipitation of salt solution	25

Annex C (informative) Guidelines on devices for independent, stand-alone temperature and humidity monitoring	26
Annex D (normative) Temperature/humidity control procedures	27
Annex E (informative) Guiding information about the test method	30
Bibliography	38

This document is a preview generated by EVS

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 16701:2015), which has been technically revised.

The main changes are as follows:

- The test cycle has been revised with the same intended acceptance criteria to improve field correlation and reproducibility, when performed in various exposure chambers.
- An alternative cycle with alternating temperature in the climate cycling (constant dew point instead of constant temperature) is introduced. It is a modification of the so called ACT1 (originally Volvo Standard 423-0014), however within the same scope and intended acceptance criteria.
- Extensive requirements and guidelines on quality assurance of test equipment and control procedures have been incorporated, mainly as normative and informative annexes.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Atmospheric corrosion of metallic materials, with or without corrosion protection, is influenced by many environmental factors. Their corrosion impact varies with the type of exposed material system. It is therefore not possible to design a laboratory corrosion test in such a way that the complexity and variations of real, in-service conditions are fully represented. Acceleration (forced conditions) as such can also have a negative impact on the correlation-to-field performance. Nevertheless, tests with humidity cycling and only intermittent exposure to a salt solution provide a better correlation-to-field performance than tests using continuous salt spray.

This document was developed in the automotive context, where the major contributor to corrosion is the use of wintertime de-icing road salt in cool/cold temperate areas, most often as sodium chloride depositions that act in cyclic humidity conditions. The test procedure is moderately forced by humidity and salt. It is intended to be applicable for quality assurance of the metals and corrosion protections typically encountered in motor vehicles.^{[1]-[4]} The method is also relevant in other areas of application, provided they have similar climatic conditions with an influence of sodium chloride depositions.^{[5][6]}

Corrosion of metals and alloys — Corrosion in artificial atmosphere — Accelerated corrosion test involving exposure under controlled conditions of humidity cycling and intermittent spraying of a salt solution

1 Scope

This document specifies an atmospheric accelerated test procedure in two closely related variants that contain intermittent salt exposure combined with dynamic humidity patterns: variant A at constant dew point and variant B at constant temperature. These variants are used in assessing the corrosion resistance of metals in environments where there is a significant influence of chloride ions, mainly as sodium chloride from, for example, winter road de-icing salt. The results obtained do not permit far-reaching conclusions on the corrosion resistance of the tested metallic material under the whole range of environmental conditions in which it can be used. Nevertheless, the method provides information on the relative corrosion resistance of a material exposed to a salt-contaminated environment with varying humidity conditions.

The two accelerated laboratory corrosion test variants are applicable to:

- metals and their alloys (ferrous and non-ferrous);
- metallic coatings;
- chemical conversion coatings;
- organic coating on metals;
- a combination of materials and coatings that include galvanic interactions and/or crevice conditions.

NOTE 1 If testing low-alloy stainless steels according to this document, especially austenitic grades, there is a risk of exaggerated pitting, which is not representative of most service environments.

NOTE 2 This document is not suitable for testing of wax and oil-based rust protection agents, due to the constantly elevated temperature condition of the test.

This document also specifies requirements on the test equipment and contains detailed procedures for quality control, including recommended instrumentation.

This document does not specify the dimensions of the tests specimens, the exposure period to be used for a particular product, or the interpretation of the results. Such details are provided in the appropriate product specifications.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>