

Aluminium and aluminium alloys - Extruded rod/bar,
tube and profiles - Part 2: Mechanical properties

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 755-2:2025 sisaldab Euroopa standardi EN 755-2:2025 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 09.07.2025.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 755-2:2025 consists of the English text of the European standard EN 755-2:2025.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 09.07.2025.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.150.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 755-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2025

ICS 77.150.10

Supersedes EN 755-2:2016

English Version

Aluminium and aluminium alloys - Extruded rod/bar, tube and profiles - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Barres, tubes et
profilés filés - Partie 2 : Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen -
Stranggepresste Stangen, Rohre und Profile - Teil 2:
Mechanische Eigenschaften

This European Standard was approved by CEN on 26 August 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Mechanical property limits	7
4.1 General	7
4.2 Elongation	7
4.3 Tables of mechanical properties	8
Table 1 — Aluminium EN AW-1050A [Al 99,5(A)]	8
Table 2 — Aluminium EN AW-1070A [Al 99,7(A)]	9
Table 3 — Aluminium EN AW-1200 [Al 99,0]	9
Table 4 — Aluminium EN AW-1350 [Al 99,5]	10
Table 5 — Alloy EN AW-2007 [Al Cu₄PbMgMn]	11
Table 6 — Alloy EN AW-2011 [Al Cu₆BiPb]	12
Table 7 — Alloy EN AW-2011A [Al Cu₆BiPb(A)]	12
Table 8 — Alloy EN AW-2014 [Al Cu₄SiMg]	13
Table 9 — Alloy EN AW-2014A [Al Cu₄SiMg(A)]	14
Table 10 — Alloy EN AW-2017A [Al Cu₄MgSi(A)]	15
Table 11 — Alloy EN AW-2618A [Al Cu₂Mg_{1.5}Ni(A)]	16
Table 12 — Alloy EN AW-2024 [Al Cu₄Mg₁]	17
Table 13 — Alloy EN AW-2030 [Al Cu₄PbMg]	18
Table 14 — Alloy EN AW-2033 [Al Cu_{2,5}MnSiMgBi]	19
Table 15 — Alloy EN AW-2077 [Al Cu_{4,5}MgMnSiBi]	20
Table 16 — Alloy EN AW-3102 [Al Mn_{0,2}]	21
Table 17 — Alloy EN AW-3003 [Al Mn₁Cu]	22
Table 18 — Alloy EN AW-3103 [Al Mn₁]	23
Table 19 — Alloy EN AW-4032 [Al Si_{12,5}MgCuNi]	23
Table 20 — Alloy EN AW-5005 [Al Mg₁]	24
Table 21 — Alloy EN AW-5005A [Al Mg₁(A)]	25
Table 22 — Alloy EN AW-5019 [Al Mg₅]	26
Table 23 — Alloy EN AW-5049 [Al Mg₂Mn_{0,8}]	27
Table 24 — Alloy EN AW-5051A [Al Mg₂(A)]	28
Table 25 — Alloy EN AW-5251 [Al Mg₂Mn_{0,3}]	29

Table 26 — Alloy EN AW-5052 [Al Mg _{2,5}]	30
Table 27 — Alloy EN AW-5154A [Al Mg _{3,5} (A)]	31
Table 28 — Alloy EN AW-5454 [Al Mg ₃ Mn]	32
Table 29 — Alloy EN AW-5754 [Al Mg ₃]	33
Table 30 — Alloy EN AW-5083 [Al Mg _{4,5} Mn _{0,7}]	34
Table 31 — Alloy EN AW-5086 [Al Mg ₄]	35
Table 32 — Alloy EN AW-6101A [Al MgSi(A)]	36
Table 33 — Alloy EN AW-6101B [Al MgSi(B)]	37
Table 34 — Alloy EN AW-6005 [Al SiMg]	38
Table 35 — Alloy EN AW-6005A [Al SiMg(A)]	39
Table 36 — Alloy EN AW-6106 [Al MgSiMn]	40
Table 37 — Alloy EN AW-6008 [Al SiMgV]	41
Table 38 — Alloy EN AW-6110A [Al Mg _{0,9} Si _{0,9} MnCu(A)]	42
Table 39 — Alloy EN AW-6012 [Al MgSiPb]	43
Table 40 — Alloy EN AW-6014 [Al Mg _{0,6} SiV]	44
Table 41 — Alloy EN AW-6018 [Al Mg ₁ SiPbMn]	45
Table 42 — Alloy EN AW-6023 [AlSi ₁ Sn ₁ MgBi]	46
Table 43 — Alloy EN AW-6026 [Al MgSiBi]	46
Table 44 — Alloy EN AW-6050 [Al Si _{1,5} FeMgNi]	47
Table 45 — Alloy EN AW-6351 [Al Si ₁ Mg _{0,5} Mn]	47
Table 46 — Alloy EN AW-6056 [AlSi ₁ MgCuMn]	49
Table 47 — Alloy EN AW-6060 [Al MgSi]	50
Table 48 — Alloy EN AW-6360 [Al SiMgMn]	51
Table 49 — Alloy EN AW-6061 [Al Mg ₁ SiCu]	52
Table 50 — Alloy EN AW-6061A [Al Mg ₁ SiCu(A)]	53
Table 51 — Alloy EN AW-6261 [Al Mg ₁ SiCuMn]	53
Table 52 — Alloy EN AW-6262 [Al Mg ₁ SiPb]	54
Table 53 — Alloy EN AW-6262A [Al Mg ₁ SiSn]	55
Table 54 — Alloy EN AW-6063 [Al Mg _{0,7} Si]	55
Table 55 — Alloy EN AW-6063A [Al Mg _{0,7} Si(A)]	57
Table 56 — Alloy EN AW-6463 [Al Mg _{0,7} Si(B)]	58
Table 57 — Alloy EN AW-6064A [Al Mg ₁ SiBi(A)]	59
Table 58 — Alloy EN AW-6065 [Al Mg ₁ Bi ₁ Si]	60
Table 59 — Alloy EN AW-6081 [Al Si _{0,9} MgMn]	61
Table 60 — Alloy EN AW-6082 [Al Si ₁ MgMn]	62
Table 61 — Alloy EN AW-6182 [Al Si ₁ MgZr]	63

Table 62 — Alloy EN AW-7003 [Al Zn6Mg0,8Zr]	64
Table 63 — Alloy EN AW-7005 [Al Zn4,5Mg1,5Mn]	65
Table 64 — Alloy EN AW-7108 [Al Zn5Mg1Zr]	66
Table 65 — Alloy EN AW-7108A [Al Zn5Mg1Zr(A)]	67
Table 66 — Alloy EN AW-7020 [Al Zn4,5Mg1]	68
Table 67 — Alloy EN AW-7021 [Al Zn5,5Mg1,5]	69
Table 68 — Alloy EN AW-7022 [Al Zn5Mg3Cu]	70
Table 69 — Alloy EN AW-7049A [Al Zn8MgCu(A)]	71
Table 70 — EN AW-7075 [Al Zn5,5MgCu]	72
Annex A (informative) List of tempers used in Tables 1 to 70 (extract of EN 515)	73
Bibliography	75

European foreword

This document (EN 755-2:2025) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2026, and conflicting national standards shall be withdrawn at the latest by January 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 755-2:2016.

Within its programme of work, Technical Committee CEN/TC 132 entrusted CEN/TC 132/WG 5 “Extruded and drawn products” to revise EN 755-2:2016.

EN 755-2:2025 includes the following significant technical changes with respect to EN 755-2:2016:

- addition of EN AW-2033, EN AW-2077, EN AW-4032, EN AW-6050 and EN AW-6061A alloys;
- addition of the terms required by the latest CCMC template;
- addition of Clause 3 compulsory from the latest CCMC template;
- deletion of former Clause 3.3 as part of the table of contents in this document;
- correction to temper of EN AW-2024 alloy.

EN 755 comprises the following parts under the general title “Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles”:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*
- *Part 9: Profiles, tolerances on dimensions and form*

CEN/TC 132 affirms its policy that if a patentee refuses to grant licenses on standardized products under reasonable and not discriminatory conditions, this product will be removed from the corresponding document.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia,

Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy extruded rod/bar, tube and profile.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 755-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 755-1, *Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles — Part 1: Technical conditions for inspection and delivery*

3 Terms and definitions

No terms and definitions are listed in this document.

4 Mechanical property limits

4.1 General

The mechanical properties shall be in conformity with those specified in Table 1 to Table 70 or those agreed upon between supplier and purchaser and stated in the order document.

For all alloys the temper F (as fabricated) can be used, but without guaranteed mechanical properties. Definitions of tempers are provided at Annex A of this document.

Table 1 to Table 70 contain limits of mechanical property values obtained by tensile testing according to EN ISO 6892-1. Test pieces sampling, location in the specimen and preparation shall be as given in EN 755-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Table 1 to Table 70 expressed as HBW values are for information only.

4.2 Elongation

If not otherwise agreed, the A value shall be used.

The A value for elongation is the % elongation measured over a gauge length of $5,65\sqrt{S_0}$ (where S_0 is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on $A_{50\text{mm}}$. Consequently, values for the $A_{50\text{mm}}$ are included in the following tables.

The $A_{50\text{mm}}$ value is the elongation measured over a gauge length of 50 mm and expressed in percent.