

This document is a preview generated by EVS

Environmental solid matrices - Determination of the specific electrical conductivity (ISO 11265:2025)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 11265:2025 sisaldab Euroopa standardi EN ISO 11265:2025 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 10.09.2025.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 11265:2025 consists of the English text of the European standard EN ISO 11265:2025.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 10.09.2025.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 13.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 11265

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2025

ICS 13.080.20

Supersedes CEN/TS 15937:2013

English Version

Environmental solid matrices - Determination of the specific electrical conductivity (ISO 11265:2025)

Matrices solides environnementales - Détermination de la conductivité électrique spécifique (ISO 11265:2025)

Feste Umweltmatrizes - Bestimmung der spezifischen elektrischen Leitfähigkeit (ISO 11265:2025)

This European Standard was approved by CEN on 23 August 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 11265:2025) has been prepared by Technical Committee ISO/TC 190 "Soil quality" in collaboration with Technical Committee CEN/TC 444 "Environmental characterization of solid matrices" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2026, and conflicting national standards shall be withdrawn at the latest by March 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15937:2013.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 11265:2025 has been approved by CEN as EN ISO 11265:2025 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Laboratory sample	2
8 Procedure	3
8.1 Extraction.....	3
8.2 Checking of the cell constant.....	3
8.3 Measurement of the electrical conductivity of the filtrates.....	4
9 Interferences	4
10 Repeatability	5
11 Test report	5
Annex A (informative) Results of an interlaboratory trial for the determination of the specific electrical conductivity of soils	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 190, *Soil quality*, Subcommittee SC 3, *Chemical and physical characterization*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 444, *Environmental characterization of solid matrices*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 11265:1994), which has been technically revised. It also incorporates the Technical Corrigendum ISO 11265:1994/Cor 1:1996.

The main changes are as follows:

- change of temperature criteria during extraction;
- the distinction between solid and sludge-like matrices is added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Environmental solid matrices — Determination of the specific electrical conductivity

1 Scope

This document specifies an instrumental method for the routine determination of the specific electrical conductivity in an aqueous extract of soil, sludge, biowaste or waste. The determination is carried out to obtain an indication of the content of water-soluble electrolytes in a sample.

This document is applicable to all types of air-dried samples of soil, sludge, biowaste and waste.

2 Normative references

The following documents are referred to in the text in such a way that some or all their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11464, *Soil quality — Pretreatment of samples for physico-chemical analysis*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

Air-dried solids are extracted with water at (22 ± 3) °C at an extraction ratio of 1:5 (m/V), to dissolve the electrolytes. The specific electrical conductivity of the extract or fresh liquid sludge is measured, and the result is corrected to a temperature of 25 °C.

NOTE For definitions of the concepts used, see ISO 7888.

5 Reagents

Use only reagents of recognized analytical grade.

5.1 Water, demineralized, with a specific electrical conductivity not higher than 0,2 mS/m at 25 °C.

5.2 Potassium chloride solution, $c(\text{KCl}) = 0,1$ mol/l.

Dissolve 7,456 g of potassium chloride, previously dried for 2 h at (105 ± 5) °C in water (5.1), and dilute to 1 000 ml at 20 °C. The specific electrical conductivity of this solution is 1 288 mS/m at 25 °C.