

Plastics piping systems for hot and cold water installations - Crosslinked polyethylene (PE-X) - Part 3: Fittings (ISO 15875-3:2025)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 15875-3:2025 sisaldab Euroopa standardi EN ISO 15875-3:2025 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 29.10.2025.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 15875-3:2025 consists of the English text of the European standard EN ISO 15875-3:2025.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 29.10.2025.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 23.040.45, 91.140.60

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 15875-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2025

ICS 23.040.45; 91.140.60

Supersedes EN ISO 15875-3:2003, EN ISO 15875-3:2003/A1:2020, EN ISO 15875-3:2003/A2:2021

English Version

Plastics piping systems for hot and cold water installations
- Crosslinked polyethylene (PE-X) - Part 3: Fittings (ISO
15875-3:2025)

Systèmes de canalisations en plastique pour les installations d'eau chaude et froide - Polyéthylène réticulé (PE-X) - Partie 3: Raccords (ISO 15875-3:2025)

Kunststoff-Rohrleitungssysteme für die Warm- und Kaltwasserinstallation - Vernetztes Polyethylen (PE-X) - Teil 3: Formstücke (ISO 15875-3:2025)

This European Standard was approved by CEN on 23 October 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 15875-3:2025) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2026, and conflicting national standards shall be withdrawn at the latest by April 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15875-3:2003, EN ISO 15875-3:2003/A1:2020, EN ISO 15875-3:2003/A2:2021.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 15875-3:2025 has been approved by CEN as EN ISO 15875-3:2025 without any modification.

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms, definitions and symbols	2
3.1 Terms and definitions.....	2
3.1.1 General.....	2
3.1.2 Mechanical fittings.....	3
3.2 Symbols.....	4
4 Generic requirements, instructions and explanations	4
4.1 Designation PE-X.....	4
4.2 Application classes, design pressures and pipe dimension classes restrictions.....	4
4.3 Application classes — Responsibility of the purchaser or specifier.....	4
4.4 Use of the parts of the ISO 15875 series.....	5
4.5 Completeness of tests.....	5
4.6 Test result interchangeability restriction.....	5
5 Material characteristics	5
5.1 Plastics fitting body material subjected to hydrostatic stress.....	5
5.2 Plastics material of auxiliary fittings parts subjected to mechanical stress.....	8
5.3 Metallic fitting body material.....	8
5.4 Influence on water intended for human consumption.....	8
6 General characteristics	8
6.1 Appearance.....	8
6.1.1 Appearance of plastic fittings.....	8
6.1.2 Appearance of metal fittings.....	9
6.2 Opacity.....	9
7 Geometrical characteristics	9
7.1 General.....	9
7.1.1 Overview.....	9
7.1.2 Nominal diameter(s).....	9
7.1.3 Angles.....	9
7.1.4 Threads.....	9
7.2 Dimensions of sockets for electro-fusion fittings.....	9
7.3 Dimensions of metallic fittings — Minimum wall thickness of fittings made of copper alloys.....	11
8 Mechanical characteristics of plastics fittings	11
8.1 General.....	11
8.2 Fitting made from a PE-X material.....	12
8.3 Fitting made from plastics material other than PE-X and specified by an ISO standard according to Annex B	13
8.4 Fitting made from plastics material not specified by an ISO standard according to Annex B	14
9 Physical and chemical characteristics	15
9.1 Physical and chemical characteristics of plastics fittings.....	15
9.1.1 Thermal stability.....	15
9.1.2 Degree of crosslinking and Melt flow rate.....	16
9.2 Physical and chemical characteristics of metallic fittings.....	16
9.2.1 Fittings made of copper alloys — Resistance to stress corrosion.....	16
9.2.2 Fittings made of copper alloys — Resistance to dezincification.....	16
9.2.3 Metallic fittings made from cast alloys — Tightness test.....	17
10 Sealing elements	17

11	Performance requirements	17
12	Marking	17
	12.1 General requirements	17
	12.2 Minimum required marking.....	17
Annex A	(normative) Dimensional requirements for metallic fittings	19
Annex B	(normative) ISO standards defining plastics material to be used for components in hot and cold applications inside buildings	21
Annex C	(normative) Plastics material of auxiliary fitting parts subjected to mechanical stress	22
Bibliography	25

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 15875-3:2003), which has been technically revised. It also incorporates the Amendments ISO 15875-3:2003/Amd. 1:2020 and ISO 15875-3:2003/Amd. 2:2021.

- clarification has been added concerning plastics fitting body material not identical to PE-X due to a distinction between:
 - plastics fitting body material not identical to PE-X, but specified by other ISO documents;
 - plastics fitting body material not identical to PE-X and not specified by other ISO documents;
- a new clause for plastics material of auxiliary fittings parts subjected to mechanical stress in [5.2](#);
- a 2 500 h at 95 °C confirmation test has been introduced in [5.1.2](#), [5.1.3](#) and [5.1.4](#).

A list of all parts in the ISO 15875 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 15875 series specifies the requirements for a piping system consisting of pipe, fitting and the jointing made of it, when the pipe is made from crosslinked polyethylene (PE-X). The ISO 15875 series consists of ISO 15875-1, ISO 15875-2, ISO 15875-2 and ISO 15875-5, and covers the requirements and related test methods for all components used in the system (e. g. pipes and fittings). In addition, the ISO 15875 series includes requirements and related test methods to verify the performance and compatibility of the jointing of components.

The piping system is intended to be used for hot and cold water installations.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by the ISO 15875 series:

- the ISO 15875 series provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

Requirements and test methods for materials and components, other than fittings, are specified in ISO 15875-1 and ISO 15875-2. Characteristics for fitness for purpose (mainly for joints) are covered in ISO 15875-5. ISO/TS 15875-7 gives guidance for the assessment of conformity.

This document specifies the characteristics of the fittings.

At the date of publication of this document, standards for piping systems of other plastics materials used for the same application include

- the ISO 15874 series,
- the ISO 15875 series,
- the ISO 15876 series,
- the ISO 15877 series,
- the ISO 21003 series, and
- the ISO 22391 series.

Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X) —

Part 3: Fittings

1 Scope

This document specifies the characteristics of fittings for crosslinked polyethylene (PE-X) piping systems intended to be used for hot and cold water installations within buildings for the conveyance of water, whether or not intended for human consumption (domestic systems) and for heating systems under design pressures and temperatures according to the class of application (see ISO 15875-1:—, Table 1).

This document also specifies the test parameters for the test methods referred to herein.

This document is applicable to fittings made from PE-X or other plastics or non-plastics materials, which are intended to be connected to pipes conforming to ISO 15875-2 for hot and cold water installations, whereby the joints conform to the requirements of ISO 15875-5.

This document is applicable to fittings of the following types:

- mechanical fittings;
- electrofusion fittings;

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments).

ISO 228-1, *Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation*

ISO 527-2:2025, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-3, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 3: Preparation of components*

ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies*

ISO 2768-1, *General tolerances — Part 1: Tolerances for linear and angular dimensions without individual tolerance indications*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 6259-1:2015, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method*

ISO 6509-1, *Corrosion of metals and alloys — Determination of dezincification resistance of copper alloys with zinc — Part 1: Test method*

ISO 6957, *Copper alloys — Ammonia test for stress corrosion resistance*

ISO 7686, *Plastics pipes and fittings — Determination of opacity*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 10147, *Pipes and fittings made of crosslinked polyethylene (PE-X) — Estimation of the degree of crosslinking by determination of the gel content*

ISO 15875-1, *Plastics piping system for hot and cold water installations — crosslinked polyethylene (PE-X) — Part 1: General*

ISO 15875-2, *Plastics piping system for hot and cold water installations — crosslinked polyethylene (PE-X) — Part 2: Pipes*

ISO 15875-5, *Plastics piping system for hot and cold water installations — crosslinked polyethylene (PE-X) — Part 5: Fitness for purpose of the system*

EN 681-1, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber*

EN 681-2, *Elastomeric seals — Materials requirements for pipe joint seals used in water and drainage applications — Part 2: Thermoplastic elastomers*

EN 10226-1, *Pipe threads where pressure-tight joints are made on the threads — Part 1: Taper external threads and parallel internal threads — Dimensions, tolerances and designation*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 15875-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1.1 General

3.1.1.1 fitting

component of a piping system, which connects two or more pipes and/or fittings together, without any further function

3.1.1.2 tolerance

permitted variation of the specified value of a quantity, expressed as the difference between the permitted maximum and the permitted minimum value

3.1.1.3 control point

pressure test parameters to verify compliance with the predicted hydrostatic strength