



**International
Standard**

ISO 13956

**Plastics pipes and fittings —
Decohesion test of polyethylene
(PE) saddle fusion joints —
Evaluation of ductility of fusion
joint interface by tear test**

*Tubes et raccords en matières plastiques — Essai de décohésion
des selles en polyéthylène (PE) assemblées par soudage —
Évaluation de la ductilité de l'interface de soudage par essai
d'arrachement*

**Second edition
2025-11**

This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
5.1 General.....	1
5.2 Tensile test equipment — Type A1 or A2.....	1
5.3 Compressive test equipment — Type B.....	3
5.4 Test equipment — Type C.....	3
6 Sampling	4
6.1 Preparation of test pieces.....	4
6.2 Number of test pieces.....	5
7 Conditioning	5
8 Procedure	5
9 Test report	7
Annex A (informative) Recommendation	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 13956:2010), which has been technically revised.

The main changes are as follows:

- a Note has been added to the scope;
- guidance on assessment of air pockets in the fusion zone has been given in [Clause 8](#), [Figure 5](#) and [Figure 6](#);
- symbols have been aligned with relevant ISO documents;
- [Figure 5](#) has been corrected.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics pipes and fittings — Decohesion test of polyethylene (PE) saddle fusion joints — Evaluation of ductility of fusion joint interface by tear test

1 Scope

This document specifies a method for the evaluation of the ductility of the fusion joint interface of assemblies of polyethylene (PE) pipe and electrofusion saddles, intended for the conveyance of fluids.

NOTE The applicability of this method depends upon the design of the saddle. If not applicable, the strip-bend test according to ISO 21751^[1] is considered an alternative.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

A load is applied to the saddle of an assembly of an electrofusion saddle fused onto pipe.

The ductility of the fusion joint interface is characterised by the appearance of the failure in the fusion plane and by the determination of the percentage of brittle fracture.

5 Apparatus

5.1 General

The test apparatus shall comprise a tensile equipment type A1 or A2, as indicated in [Figures 1](#) and [2](#) respectively, or a compressive equipment type B as indicated in [Figure 3](#). For nominal outside pipe diameter ≥ 250 mm, equipment type C as indicated in [Figure 4](#) can be used.

5.2 Tensile test equipment — Type A1 or A2

The tensile equipment shall include the following main parts:

- a) **tensile testing machine**, capable of maintaining a speed of (100 ± 10) mm/min, with sufficient force to separate the saddle from the pipe;
- b) **loading pin**, with an outside diameter of at least $\frac{1}{2}$ nominal outside diameter of the pipe and allowing rotation;