
**Fibre-reinforced plastics — Methods of
producing test plates —**

Part 1:
General conditions

*Plastiques renforcés de fibres — Méthodes de fabrication de plaques
d'essai —*

Partie 1: Conditions générales



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Health and safety	2
5 Principle.....	2
6 Raw materials and semi-finished products	2
7 Plate dimensions	2
8 Reinforcement.....	2
9 General requirements for the laboratory/workshop apparatus	2
10 Procedure	3
11 Verification of the characteristics of the plates obtained	3
12 Marking	3
13 Test plate preparation report.....	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 1268 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1268-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

Together with the other parts (see below), this part of ISO 1268 cancels and replaces ISO 1268:1974, which has been technically revised.

ISO 1268 consists of the following parts, under the general title *Fibre-reinforced plastics — Methods of producing test plates*:

- *Part 1: General conditions*
- *Part 2: Contact and spray-up moulding*
- *Part 3: Wet compression moulding*
- *Part 4: Moulding of prepregs*
- *Part 5: Filament winding*
- *Part 6: Pultrusion moulding*
- *Part 7: Resin transfer moulding*
- *Part 8: Compression moulding of SMC and BMC*
- *Part 9: Moulding of GMT/STC*
- *Part 10: Injection moulding of SMC and other long-fibre moulding compounds — General principles and moulding of multipurpose test specimens*
- *Part 11: Injection moulding of SMC and other long-fibre moulding compounds — Small plates*

Fibre-reinforced plastics — Methods of producing test plates —

Part 1:

General conditions

1 Scope

The various parts of ISO 1268 (see the foreword) describe methods used to prepare reinforced-plastics plates from which test specimens can be cut. This allows the properties of a composite, or the constituents of the composite, to be determined. The methods are intended to cover all the main types of reinforcement and resin matrix.

The choice of test plate preparation method depends on:

- a) the reinforcement:
 - its nature (glass, carbon, aramid, etc.);
 - its form (roving, mat, woven fabric, etc.);
 - its orientation with respect to the length, width and thickness of the plate;
 - its content in the reinforced plastic;
- b) the matrix (thermosetting or thermoplastic);
- c) the magnitude expected for the properties;
- d) the production process that is to be evaluated.

Since the mechanical properties of a reinforced plastic are known to be dependent on the process by which the plastic is produced, it is recommended that the test plates be prepared, if possible, by the same method that will be used to produce the plastic.

This part of ISO 1268 describes the general requirements common to all the methods.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 1268. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 1268 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 472, *Plastics — Vocabulary*

ISO 1172, *Textile-glass-reinforced plastics — Prepregs, moulding compounds and laminates — Determination of the textile-glass and mineral-filler content — Calcination methods*

ISO 1268-1:2001(E)

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 7822, *Textile glass reinforced plastics — Determination of void content — Loss on ignition, mechanical disintegration and statistical counting methods*

ISO 10724-2:1998, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 2: Small plates*

3 Terms and definitions

For the purposes of this part of ISO 1268, the terms and definitions given in ISO 472 apply. Each subsequent part of ISO 1268 gives, where necessary, the definitions of specific terms it needs to introduce.

4 Health and safety

The various parts of ISO 1268 are limited to describing test plate preparation methods. The conditions under which the materials used are handled shall comply with the national regulations in force in each country and the staff shall be informed of the hazards involved and appropriate precautions taken.

5 Principle

Subsequent parts of this International Standard describe the basic methods utilized to produce test plates.

6 Raw materials and semi-finished products

All the materials used (reinforcements, resins, additives; SMC, BMC, prepregs, etc.) shall be identified in a precise manner. They shall be stored under the conditions recommended by the manufacturer and shall be used before the expiration date marked on the label.

7 Plate dimensions

The length, width and thickness of the plates produced will depend on the material being processed and the method used to produce them. The dimensions shall be as specified in the relevant part of this International Standard.

NOTE The plate dimensions will also depend on the test which will be conducted on the test specimens cut from the plates. For example, a square plate of side at least 250 mm is required to perform tensile tests in two perpendicular directions.

8 Reinforcement

The reinforcement content of the plate shall be the same as in the finished products whose properties are to be evaluated. In the absence of particular specifications, use the recommended content given in the relevant part of this International Standard.

9 General requirements for the laboratory/workshop apparatus

Unless otherwise specified, the apparatus used to produce the plates shall be capable of maintaining the required temperatures and pressures to within the accuracy prescribed for the chosen plate production method.