

**Metallilised pinnakatted. Elektrosadestatud kullast ja kullasulamist pinnatöötlusmaterjalid elektrilistele, elektroonilistele ja insenertehnilistele rakendustele. Spetsifikatsioonid ja katsemeetodid**

Metallic coatings - Electrodeposited gold and gold alloy coatings for electrical, electronic and engineering purposes - Specification and test methods

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 27874:2008 sisaldab Euroopa standardi EN ISO 27874:2008 ingliskeelset teksti.</p> <p>Standard on kinnitatud Eesti Standardikeskuse 15.12.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.09.2008.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 27874:2008 consists of the English text of the European standard EN ISO 27874:2008.</p> <p>This standard is ratified with the order of Estonian Centre for Standardisation dated 15.12.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p> <p>Date of Availability of the European standard text 15.09.2008.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

ICS 25.220.40

Võtmesõnad:

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

ICS 25.220.40

English Version

**Metallic and other inorganic coatings - Electrodeposited gold and gold alloy coatings for electrical, electronic and engineering purposes - Specification and test methods (ISO 27874:2008)**

Revêtements métalliques et autres revêtements inorganiques - Dépôts électrolytiques d'or et d'alliages d'or pour usages électrique, électronique et industriels - Spécification et méthodes d'essai (ISO 27874:2008)

Metallische Überzüge - Galvanische Gold- und Goldlegierungsüberzüge für elektrische, elektronische und technische Zwecke - Anforderungen und Prüfverfahren (ISO 27874:2008)

This European Standard was approved by CEN on 13 September 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Foreword

This document (EN ISO 27874:2008) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2009, and conflicting national standards shall be withdrawn at the latest by March 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 27874:2008 has been approved by CEN as a EN ISO 27874:2008 without any modification.

## Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Information to be supplied to the electroplater</b> .....	<b>3</b>
<b>5 Designation</b> .....	<b>4</b>
<b>6 Requirements and test methods</b> .....	<b>6</b>
<b>7 Sampling</b> .....	<b>9</b>
<b>Annex A (normative) Requirements for undercoats</b> .....	<b>10</b>
<b>Annex B (normative) Methods of measuring the thickness of gold and gold alloy coatings</b> .....	<b>12</b>
<b>Annex C (normative) Adhesion tests</b> .....	<b>20</b>
<b>Annex D (normative) Determination of gold content</b> .....	<b>22</b>
<b>Bibliography</b> .....	<b>24</b>

## Introduction

The engineering uses of electrodeposited gold and gold alloy coatings have expanded with the growth of the electrical and electronic industries. Low voltages and currents, dry circuits and microwave frequencies require low-resistance interconnection systems, connectors and waveguides. Non-tarnishing, low-resistance gold coatings were the logical choice for connectors where the stability of contact surfaces was critical. The need to improve the wear resistance of gold coatings led to the development of new electroplating solutions containing controlled amounts of metallic and non-metallic additives that either changed the composition or altered the crystal structure of the coating. The special needs of the printed-circuit industry led to the development of acid gold electroplating solutions that contained no free cyanide, yielding coatings that are hard, bright and solderable. Formulations for high-speed electroplating up to current densities of  $200 \text{ A/dm}^2$  were introduced for continuous strip, stripe or spot gold and gold alloy coatings.

The high cost of gold metal has led to the development of selective and thickness profile plating techniques to limit the use of the metal to the active areas only of the components, where the gold is required. Designers will therefore often specify the area requiring gold electroplating as well as the thickness profile, if required, by reference to suitably marked drawings.

With the introduction of many new gold electroplating formulations and the proliferation of engineering applications, the need for technical standards that specify the requirements of electrodeposited gold and gold alloy coatings, as well as the test methods to ensure that the specified requirements are met, is critical. Composition, appearance, hardness, thickness, purity, porosity, wear resistance, solderability, electrical contact resistance, infrared reflectivity and other properties must be controlled to produce high-quality gold and gold alloy coatings for engineering purposes.

# Metallic and other inorganic coatings — Electrodeposited gold and gold alloy coatings for electrical, electronic and engineering purposes — Specification and test methods

**WARNING** — This International Standard may not be compliant with some countries' health, safety and environmental legislations. It calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This International Standard does not address any health hazards, safety or environmental matters, or legislation associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health, safety and environmentally acceptable practices and take appropriate action to comply with any national, regional and/or international regulations. Compliance with this International Standard does not, of itself, confer immunity from legal obligations.

## 1 Scope

This International Standard specifies the requirements for electrodeposited gold and gold alloy coatings for electrical, electronic and other engineering applications on metallic and non-metallic substrates. It also specifies test methods for measuring the properties of the coatings.

Although this International Standard does not specify the condition, finish or surface roughness of the basis material prior to electroplating, the appearance and serviceability of electroplated gold or gold alloy coatings depends on the condition of the basis material. It is essential that the purchaser specify the surface finish and roughness of the basis material in order to conform to the product requirements.

This International Standard does not apply to coatings on threaded articles or to coatings on sheet or strip in non-fabricated form.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*

ISO 2819, *Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3868, *Metallic and other non-organic coatings — Measurement of coating thicknesses — Fizeau multiple-beam interferometry method*

ISO 3882, *Metallic and other inorganic coatings — Review of methods of measurement of thickness*

ISO 4516, *Metallic and other inorganic coatings — Vickers and Knoop microhardness tests*

ISO 4518, *Metallic coatings — Measurement of coating thickness — Profilometric method*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 4524-2, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 2: Mixed flowing gas (MFG) environmental tests*

ISO 4524-3:1985, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 3: Electrographic tests for porosity*

ISO 4524-6, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 6: Determination of the presence of residual salts*

ISO 9587, *Metallic and other inorganic coatings — Pretreatment of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 10289, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests*

ISO 10308, *Metallic coatings — Review of porosity tests*

ISO 12687, *Metallic coatings — Porosity tests — Humid sulfur (flowers of sulfur) test*

ISO 14647, *Metallic coatings — Determination of porosity in gold coatings on metal substrates — Nitric acid vapour test*

IEC 60068-2-20, *Environmental testing — Part 2-20: Tests — Test T: Test methods for solderability and resistance to soldering heat of devices with leads*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in ISO 2064 and ISO 2080 and the following apply.

#### **3.1**

##### **gold or gold alloy coating**

electrodeposited gold or gold alloy having intentional alloying elements in its composition

#### **3.2**

##### **double-layer gold or gold alloy coating**

gold or gold alloy coating consisting of two discrete layers of differing gold contents

#### **3.3**

##### **multilayer gold or gold alloy coating**

gold or gold alloy coating consisting of more than two discrete layers of differing gold contents