

**Testing fresh concrete - Part 12: Self-compacting
concrete - J-ring test**

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 12350-12:2010 sisaldab Euroopa standardi EN 12350-12:2010 ingliskeelset teksti.</p> <p>Standard on kinnitatud Eesti Standardikeskuse 30.09.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 21.07.2010.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 12350-12:2010 consists of the English text of the European standard EN 12350-12:2010.</p> <p>This standard is ratified with the order of Estonian Centre for Standardisation dated 30.09.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p> <p>Date of Availability of the European standard text 21.07.2010.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

ICS 91.100.30

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

ICS 91.100.30

English Version

Testing fresh concrete - Part 12: Self-compacting concrete - J-ring test

Essai pour béton frais - Partie 12 : Béton auto-plaçant -
Essai d'écoulement à l'anneau

Prüfung von Frischbeton - Teil 12: Selbstverdichtender
Beton - Blockierring-Versuch

This European Standard was approved by CEN on 20 June 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	5
2 Normative references	5
3 Principle	5
4 Apparatus	5
5 Test sample	7
6 Procedure	7
7 Expression of results	8
8 Test report	8
9 Repeatability and reproducibility	9
Bibliography	10

Foreword

This document (EN 12350-12:2010) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2011, and conflicting national standards shall be withdrawn at the latest by January 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

This standard is based on the results from the EU-project "Testing-SCC" under the 5th Frame Programme (GRD2-2000-30024/G6RD-CT-2001-00580).

Owing to its significant advantages in the improvement of construction quality and working environment, self-compacting concrete (SCC) has been widely accepted by the construction owners. The use of SCC in practical concrete construction is steadily increasing. Since SCC has to give satisfactory in-situ properties (perfect filling of the mould and embedment of the reinforcement, homogeneity and full compaction) without vibration, the proper methods for testing fresh SCC are very important. The consistence of fresh SCC should basically include three key properties: filling ability, passing ability and resistance to segregation. It is desirable, especially in the case of new constituents or new concrete compositions, to test the consistence of fresh SCC before casting in place.

A number of test methods including this test are available for testing fresh SCC. Most of the commonly used test methods were evaluated in the recently closed EU-project "Testing-SCC" under the 5th Frame Programme (GRD2-2000-30024/G6RD-CT-2001-00580). According to the results from this EU project, it seems no single test method can completely cover all the three key properties. Nevertheless any test method should at least be correlated to the practical situation and give consistent results in order to provide reliable data for judgment of concrete workability.

This standard is one of a series concerned with testing fresh concrete.

EN 12350, *Testing fresh concrete*, consists of the following parts:

- *Part 1: Sampling*
- *Part 2: Slump-test*
- *Part 3: Vebe test*
- *Part 4: Degree of compactability*
- *Part 5: Flow table test*
- *Part 6: Density*
- *Part 7: Air content — Pressure methods*
- *Part 8: Self-compacting concrete — Slump-flow test*

- *Part 9: Self-compacting concrete — V-funnel test*
- *Part 10: Self-compacting concrete — L box test*
- *Part 11: Self-compacting concrete — Sieve segregation test*
- *Part 12: Self-compacting concrete — J-ring test*

CAUTION — When cement is mixed with water, alkali is released. Take precautions to avoid dry cement entering the eyes, mouth and nose whilst mixing concrete. Prevent skin contact with wet cement or concrete by wearing suitable protective clothing. If cement or concrete enters the eye, immediately wash it out thoroughly with clean water and seek medical treatment without delay. Wash wet concrete off the skin immediately.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the procedure for determining the passing ability (measured by the blocking step), the flow spread and t_{500J} flow time of self-compacting concrete as the concrete flows through the J-ring.

The test is not suitable when the maximum size of aggregate exceeds 40 mm.

NOTE In respect to the relationship between aggregate size and bar spacing, the test is intended to assess the passing ability of the concrete proposed with the bar spacing typically in the works. If the concrete blocks then the aggregate size could be too large for the particular application.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12350-1, *Testing fresh concrete — Part 1: Sampling*

EN 12350-8, *Testing fresh concrete — Part 8: Self-compacting concrete — Slump-flow test*

3 Principle

The J-ring test is used to assess the passing ability of self-compacting concrete to flow through tight openings including spaces between reinforcing bars and other obstructions without segregation or blocking.

A narrow and wide bar spacing test is described. The narrow bar spacing simulates more congested reinforcement.

The J-ring test is an alternative to the L box test EN 12350-10 although the result is not directly comparable.

The method follows the procedure detailed in EN 12350-8 except that, before filling the slump cone with concrete, the J-ring, consisting of a ring of evenly spaced vertical smooth bars, is placed over the cone.

In addition, the time when the concrete has flowed to a diameter of 500 mm t_{500J} shall be measured, when specified.

4 Apparatus

The apparatus shall be in accordance with EN 12350-8 with the additional items as detailed below:

NOTE The feet to the slump cone may be removed to fit inside the J-ring or if their presence prevents free upward movement from within the J-ring.

4.1 Narrow gap J-ring.

Smooth steel bars, $(18 \pm 0,5)$ mm \varnothing , secured to a ring (300 ± 2) mm diameter (bar spacing of (41 ± 1) mm) with the dimensions as shown in Figures 1 and 2.

4.2 Wide gap J-ring.

Smooth steel bars, $(18 \pm 0,5)$ mm \varnothing , secured to a ring (300 ± 2) mm diameter (bar spacing of (59 ± 1) mm) with the dimensions as shown in Figures 1 and 3.