

**Puitplaadid. Tunnusväärtused
ehitusprojekteerimiseks. Osa 3: Liimpuitkilbid**

Wood-based panels - Characteristic values for
structural design - Part 3: Solid-wood panels

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 12369-3:2008 sisaldab Euroopa standardi EN 12369-3:2008 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 15.12.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 12.11.2008.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 12369-3:2008 consists of the English text of the European standard EN 12369-3:2008.

This standard is ratified with the order of Estonian Centre for Standardisation dated 15.12.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 12.11.2008.

The standard is available from Estonian standardisation organisation.

ICS 79.060.99

Võtmesõnad:

Standardite reprodutseerimis- ja levitamisoigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

ICS 79.060.99

English Version

Wood-based panels - Characteristic values for structural design - Part 3: Solid-wood panels

Panneaux à base de bois - Valeurs caractéristiques pour
conception des structures - Partie 3: Bois panneautés

Holzwerkstoffe - Charakteristische Werte für die
Berechnung und Bemessung von Holzbauwerken - Teil 3:
Massivholzplatten

This European Standard was approved by CEN on 12 October 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions and symbols	4
3.1 Terms and definitions	4
3.2 Symbols	5
3.2.1 Main Symbols	5
3.2.2 Subscripts	6
4 General.....	6
5 Characteristic values for solid wood panels	6
5.1 Introduction	6
5.2 Load-bearing panels for use in all service classes.....	7
Annex A (informative) Presentation of characteristic values	9
Bibliography	10

This document is a preview generated by EVS

Foreword

This document (EN 12369-3:2008) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2009, and conflicting national standards shall be withdrawn at the latest by May 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard is intended to be used in conjunction with EN 1995-1-1.

This European Standard is one of a series specifying characteristic values of wood-based panels for structural design. The other parts of this series are listed in the Bibliography.

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard provides information on the characteristic values for use in designing structures incorporating wood-based panels. The characteristic values given are as defined in EN 1995-1-1.

This European Standard includes the characteristic values of the mechanical properties and of the raw density for solid-wood panels complying with EN 13353:2008 technical classes SWP/1 S, SWP/2 S, SWP/3 S.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 338, *Structural timber — Strength classes*

EN 789, *Timber structures — Test methods — Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels — Determination of characteristic values of mechanical properties and density*

EN 1995-1-1, *Eurocode 5: Design of timber structures — Part 1-1: General — Common rules and rules for buildings*

EN 13017-1, *Solid wood panels — Classification by surface appearance — Part 1: Softwood*

EN 13017-2, *Solid wood panels — Classification by surface appearance — Part 2: Hardwood*

EN 13353:2008, *Solid wood panels (SWP) — Requirements*

3 Terms and definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1 characteristic values

3.1.1.1 characteristic strength value

population 5-percentile value obtained from the results of tests with a duration of 300 s at an equilibrium moisture content of the test pieces relating to a temperature of 20 °C and a relative humidity of 65 %

3.1.1.2 characteristic stiffness value

either the population 5-percentile or the mean value obtained of tests with a duration of 300 s at an equilibrium moisture content of the test pieces relating to a temperature of 20 °C and a relative humidity of 65 %

NOTE The stiffness values given in the Tables are mean values as these are most commonly used in design. A note in Annex A explains how to calculate the 5-percentile value.

3.1.1.3 characteristic density

population 5-percentile value with mass and volume corresponding to equilibrium moisture content at a temperature of 20 °C and a relative humidity of 65 %