

**Plastics - Unsaturated-polyester resins
(UP-R) - Part 2: Preparation of test
specimens and determination of properties**

Plastics - Unsaturated-polyester resins (UP-R) -
Part 2: Preparation of test specimens and
determination of properties

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 3672-2:2002 sisaldab Euroopa standardi EN ISO 3672-2:2001 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 14.02.2002 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 3672-2:2002 consists of the English text of the European standard EN ISO 3672-2:2001.</p> <p>This document is endorsed on 14.02.2002 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This standard specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of unsaturated-polyester resins. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.</p>	<p>Scope: This standard specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of unsaturated-polyester resins. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.</p>
---	---

ICS 83.080.10

Võtmesõnad: deter, inspection by attributes, inspection specification, materials, organic compounds, plastics, polyester resins, polyesters, production, properties, specifications, specimen preparation, test specimens, testing, tests, unsaturated, unsaturated polyester resins

English version

Plastics

Unsaturated-polyester resins (UP-R)

Part 2: Preparation of test specimens and determination of properties
(ISO 3672-2 : 2000)

Plastiques – Résines de polyesters
non saturés (UP-R) – Partie 2: Prépara-
tion des éprouvettes et détermination
des propriétés (ISO 3672-2 : 2000)

Kunststoffe – Ungesättigte Polyester-
harze (UP-R) – Teil 2: Herstellung von
Probekörpern und Bestimmung von
Eigenschaften (ISO 3672-2 : 2000)

This European Standard was approved by CEN on 2001-06-17.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Management Centre: rue de Stassart 36, B-1050 Brussels

Foreword

International Standard

ISO 3672-2 : 2000 Plastics – Unsaturated-polyester resins (UP-R) – Part 2: Preparation of test specimens and determination of properties,

which was prepared by ISO/TC 61 'Plastics' of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 249 'Plastics', the Secretariat of which is held by IBN, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by February 2002 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3672-2 : 2000 was approved by CEN as a European Standard without any modification.

Contents

	Page
Foreword	2
Introduction	2
1 Scope	3
2 Normative references	3
3 Preparation of test specimens	5
3.1 General	5
3.2 Pretreatment of materials	5
3.3 Preparation of the sheets	6
3.4 Cutting out test specimens	8
4 Conditioning of test specimens	8
5 Determination of properties	8

Introduction

The purpose of this part of ISO 3672 is to designate procedures for the determination of intrinsic properties of unsaturated-polyester (UP) resins. It specifies procedures and conditions for the preparation of test specimens of unsaturated-polyester resins in a specified state, and methods for measuring their properties. Those properties and test methods which are suitable and necessary for characterizing unsaturated-polyester resins are listed. Because of the specificity of thermosetting resins like unsaturated-polyester resins, contrary to other plastic products, a distinction is made between the presentation of the properties before crosslinking (characteristics which are useful for processing) and after crosslinking (intrinsic characteristics).

WARNING — Persons using this part of ISO 3672 should be familiar with normal laboratory practice. This part of ISO 3672 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This part of ISO 3672 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of unsaturated-polyester resins. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.

The properties of crosslinked unsaturated-polyester resins have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, unsaturated-polyester resins (particularly properties useful for the processing of non-crosslinked resins) are also included in this part of ISO 3672.

In order to obtain reproducible and comparable test results, it is necessary to use the test methods, sample preparation and conditioning procedures, and specimen dimensions specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

Other standards exist concerning the determination of properties and preparation of test specimens for unsaturated-polyester-based products, to which reference will be made, if required.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 3672. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 3672 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 62:1999, *Plastics — Determination of water absorption.*

ISO 75-2:1993, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite.*

ISO 178:1993, *Plastics — Determination of flexural properties.*

ISO 179-1:—¹⁾, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test.*

1) To be published. (Revision of ISO 179:1993)

- ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing.*
- ISO 527-1:1993, *Plastics — Determination of tensile properties — Part 1: General principles.*
- ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics.*
- ISO 604:1993, *Plastics — Determination of compressive properties.*
- ISO 760:1978, *Determination of water — Karl Fischer method (General method).*
- ISO 1523:1983, *Paints, varnishes, petroleum and related products — Determination of flashpoint — Closed cup equilibrium method.*
- ISO 1675:1985, *Plastics — Liquid resins— Determination of density by the pycnometer method.*
- ISO 2114:—²⁾, *Plastics (polyester resins) and paints and varnishes (binders) — Determination of partial acid value and total acid value.*
- ISO 2535:—³⁾, *Plastics — Unsaturated-polyester resins — Measurement of gel time at ambient temperature.*
- ISO 2554:1997, *Plastics — Unsaturated polyester resins — Determination of hydroxyl value.*
- ISO 2577:1984, *Plastics — Thermosetting moulding materials — Determination of shrinkage.*
- ISO 2719:—⁴⁾, *Determination of flash point — Pensky-Martens closed cup method.*
- ISO 2818:1994, *Plastics — Preparation of test specimens by machining.*
- ISO 3167:1993, *Plastics — Multipurpose test specimens.*
- ISO 3219:1993, *Plastics — Polymers/resins in the liquid state or as emulsions or dispersions — Determination of viscosity using a rotational viscometer with defined shear rate.*
- ISO 3521:1997, *Plastics — Unsaturated polyester and epoxy resins — Determination of overall volume shrinkage.*
- ISO 3672-1:2000, *Plastics — Unsaturated-polyester resins (UP-R) — Part 1: Designation system.*
- ISO 4589-2:1996, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test.*
- ISO 4615:1979, *Plastics — Unsaturated polyesters and epoxide resins — Determination of total chlorine content.*
- ISO 4630:1997, *Binders for paints and varnishes — Estimation of colour of clear liquids by the Gardner colour scale.*
- ISO 4901:1985, *Reinforced plastics based on unsaturated polyester resins — Determination of residual styrene monomer content.*
- ISO 6271:1997, *Clear liquids — Estimation of colour by the platinum-cobalt scale.*
- ISO 6603-2:—⁵⁾, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing.*
- ISO 8256:1990, *Plastics — Determination of tensile-impact strength.*

-
- 2) To be published. (Revision of ISO 2114:1996)
- 3) To be published. (Revision of ISO 2535:1997)
- 4) To be published. (Revision of ISO 2719:1988)
- 5) To be published. (Revision of ISO 6603-2:1989)

ISO 10350-1:1998, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials.*

ISO 11357-2:1999, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature.*

ISO 11359-2:1999, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature.*

ISO 14848:1998, *Plastics — Unsaturated-polyester resins — Determination of reactivity at 130 °C.*

IEC 60093:1980, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials.*

IEC 60112:1979, *Methods for determining the comparative and the proof tracking indices of solid insulating materials under moist conditions.*

IEC 60243-1:1998, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies.*

IEC 60250:1969, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths.*

IEC 60296:1982, *Specification for unused mineral insulating oils for transformers and switchgear.*

IEC 60695-11-10:1999, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods.*

IEC 60695-11-20:1999, *Fire hazard testing — Part 11-20: Test flames — 500 W flame test methods.*

EN 59:1977, *Glass reinforced plastics — Measurement of hardness by means of a Barcol impressor.*

3 Preparation of test specimens

3.1 General

This procedure shall be used for the preparation of specimens for the determination of crosslinked-resin properties.

It is essential that specimens are always prepared by the same procedure using the same processing conditions.

The specimens on which the properties are measured shall be cut from sheets of crosslinked resin, produced by a casting process. In view of the numerous possible fields of application for unsaturated-polyester resins, the choice was made to prepare specimens from resins not containing any filler or reinforcement in order to obtain the intrinsic properties of the crosslinked polymer, free of structural additives.

This procedure shall only be used for the determination of properties of crosslinked resins obtained from liquid unsaturated-polyester resins.

Test specimens from solid UP-R shall be prepared in accordance with the resin supplier's instructions.

Sheets of thermosetting resin shall be manufactured at 2 mm, 3 mm and 4 mm thickness, as required, for tests in Table 2. A sufficient number shall be produced to determine those properties required.

3.2 Pretreatment of materials

Before casting, no treatment of the resin sample is normally necessary. If pretreatment is required, this shall be in accordance with the manufacturer's recommendations.

The resin shall be kept in moisture-proof containers until it is required for use.