

**Leather - Chemical determination of
chromic oxide content - Part 4:
Quantification by inductive coupled
plasma/optical emission spectrometer
(ICP-OES)**

Leather - Chemical determination of chromic oxide
content - Part 4: Quantification by inductive coupled
plasma/optical emission spectrometer (ICP-OES)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 5398-4:2007 sisaldab Euroopa standardi EN ISO 5398-4:2007 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 30.10.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 5398-4:2007 consists of the English text of the European standard EN ISO 5398-4:2007.</p> <p>This document is endorsed on 30.10.2007 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This part of ISO 5398 describes a method for the determination of chromium in aqueous solution obtained from leather. This is an analysis for total chromium in leather; it is not compound specific or specific to its oxidation state. This method describes the determination of chromium by inductively coupled plasma – optical emission spectrometry and is applicable to leathers which are expected to have chromic oxide contents in excess of 1 mg/kg. Two techniques for the preparation of the solution to be analysed are included. In the case of dispute, the wet oxidation technique is to be used.</p>	<p>Scope: This part of ISO 5398 describes a method for the determination of chromium in aqueous solution obtained from leather. This is an analysis for total chromium in leather; it is not compound specific or specific to its oxidation state. This method describes the determination of chromium by inductively coupled plasma – optical emission spectrometry and is applicable to leathers which are expected to have chromic oxide contents in excess of 1 mg/kg. Two techniques for the preparation of the solution to be analysed are included. In the case of dispute, the wet oxidation technique is to be used.</p>
--	--

ICS 59.140.30

Võtmesõnad:

ICS 59.140.30

English Version

Leather - Chemical determination of chromic oxide content - Part 4: Quantification by inductively coupled plasma - optical emission spectrometer (ICP-OES) (ISO 5398-4:2007)

Cuir - Dosage chimique de l'oxyde de chrome - Partie 4: Quantification par plasma à couplage inductif - spectromètre d'émission optique (ICP-OES) (ISO 5398-4:2007)

Leder - Chemische Bestimmung des Chromoxidgehaltes - Teil 4: Bestimmung durch induktiv gekoppeltes Plasma/optisches Spektrometer (ICP-OES) (ISO 5398-4:2007)

This European Standard was approved by CEN on 28 July 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....3

This document is a preview generated by EVS

Foreword

This document (EN ISO 5398-4:2007) has been prepared by Technical Committee CEN/TC 289 "Leather", the secretariat of which is held by UNI, in collaboration with the International Union of Leather Technologists and Chemists Societies (IULTCS).

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

**Leather — Chemical determination of
chromic oxide content —**

Part 4:

**Quantification by inductively coupled
plasma – optical emission spectrometer
(ICP-OES)**

Cuir — Dosage chimique de l'oxyde de chrome —

*Partie 4: Quantification par plasma à couplage inductif – spectromètre
d'émission optique (ICP-OES)*

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Sampling and sample preparation.....	2
6 Reagents.....	2
6.1 Wet oxidation method.....	2
6.2 ICP-OES.....	2
7 Apparatus.....	2
8 Methods.....	3
8.1 Preparation of analytical solution.....	3
8.2 Measurement of the aqueous solution.....	3
9 Calculation and expression of results.....	4
10 Test report.....	5
Annex A (informative) Determination of water and other volatile matter.....	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

This part of ISO 5398 was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical co-operation between ISO and CEN (Vienna Agreement). It is based on IUC 8 originally published in *J. Soc. Leather Trades Chemists* **49**, p. 17, (1965) and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

ISO 5398 consists of the following parts, under the general title *Leather — Chemical determination of chromic oxide content*:

- *Part 1: Quantification by titration*
- *Part 2: Quantification by colorimetric determination*
- *Part 3: Quantification by atomic absorption spectrometry*
- *Part 4: Quantification by inductively coupled plasma – optical emission spectrometer (ICP-OES)*

Introduction

ISO 5398 has been split into four parts, each describing methods suitable for the determination of the chromic oxide content in leather. The different techniques have been described to reflect the variations in industrial practice compared with the more sensitive analytical equipment available for test laboratories. Variations also exist in the range of chromic oxide that the methods are deemed suitable to quantify.

ISO 5398-4 describes a technique that is suitable for determining chromium more precisely than those described in ISO 5398-1 and ISO 5398-2. It requires the use of sophisticated analytical equipment, such as inductively coupled plasma and atomic absorption spectroscopy.

Leather — Chemical determination of chromic oxide content —

Part 4:

Quantification by inductively coupled plasma — optical emission spectrometer (ICP-OES)

1 Scope

This part of ISO 5398 describes a method for the determination of chromium in aqueous solution obtained from leather. This is an analysis for total chromium in leather; it is not compound specific or specific to its oxidation state.

This method describes the determination of chromium by inductively coupled plasma – optical emission spectrometry and is applicable to leathers which are expected to have chromic oxide contents in excess of 1 mg/kg. Two techniques for the preparation of the solution to be analysed are included. In the case of dispute, the wet oxidation technique is to be used.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

EN 14602, *Footwear — Test methods for the assessment of ecological criteria*

ISO 4684, *Leather — Chemical tests — Determination of volatile matter*

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectroscopy (ICP-OES)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

chromic oxide content

amount of chromium in leather, determined by this method and reported as chromic oxide

NOTE The chromic oxide content is expressed in milligrams per kilogram (mg/kg), based on dry matter.