

Corrosion of metals and alloys - Stress corrosion cracking - Part 11: Guidelines for testing the resistance of metals and alloys to hydrogen embrittlement and hydrogen-assisted cracking (ISO 7539-11:2013)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 7539-11:2015 sisaldab Euroopa standardi EN ISO 7539-11:2014 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 7539-11:2015 consists of the English text of the European standard EN ISO 7539-11:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.12.2014.	Date of Availability of the European standard is 17.12.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.060

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

ICS 77.060

English Version

Corrosion of metals and alloys - Stress corrosion cracking - Part  
11: Guidelines for testing the resistance of metals and alloys to  
hydrogen embrittlement and hydrogen-assisted cracking (ISO  
7539-11:2013)

Corrosion des métaux et alliages - Essai de corrosion sous  
contrainte - Partie 11: Lignes directrices pour les essais de  
résistance des métaux et alliages à la fragilisation par  
l'hydrogène et la fissuration assistée sous hydrogène (ISO  
7539-11:2013)

Korrosion der Metalle und Legierungen - Prüfung der  
Spannungsrissskorrosion - Teil 11: Leitfaden für die Prüfung  
der Resistenz von Metallen und Legierungen gegen  
Wasserstoffversprödung und wasserstoffverursachte  
Brüche (ISO 7539-11:2013)

This European Standard was approved by CEN on 16 December 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

## Foreword

The text of ISO 7539-11:2013 has been prepared by Technical Committee ISO/TC 156 “Corrosion of metals and alloys” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 7539-11:2014 by Technical Committee CEN/TC 262 “Metallic and other inorganic coatings” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2015, and conflicting national standards shall be withdrawn at the latest by June 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### Endorsement notice

The text of ISO 7539-11:2013 has been approved by CEN as EN ISO 7539-11:2014 without any modification.

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Factors to be considered in hydrogen embrittlement and hydrogen-assisted cracking testing.....</b>	<b>1</b>
3.1 Dynamic plastic straining.....	1
3.2 Test time and hydrogen uptake.....	2
3.3 Temperature.....	2
<b>4 Selection of test method.....</b>	<b>3</b>
4.1 General.....	3
4.2 Specimen type.....	3
4.3 Test duration.....	3
4.4 Load form.....	8
4.5 Pre-charging and hydrogen effusivity.....	12
4.6 Testing of welds.....	12
<b>5 Post-test evaluation.....</b>	<b>13</b>
<b>Bibliography.....</b>	<b>15</b>

# Corrosion of metals and alloys — Stress corrosion cracking —

## Part 11:

# Guidelines for testing the resistance of metals and alloys to hydrogen embrittlement and hydrogen-assisted cracking

## 1 Scope

This part of ISO 7539 gives guidance on the key features that should be accounted for in designing and conducting tests to evaluate the resistance of a metal or its alloy to hydrogen embrittlement and hydrogen-assisted cracking.

NOTE Particular methods of testing are not treated in detail in this document. These are described in other International Standards to which reference is given.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7539-7, *Corrosion of metals and alloys — Stress corrosion testing — Part 7: Method for slow strain rate testing*

ISO 17081, *Method of measurement of hydrogen permeation and determination of hydrogen uptake and transport in metals by an electrochemical technique*

## 3 Factors to be considered in hydrogen embrittlement and hydrogen-assisted cracking testing

### 3.1 Dynamic plastic straining

**3.1.1** Surface films such as passive oxide films, and sulphide films in the case of exposure of carbon steel to H<sub>2</sub>S environments, for example, can markedly reduce hydrogen uptake. Film rupture will enhance ingress locally, which means that dynamic plastic straining and the strain rate can be particularly important. In that context, there is then usually no relationship between hydrogen uptake as measured in a permeation experiment and the cracking response since uptake is local at the film rupture sites. A possible exception is when there is a significant sub-surface region of susceptibility associated with residual stress or microchemistry as might possibly be found in welds. Here, detailed characterization of the weld should be conducted prior to testing.

**3.1.2** Dynamic plastic straining may be induced under static load if there is significant creep, as in some duplex stainless steels.

**3.1.3** In testing of alloys that are actively corroding, there is often a correlation between cracking and the measured bulk hydrogen uptake. Dynamic plastic straining may have only a relatively minor role in hydrogen uptake in that case.

**3.1.4** In all alloys, dynamic plastic straining and the strain rate may be important in dislocation transport of hydrogen. The mobility of hydrogen atoms and trapping at dislocations means that dislocations can