

**Ümarpuit ja saematerjal. Lubatud
hälbed ja eelismõõtmed. Osa 1:
Okaspuu saematerjal**

Round and sawn timber - Permitted deviations and preferred sizes - Part 1: Softwood sawn timber

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 1313-1:2001 sisaldab Euroopa standardi EN 1313-1:1997 + A1:1999 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 18.05.2001 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 1313-1:2001 consists of the English text of the European standard EN 1313-1:1997 + A1:1999.</p> <p>This document is endorsed on 18.05.2001 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This Standard specifies permitted deviations for thicknesses and widths at a reference moisture content and adjustments for changes in size due to changes in moisture content. Preferred sizes for thicknesses of 38 mm and over are also specified.</p>	<p>Scope: This Standard specifies permitted deviations for thicknesses and widths at a reference moisture content and adjustments for changes in size due to changes in moisture content. Preferred sizes for thicknesses of 38 mm and over are also specified.</p>
--	--

ICS 79.040

Võtmesõnad:

English version

Round and sawn timber – Permitted deviations and preferred sizes

Part 1: Softwood sawn timber
(includes Amendment A1 : 1999)

Bois ronds et bois sciés – Ecart
admissibles et dimensions
préférentielles – Partie 1: Bois sciés
résineux (amendement A1 : 1999
inclus)

Rund- und Schnittholz – Zulässige
Abweichungen und Vorzugsmaße –
Teil 1: Nadelschnittholz (einschließ-
lich Änderung A1 : 1999)

This European Standard was approved by CEN on 1996-12-27 and Amendment A1 on 1999-05-02.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Contents

	Page
Foreword to EN 1313-1 : 1997	2
Foreword to EN 1313-1 : 1997/A1 : 1999	2
1 Scope	3
2 Normative references	3
3 Definitions	3
4 Reference moisture content	3
5 Change in size due to changes in moisture content	3
6 Permitted deviations	4
7 Preferred target cross-sectional sizes	4
8 Annex A (informative) Complementary national sizes	5

Foreword to EN 1313-1 : 1997

This European Standard has been prepared by Technical Committee CEN/TC 175 'Round and sawn timber', the Secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by August 1997 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

Foreword to EN 1313-1 : 1997/A1 : 1999

This Amendment to EN 1313-1 : 1997 has been prepared by Technical Committee CEN/TC 175 'Round and sawn timber', the Secretariat of which is held by AFNOR.

This Amendment shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by December 1999 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

1 Scope

This Standard specifies permitted deviations for thicknesses and widths at a reference moisture content and adjustments for changes in size due to changes in moisture content. Preferred sizes for thicknesses of 38 mm and over are also specified.

This standard applies to softwood sawn timber.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard, only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies.

EN 844-1	Round and sawn timber - Terminology - Part 1 : General terms common to round timber and sawn timber.
EN 844-3	Round and sawn timber - Terminology - Part 3 : General terms relating to sawn timber.
EN 844-4	Round and sawn timber - Terminology - Part 4 : Terms relating to moisture content.
EN 844-6	Round and sawn timber - Terminology - Part 6 : Terms relating to dimensions of sawn timber.
EN 1309-1	Round and sawn timber - Method of measurement of dimensions - Part 1: Sawn timber.

3 Definitions

For the purposes of this standard, definitions contained in parts 1, 3, 4 and 6 of EN 844 shall apply.

4 Reference moisture content

The reference moisture content is 20%. The target sizes in clause 7 are applied at this moisture content.

5 Change in size due to changes in moisture content

Unless there is evidence to the contrary, it shall be assumed that the thickness and width of a piece of timber will increase by 0,25 % every 1 % of moisture content higher than 20 % up to fibre saturation point, and decrease by up to 0,25 % every 1 % of moisture content lower than 20 %. The above values are independent of the species.