
**Physical and mechanical properties of
wood — Test methods for small clear
wood specimens —**

Part 6:
**Determination of ultimate tensile
stress parallel to grain**

*Propriétés physiques et mécaniques du bois — Méthodes d'essais sur
échantillons de bois sans défauts —*

*Partie 6: Détermination de la contrainte de rupture en traction
parallèle aux fibres*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	1
6 Preparation of test pieces.....	2
6.1 General.....	2
6.2 Moisture content of test pieces.....	2
7 Procedure.....	2
8 Calculations and expression of results.....	2
9 Test report.....	3
Bibliography.....	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: Foreword — Supplementary information.

The committee responsible for this document is ISO/TC 218, *Timber*.

This first edition of ISO 13061-6 cancels and replaces ISO 3345:1975, which has been technically revised with regards to the sizes, moisture content of test pieces, and adjustment for moisture content.

ISO 13061 consists of the following parts, under the general title *Physical and mechanical properties of wood — Test methods for small clear specimens*:

- *Part 1: Determination of moisture content for physical and mechanical tests*
- *Part 2: Determination of density for physical and mechanical tests*
- *Part 3: Determination of ultimate strength in static bending*
- *Part 4: Determination of modulus of elasticity in static bending*
- *Part 6: Determination of ultimate tensile stress parallel to grain*
- *Part 7: Determination of ultimate tensile stress perpendicular to grain*

The following parts are under preparation:

- *Part 5: Determination of strength in compression perpendicular to grain*
- *Part 10: Determination of impact bending strength*
- *Part 11: Determination of resistance to impact indentation*
- *Part 12: Determination of static hardness*
- *Part 13: Determination of radial and tangential shrinkage*
- *Part 14: Determination of volumetric shrinkage*
- *Part 15: Determination of radial and tangential swelling*

- *Part 16: Determination of volumetric swelling*
- *Part 17: Determination of strength in compression parallel to grain*

This document is a preview generated by EVS

Introduction

The main purpose of this International Standard is to establish the common international point of member countries of the International Organization for Standardization (ISO), concerning testing methods for small clear wood specimens and general requirements for determining physical and mechanical properties of wood.

This document is a preview generated by EVS

Physical and mechanical properties of wood — Test methods for small clear wood specimens —

Part 6:

Determination of ultimate tensile stress parallel to grain

1 Scope

This part of ISO 13061 specifies a method for determining the ultimate tensile stress of wood parallel to grain on small clear specimens by measuring the breaking load applied statically along the longitudinal axis of a test piece.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3129, *Wood — Sampling methods and general requirements for physical and mechanical testing of small clear wood specimens*

ISO 13061-1, *Physical and mechanical properties of wood — Test methods for small clear specimens — Part 1: Determination of moisture content for physical and mechanical tests*

ISO 13061-2, *Physical and mechanical properties of wood — Test methods for small clear specimens — Part 2: Determination of density for physical and mechanical tests*

ISO 24294, *Timber — Round and sawn timber — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 24294 apply.

4 Principle

The ultimate tensile stress parallel to grain is determined by application of a gradually increasing load in direction parallel to grain of a test piece until failure.

5 Apparatus

5.1 Testing machine capable of ensuring constant rate of loading or of movement of the loading head and allowing measurement of the load to an accuracy of 1 %.

The grips of the testing machine shall be such that the load is applied along the longitudinal axis of the test piece and shall prevent longitudinal twisting of the test piece.

5.2 Measuring instrument capable of measuring the dimensions of the gauge portion of the test piece to the nearest 0,1 mm.

5.3 Equipment for the determination of moisture content, in accordance with ISO 13061-1.