

Textiles - Determination of the abrasion resistance of knitted footwear garments

Textiles - Determination of the abrasion resistance of knitted footwear garments

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 13770:2002 sisaldab Euroopa standardi EN 13770:2002 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 18.10.2002 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 13770:2002 consists of the English text of the European standard EN 13770:2002.</p> <p>This document is endorsed on 18.10.2002 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This standard specifies two test methods for the determination of abrasion resistance of knitted footwear garments, e.g. ankle socks, socks, and heavy tights. The test methods apply to any of these articles, irrespective of size, composition and structure.</p>	<p>Scope: This standard specifies two test methods for the determination of abrasion resistance of knitted footwear garments, e.g. ankle socks, socks, and heavy tights. The test methods apply to any of these articles, irrespective of size, composition and structure.</p>
---	---

ICS 61.020

Võtmesõnad: clothing, knitting, resistance, resistance against abrasion, sampling, sampling methods, socks, specimen preparation, stockings, surface patterns, test equipment, testing, tests, textile industry, textile testing, textiles, tights, wear tests

ICS 61.020

English version

Textiles - Determination of the abrasion resistance of knitted footwear garments

Textiles - Détermination de la résistance à l'abrasion des articles chaussants tricotés

Textilien - Bestimmung der Scheuerbeständigkeit von gestrickter Fußbekleidung

This European Standard was approved by CEN on 11 April 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Conditioning and testing atmosphere	5
4 Method 1 : Martindale abrasion machine method	5
4.1 Principle	5
4.2 Apparatus and agents	5
4.3 Sampling and preparation of test specimens	6
4.3.1 General	6
4.3.2 Sampling of the test specimens from the laboratory sample	6
4.3.3 Dimensions of auxiliary materials	6
4.3.4 Mounting the test specimens	6
4.4 Test procedure	6
4.5 Assessment intervals	7
4.6 Test report	7
5 Method 2 : Abrasion on leg forms	8
5.1 Principle	8
5.2 Apparatus	8
5.2.1 Abrasion tester (Figure C.1)	8
5.2.2 Legs forms	8
5.2.3 Elastic retaining collars	9
5.2.4 Abradant paper	9
5.2.5 Foam backing material (see annex F)	9
5.2.6 Soft brush	9
5.3 Sampling and number of tests	9
5.4 Test procedure	9
5.5 Test report	10
Annex A (normative) Specimen holders	11
Annex B (informative) Recommended inspection intervals	14
Annex C (informative) Apparatus for abrasion on leg forms	15
Annex D (normative) Size of legs forms, based on the MONDOPOINT sizes	17
Annex E (informative) Technical characteristics of abradant paper	18
Annex F (informative) Technical characteristics of foam	19

Foreword

This document EN 13370:2002 has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2003, and conflicting national standards shall be withdrawn at the latest by January 2003.

Annex A and annex D are normative.

Annex B, annex C, annex E and annex F are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This European Standard is composed of two tests.

The first test describes a method for the determination of the abrasion resistance of knitted footwear garments on samples stretched with a modified sample holder, on a Martindale abrasion machine.

The second test describes a testing device and a method for the determination of the abrasion resistance of knitted footwear garments in a stretched controlled state.

The test method is chosen before starting the test and recorded in the test report, since the results of the different methods cannot be compared with each other.

1 Scope

This European Standard specifies two test methods for the determination of abrasion resistance of knitted footwear garments, e.g. ankle socks, socks, and heavy tights. The test methods apply to any of these articles, irrespective of size, composition and structure.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 20139, *Textiles — Standard atmospheres for conditioning and testing (ISO 139:1973)*.

EN ISO 12947-1, *Textiles — Determination of the abrasion resistance of fabrics by the Martindale method — Part 1: Martindale abrasion testing apparatus (ISO 12947-1:1998)*.

3 Conditioning and testing atmosphere

The standard temperate atmosphere for conditioning and testing textiles as defined in EN 20139 shall be used.

4 Method 1 : Martindale abrasion machine method

4.1 Principle

Circular specimens of the hosiery are selected from the known wear areas of the socks, stretched over a flattened rubber surface and abraded against a reference abradant under a known pressure with a cyclic planar motion in the form of a Lissajous figure which is the resultant of two simple harmonic motions at right angles to each other. The resistance to abrasion is estimated by the number of cycles to either total breakdown or thinning of one component.

4.2 Apparatus and agents

4.2.1 Martindale abrasion machine as specified in EN ISO 12947–1.

4.2.2 Modified specimen holders for the evaluation of abrasion of knitted footwear garments (in accordance with annex A), consisting of a guide spindle, holder body, needle ring, holder nut and rubber sphere with flattened surfaces (20 mm being the test area).

4.2.3 Springloaded tightening block spanner which enables the tightening of the holder body and holder nut whilst ensuring the flat surface of the rubber sphere remains flat and horizontal.

4.2.4 Abradant and woven felt as specified in EN ISO 12947–1.