

KEEVITUSMATERJALID. TÄIDISTRAADID LEGEERIMATA
JA PEENTERATERASTE KAARKEEVITUSEKS
KAITSEGAASIS JA KAITSEGAASITA. LIIGITUS

Welding consumables - Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of non-alloy and fine grain steels - Classification (ISO 17632:2015)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 17632:2015 sisaldab Euroopa standardi EN ISO 17632:2015 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 17632:2015 consists of the English text of the European standard EN ISO 17632:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.12.2015.	Date of Availability of the European standard is 16.12.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.160.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 17632

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 25.160.20

Supersedes EN ISO 17632:2008

English Version

Welding consumables - Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of non-alloy and fine grain steels - Classification (ISO 17632:2015)

Produits consommables pour le soudage - Fils-électrodes fourrés pour soudage à l'arc avec ou sans gaz de protection des aciers non alliés et des aciers à grains fins - Classification (ISO 17632:2015)

Schweißzusätze - Fülldrahtelektroden zum Metall-Lichtbogenschweißen mit und ohne Schutzgas von unlegierten Stählen und Feinkornstählen - Einteilung (ISO 17632:2015)

This European Standard was approved by CEN on 15 August 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17632:2015) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17632:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17632:2015 has been approved by CEN as EN ISO 17632:2015 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	3
4.1 Symbol for the product/process.....	3
4.2 Symbol for tensile properties of all-weld metal or welded joint.....	4
4.2.1 Multi-run technique.....	4
4.2.2 Single-run technique.....	4
4.3 Symbol for impact properties of all-weld metal or welded joint.....	5
4.4 Symbol for chemical composition of all-weld metal.....	6
4.5 Symbol for type of electrode core or for the usability characteristics of the electrode.....	9
4.6 Symbol for shielding gas.....	9
4.7 Symbol for welding position.....	12
4.8 Symbol for hydrogen content of deposited metal.....	12
4.9 Symbol for condition of postweld heat treatment of all-weld metal.....	13
5 Mechanical tests	13
5.1 Multi-run technique.....	13
5.1.1 Preheating and interpass temperatures.....	13
5.1.2 Procedure requirements for welding multi-run test assemblies.....	14
5.1.3 Post-weld heat treatment (PWHT) condition.....	15
5.2 Single-run technique.....	15
6 Chemical analysis	15
7 Rounding procedure	15
8 Fillet weld test	15
9 Retests	16
10 Technical delivery conditions	17
11 Examples of designation	17
Annex A (informative) Classification systems	21
Annex B (informative) Description of types of electrode core in the classification system based upon yield strength and average impact energy of 47 J	24
Annex C (informative) Description of types of usability characteristics in the classification system based upon tensile strength and average impact energy of 27 J	26
Annex D (informative) Notes on hydrogen content	29

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second edition cancels and replaces the first edition (ISO 17632:2004), which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3, through your national standards body, a complete listing of which can be found at www.iso.org.

Introduction

This International Standard provides a classification system for tubular cored electrodes in terms of tensile properties, impact properties, chemical composition of the all-weld metal, type of electrode core, shielding gas, and welding position. The ratio of yield to tensile strength of weld metal is generally higher than that of the parent metal. Matching weld metal yield strength to parent metal yield strength will not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Where the application requires matching tensile strengths, selection of consumables is made by reference to column 3 of [Table 1A](#) or [Table 1B](#).

Of note is that the mechanical properties of all-weld metal test specimens used to classify the tubular cored electrodes will vary from those obtained in production joints because of the differences in welding procedure such as electrode size, width of weave, welding position, and parent metal composition.

The classification in accordance with system A is mainly based on EN 758:1997. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

Welding consumables — Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of non-alloy and fine grain steels — Classification

1 Scope

This International Standard specifies requirements for classification of tubular cored electrodes with or without a gas shield for metal arc welding of non-alloy and fine grain steels in the as-welded condition or in the post-weld heat-treated condition with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa. One tubular cored electrode can be tested and classified with different shielding gases, if any.

This International Standard is a combined specification providing classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- 1) Paragraphs and tables which carry the suffix letter "A" are applicable only to tubular cored electrodes classified to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal in accordance with this International Standard.
- 2) Paragraphs and tables which carry the suffix letter "B" are applicable only to tubular cored electrodes classified to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal in accordance with this International Standard.
- 3) Paragraphs and tables which have neither the suffix letter "A" nor the suffix letter "B" are applicable to all tubular cored electrodes classified in accordance with this International Standard.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current, but for the purposes of this International Standard, pulsed current is not permitted for determining the electrode classification.

2 Normative references

The following referenced documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:2011, *Welding and allied processes — Welding positions*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*. Amended by ISO 15792-1:2000/Amd 1:2011

ISO 15792-2:2000, *Welding consumables — Test methods — Part 2: Preparation of single-run and two-run technique test specimens in steel*

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2009, *Quantities and units — Part 1: General*. Corrected by ISO 80000-1:2009/Cor 1:2011

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all as will be clear from the following. In most cases, a given commercial product can be classified in both systems. Then, either or both classification designations can be used for the product (see Annex A).

The classification includes all-weld metal properties obtained with a tubular cored electrode and appropriate shielding gas combination as given below. With the exception of the symbol for welding position which is based on ISO 15792-3, the classification of gas shielded tubular cored electrodes is based on the 1,2 mm electrode size or if this size is not manufactured, the next larger diameter manufactured. The classification of self-shielded tubular cored electrodes is based on the 2,4 mm diameter or the largest diameter manufactured if less than 2,4 mm.

3.1A Classification by yield strength and 47 J impact energy

The classification is divided into eight parts.

- 1) The first part (T) indicates a tubular cored electrode.
- 2) The second part gives a symbol indicating the yield strength and elongation of all-weld metal for multi-run technique or the strength of the parent material used in classification for the single-run technique (see [Table 1A](#) or [Table 2A](#)).
- 3) The third part gives a symbol indicating the impact properties of all-weld metal or welded joint (see [Table 3](#)).
- 4) The fourth part gives a symbol indicating the chemical composition of all-weld metal (see [Table 4A](#)).
- 5) The fifth part gives a symbol indicating the type of electrode core (see [Table 5A](#)).
- 6) The sixth part gives a symbol indicating the shielding gas (see [4.6](#)).

3.1B Classification by tensile strength and 27 J impact energy

The classification is divided into nine parts.

- 1) The first part (T) indicates a tubular cored electrode.
- 2) The second part gives a symbol indicating the tensile strength and elongation of all-weld metal for multi-run technique or the strength of the parent material used in classification for the single-run technique (see [Table 1B](#) or [Table 2B](#)).
- 3) The third part gives a symbol indicating the impact properties of all-weld metal (see [Table 3](#)). The symbol "U" added as an optional supplemental designator at or near the end of the complete tubular cored electrode designation indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature.
- 4) The fourth part gives a symbol indicating the usability characteristics of the electrode (see [Table 5B](#)).
- 5) The fifth part gives a symbol indicating the welding position (see [Table 6B](#)).
- 6) The sixth part gives a symbol indicating the shielding gas (see [4.6](#)). The letter "S" added to this designator indicates that the electrode is classified for single-pass welding.