

This document is a preview generated by EVS

**Vask ja vasesulamid. Sepised**

**Copper and copper alloys - Forgings**

<b>EESTI STANDARDI EESSÕNA</b>	<b>NATIONAL FOREWORD</b>
See Eesti standard EVS-EN 12420:2014 sisaldab Euroopa standardi EN 12420:2014 ingliskeelset teksti.	This Estonian standard EVS-EN 12420:2014 consists of the English text of the European standard EN 12420:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 25.06.2014.	Date of Availability of the European standard is 25.06.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.150.30

**Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Aru 10, 10317 Tallinn, Eesti; [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

**The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation**

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:  
Aru 10, 10317 Tallinn, Estonia; [www.evs.ee](http://www.evs.ee); phone 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Copper and copper alloys - Forgings

Cuivre et alliages de cuivre - Pièces forgées

Kupfer und Kupferlegierungen - Schmiedestücke

This European Standard was approved by CEN on 24 April 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

**Contents**

Page

Foreword.....	4
Introduction.....	6
<b>1</b> <b>Scope</b> .....	<b>7</b>
<b>2</b> <b>Normative references</b> .....	<b>7</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>7</b>
<b>4</b> <b>Designations</b> .....	<b>8</b>
<b>4.1</b> <b>Material</b> .....	<b>8</b>
<b>4.1.1</b> <b>General</b> .....	<b>8</b>
<b>4.1.2</b> <b>Symbol</b> .....	<b>8</b>
<b>4.1.3</b> <b>Number</b> .....	<b>8</b>
<b>4.2</b> <b>Material condition</b> .....	<b>8</b>
<b>4.3</b> <b>Product</b> .....	<b>8</b>
<b>5</b> <b>Ordering information</b> .....	<b>10</b>
<b>6</b> <b>Requirements</b> .....	<b>10</b>
<b>6.1</b> <b>Composition</b> .....	<b>10</b>
<b>6.2</b> <b>Mechanical properties</b> .....	<b>11</b>
<b>6.2.1</b> <b>Hardness properties</b> .....	<b>11</b>
<b>6.2.2</b> <b>Tensile properties</b> .....	<b>11</b>
<b>6.3</b> <b>Electrical properties</b> .....	<b>11</b>
<b>6.4</b> <b>Resistance to dezincification</b> .....	<b>11</b>
<b>6.5</b> <b>Residual stress level</b> .....	<b>11</b>
<b>6.6</b> <b>Tolerances for die forgings</b> .....	<b>11</b>
<b>6.6.1</b> <b>General</b> .....	<b>11</b>
<b>6.6.2</b> <b>Tolerances for dimensions within the die cavity and for dimensions across the die parting line</b> .....	<b>12</b>
<b>6.6.3</b> <b>Mismatch</b> .....	<b>13</b>
<b>6.6.4</b> <b>Flash projection</b> .....	<b>14</b>
<b>6.6.5</b> <b>Ejector marks</b> .....	<b>15</b>
<b>6.6.6</b> <b>Flatness tolerances</b> .....	<b>15</b>
<b>6.6.7</b> <b>Angular tolerances</b> .....	<b>16</b>
<b>6.7</b> <b>Tolerances for cored forgings</b> .....	<b>16</b>
<b>6.8</b> <b>Tolerances for hand forgings</b> .....	<b>17</b>
<b>6.8.1</b> <b>General</b> .....	<b>17</b>
<b>6.8.2</b> <b>Tolerances on dimensions</b> .....	<b>18</b>
<b>6.8.3</b> <b>Flatness tolerance</b> .....	<b>18</b>
<b>6.9</b> <b>Surface quality</b> .....	<b>19</b>
<b>6.10</b> <b>Drawings</b> .....	<b>19</b>
<b>7</b> <b>Sampling</b> .....	<b>19</b>
<b>7.1</b> <b>General</b> .....	<b>19</b>
<b>7.2</b> <b>Analysis</b> .....	<b>19</b>
<b>7.3</b> <b>Hardness, stress corrosion resistance, dezincification resistance and electrical property tests</b> .....	<b>20</b>
<b>8</b> <b>Test methods</b> .....	<b>20</b>
<b>8.1</b> <b>Analysis</b> .....	<b>20</b>
<b>8.2</b> <b>Hardness test</b> .....	<b>20</b>

8.3	Electrical conductivity test .....	20
8.4	Dezincification resistance test .....	20
8.5	Stress corrosion resistance test .....	20
8.6	Retests .....	21
8.6.1	Analysis, hardness, electrical conductivity and dezincification resistance tests .....	21
8.6.2	Stress corrosion resistance test .....	21
8.7	Rounding of results .....	21
9	Declaration of conformity and inspection documentation .....	21
9.1	Declaration of conformity .....	21
9.2	Inspection documentation .....	21
10	Marking, labelling, packaging .....	22
Annex A (informative)	Recommended guidelines for design .....	39
A.1	Introduction .....	39
A.2	General information .....	39
A.3	Guidelines for die forgings .....	40
A.3.1	Drafts .....	40
A.3.2	Web thicknesses .....	40
A.3.3	Side wall thicknesses .....	41
A.3.4	Rib design .....	42
A.3.5	Cores .....	43
A.3.6	Flash .....	44
A.3.7	Transition radii .....	45
A.3.8	Clamping lengths and clamping areas for finish machining .....	47
A.3.9	Design for cross-sectional shapes .....	47
A.3.10	Recommended machining allowances and total allowances .....	48
A.4	Guidelines for hand forgings .....	50
A.4.1	General .....	50
A.4.2	General information .....	50
A.4.3	Section changes and transitions .....	51
A.4.4	Recommended machining allowances .....	51
A.4.5	Total allowances per side of forging .....	52
A.5	Guidelines for marking .....	52
Annex B (informative)	Tensile properties .....	54
Annex ZA (informative)	Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC, Pressure Equipment Directive (PED) .....	58
Bibliography	.....	59

## Foreword

This document (EN 12420:2014) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014 and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12420:1999.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Pressure Equipment Directive (PED) 97/23/EC.

For relationship with EU Directive 97/23/EC, see informative Annex ZA, which is an integral part of this document.

This is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- EN 12163, *Copper and copper alloys — Rod for general purposes*;
- EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
- EN 12165, *Copper and copper alloys — Wrought and unwrought forging stock*;
- EN 12166, *Copper and copper alloys — Wire for general purposes*;
- EN 12167, *Copper and copper alloys — Profiles and rectangular bars for general purposes*;
- EN 12168, *Copper and copper alloys — Hollow rod for free machining purposes*.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 4 "Extruded and drawn products, forgings and scrap" to revise the following standard: EN 12420:1999, *Copper and copper alloys — Forgings*.

In comparison with EN 12420:1999, the following significant technical changes were made:

- 1) new text has been introduced concerning optional restrictions to chemical compositions of materials with respect to individual uses or regulations for the use in contact with drinking water;
- 2) materials have been considered coherently with EN 12165:2011;
- 3) four new materials have been added: CuZn35Pb1,5AlAs (CW625N), CuZn33Pb1,5AlAs (CW626N), CuZn21Si3P (CW724R) and CuZn33Pb1AlSiAs (CW725R);
- 4) the mechanical properties have been modified to reflect market needs;
- 5) an informative Annex B Tensile properties has been introduced.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

## Introduction

The European Committee for Standardization (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning the alloys CuZn21Si3P (CW724R) and CuZn33Pb1AlSiAs (CW725R).

CEN takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the CEN that he/she is willing to negotiate licences under reasonable and not-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with CEN.

— For CuZn21Si3P (CW724R) information may be obtained from:

Wieland-Werke AG  
Graf Arco Straße 36  
89079 Ulm  
GERMANY

— For CuZn33Pb1AlSiAs (CW725R) information may be obtained from:

Diehl Metall Messing  
Heinrich-Diehl-Straße 9  
D-90552 Röthenbach/Pegnitz  
GERMANY

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. CEN shall not be held responsible for identifying any or all such patent rights.

CEN (<http://www.cen.eu/cen/WorkArea/IPR/Pages/default.aspx>) and CENELEC (<http://www.cenelec.eu/membersandexperts/toolsandapplications/index.html>) maintain on-line lists of patents relevant to their standards. Users are encouraged to consult the lists for the most up to date information concerning patents.

Due to developing legislation, the composition of a material may be restricted to the composition specified in this European Standard with respect to individual uses (e.g. for the use in contact with drinking water in some Member States of the European Union). These individual restrictions are not part of this European Standard. Nevertheless, for materials for which traditional and major uses are affected, these restrictions are indicated. The absence of an indication, however, does not imply that the material can be used in any application without any legal restriction.

## 1 Scope

This European Standard specifies the composition, the property requirements and tolerances on dimensions and form for copper and copper alloy die and hand forgings.

The sampling procedures, the methods of test for verification of conformity to the requirements of this standard, and the delivery conditions are also specified.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1173, *Copper and copper alloys — Material condition designation*

EN 1655, *Copper and copper alloys — Declarations of conformity*

EN 1976, *Copper and copper alloys — Cast unwrought copper products*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 14977, *Copper and copper alloys — Detection of tensile stress — 5 % ammonia test*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*

EN ISO 6509, *Corrosion of metals and alloys — Determination of dezincification resistance of brass (ISO 6509)*

ISO 2768-1, *General tolerances — Part 1: Tolerances for linear and angular dimensions without individual tolerance indications*

ISO 6957, *Copper alloys — Ammonia test for stress corrosion resistance*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **forging**

wrought product, hot formed by hammering or pressing

#### 3.1.1

##### **die forging**

forging produced between closed dies

#### 3.1.2

##### **hand forging**

forging produced between open dies

#### 3.1.3

##### **cored forging**

forging produced between closed dies including cores