

**Asfaltsegud. Kuuma asfaltsegu katsemeetodid. Osa 49:  
Haardeteguri määramine**

**Bituminous mixtures - Test methods for hot mix asphalt  
- Part 49: Determination of friction after polishing**

## EESTI STANDARDI EESSÕNA

See Eesti standard EVS-EN 12697-49:2014 sisaldab Euroopa standardi EN 12697-49:2014 ingliskeelset teksti.

Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.

Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.01.2014.

Standard on kättesaadav Eesti Standardikeskusest.

## NATIONAL FOREWORD

This Estonian standard EVS-EN 12697-49:2014 consists of the English text of the European standard EN 12697-49:2014.

This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.

Date of Availability of the European standard is 22.01.2014.

The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 93.080.20

### Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Aru 10, 10317 Tallinn, Eesti; [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

### The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:  
Aru 10, 10317 Tallinn, Estonia; [www.evs.ee](http://www.evs.ee); phone 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

ICS 93.080.20

English Version

## Bituminous mixtures - Test methods for hot mix asphalt - Part 49: Determination of friction after polishing

Mélanges bitumineux - Méthodes d'essai pour mélange  
hydrocarboné à chaud - Partie 49: Détermination du  
coefficient de frottement après polissage

Asphalt - Prüfverfahren für Heißasphalt - Teil 49: Messung  
der Griffigkeit nach Polierung

This European Standard was approved by CEN on 9 November 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

Page

Foreword.....	3
<b>1 Scope .....</b>	<b>6</b>
<b>2 Normative references .....</b>	<b>6</b>
<b>3 Terms, definitions and symbols.....</b>	<b>6</b>
3.1 Terms and definitions .....	6
3.2 Symbols .....	6
<b>4 Principle.....</b>	<b>7</b>
<b>5 Equipment .....</b>	<b>7</b>
5.1 Test device .....	7
5.1.1 General.....	7
5.1.2 Polishing unit .....	7
5.1.3 Specimen clamping system.....	10
5.1.4 Friction measuring unit.....	10
5.2 Glass-control plate .....	12
5.3 Sand-blasting-equipment.....	12
<b>6 Other materials.....</b>	<b>12</b>
6.1 Quartz powder.....	12
6.2 Water quartz powder mixture .....	13
6.3 Corundum.....	13
<b>7 Test method.....</b>	<b>13</b>
7.1 Preparation of the specimens .....	13
7.1.1 Specimens prepared in the laboratory .....	13
7.1.2 Specimens taken from the site.....	13
7.2 Polishing procedure .....	14
7.3 Friction measurement .....	14
7.3.1 Pre-test check of the measurement device.....	14
7.3.2 Friction test .....	15
<b>8 Calculation and expression of the results .....</b>	<b>15</b>
8.1 Friction force and friction coefficient .....	15
8.2 Determination of FAP .....	15
<b>9 Test report .....</b>	<b>16</b>
<b>10 Precision.....</b>	<b>16</b>
<b>Annex A (informative) Example of polishing head and friction unit.....</b>	<b>17</b>
<b>Bibliography .....</b>	<b>18</b>

## Foreword

This document (EN 12697-49:2014) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2014, and conflicting national standards shall be withdrawn at the latest by July 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This European Standard is one of a series of standards as listed below:

EN 12697-1, *Bituminous mixtures — Test methods for hot mix asphalt — Part 1: Soluble binder content*

EN 12697-2, *Bituminous mixtures — Test methods for hot mix asphalt — Part 2: Determination of particle size distribution*

EN 12697-3, *Bituminous mixtures — Test methods for hot mix asphalt — Part 3: Bitumen recovery: Rotary evaporator*

EN 12697-4, *Bituminous mixtures — Test methods for hot mix asphalt — Part 4: Bitumen recovery: Fractionating column*

EN 12697-5, *Bituminous mixtures — Test methods for hot mix asphalt — Part 5: Determination of the maximum density*

EN 12697-6, *Bituminous mixtures — Test methods for hot mix asphalt — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-7, *Bituminous mixtures — Test methods for hot mix asphalt — Part 7: Determination of bulk density of bituminous specimens by gamma rays*

EN 12697-8, *Bituminous mixtures — Test methods for hot mix asphalt — Part 8: Determination of void characteristics of bituminous specimens*

EN 12697-10, *Bituminous mixtures — Test methods for hot mix asphalt — Part 10: Compactability*

EN 12697-11, *Bituminous mixtures — Test methods for hot mix asphalt — Part 11: Determination of the affinity between aggregate and bitumen*

EN 12697-12, *Bituminous mixtures — Test methods for hot mix asphalt — Part 12: Determination of the water sensitivity of bituminous specimens*

EN 12697-13, *Bituminous mixtures — Test methods for hot mix asphalt — Part 13: Temperature measurement*

EN 12697-14, *Bituminous mixtures — Test methods for hot mix asphalt — Part 14: Water content*

EN 12697-15, *Bituminous mixtures — Test methods for hot mix asphalt — Part 15: Determination of the segregation sensitivity*

- EN 12697-16, *Bituminous mixtures — Test methods for hot mix asphalt — Part 16: Abrasion by studded tyres*
- EN 12697-17, *Bituminous mixtures — Test methods for hot mix asphalt — Part 17: Particle loss of porous asphalt specimen*
- EN 12697-18, *Bituminous mixtures — Test methods for hot mix asphalt — Part 18: Binder drainage*
- EN 12697-19, *Bituminous mixtures — Test methods for hot mix asphalt — Part 19: Permeability of specimen*
- EN 12697-20, *Bituminous mixtures — Test methods for hot mix asphalt — Part 20: Indentation using cube or cylindrical specimens (CY)*
- EN 12697-21, *Bituminous mixtures — Test methods for hot mix asphalt — Part 21: Indentation using plate specimens*
- EN 12697-22, *Bituminous mixtures — Test methods for hot mix asphalt — Part 22: Wheel tracking*
- EN 12697-23, *Bituminous mixtures — Test methods for hot mix asphalt — Part 23: Determination of the indirect tensile strength of bituminous specimens*
- EN 12697-24, *Bituminous mixtures — Test methods for hot mix asphalt — Part 24: Resistance to fatigue*
- EN 12697-25, *Bituminous mixtures — Test methods for hot mix asphalt — Part 25: Cyclic compression test*
- EN 12697-26, *Bituminous mixtures — Test methods for hot mix asphalt — Part 26: Stiffness*
- EN 12697-27, *Bituminous mixtures — Test methods for hot mix asphalt — Part 27: Sampling*
- EN 12697-28, *Bituminous mixtures — Test methods for hot mix asphalt — Part 28: Preparation of samples for determining binder content, water content and grading*
- EN 12697-29, *Bituminous mixtures — Test method for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen*
- EN 12697-30, *Bituminous mixtures — Test methods for hot mix asphalt — Part 30: Specimen preparation by impact compactor*
- EN 12697-31, *Bituminous mixtures — Test methods for hot mix asphalt — Part 31: Specimen preparation by gyratory compactor*
- EN 12697-32, *Bituminous mixtures — Test methods for hot mix asphalt — Part 32: Laboratory compaction of bituminous mixtures by vibratory compactor*
- EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*
- EN 12697-34, *Bituminous mixtures — Test methods for hot mix asphalt — Part 34: Marshall test*
- EN 12697-35, *Bituminous mixtures — Test methods for hot mix asphalt — Part 35: Laboratory mixing*
- EN 12697-36, *Bituminous mixtures — Test methods for hot mix asphalt — Part 36: Determination of the thickness of a bituminous pavement*
- EN 12697-37, *Bituminous mixtures — Test methods for hot mix asphalt — Part 37: Hot sand test for the adhesivity of binder on precoated chippings for HRA*

EN 12697-38, *Bituminous mixtures — Test methods for hot mix asphalt — Part 38: Common equipment and calibration*

EN 12697-39, *Bituminous mixtures — Test methods for hot mix asphalt — Part 39: Binder content by ignition*

EN 12697-40, *Bituminous mixtures — Test methods for hot mix asphalt — Part 40: In situ drainability*

EN 12697-41, *Bituminous mixtures — Test methods for hot mix asphalt — Part 41: Resistance to de-icing fluids*

EN 12697-42, *Bituminous mixtures — Test methods for hot mix asphalt — Part 42: Amount of foreign matter in reclaimed asphalt*

EN 12697-43, *Bituminous mixtures — Test methods for hot mix asphalt — Part 43: Resistance to fuel*

EN 12697-44, *Bituminous mixtures — Test methods for hot mix asphalt — Part 44: Crack propagation by semi-circular bending test*

EN 12697-45, *Bituminous mixtures — Test methods for hot mix asphalt — Part 45: Saturation Ageing Tensile Stiffness (SATS) conditioning test*

EN 12697-46, *Bituminous mixtures — Test methods for hot mix asphalt — Part 46: Low temperature cracking and properties by uniaxial tension tests*

EN 12697-47, *Bituminous mixtures — Test methods for hot mix asphalt — Part 47: Determination of the ash content of natural asphalts*

prEN 12697-48, *Bituminous mixtures — Test methods for hot mix asphalt — Part 48: Interlayer Bonding (Torque bond test — TBT, Shear bond test - SBT, Tensile Adhesion Test (TAT)<sup>1)</sup>*

EN 12697-49, *Bituminous mixtures — Test methods for hot mix asphalt — Part 49: Determination of friction after polishing*

prCEN/TS 12697-50, *Bituminous mixtures — Test methods for hot mix asphalt — Part 50: Scuffing resistance of surface course<sup>1)</sup>*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

---

<sup>1)</sup> In preparation.

## 1 Scope

This European Standard describes a test method to determine the friction at 60 km/h after polishing during a fixed number of passes on surfaces of bituminous mixtures samples.

The samples used are either produced in a laboratory or are cores taken from the site.

NOTE This procedure was previously known as Wehner and Schulze method (see [1]).

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-27, *Bituminous mixtures - Test methods for hot mix asphalt - Part 27: Sampling*

EN 12697-33, *Bituminous mixtures — Test methods for hot mix asphalt — Part 33: Specimen prepared by roller compactor*

ISO 4662, *Rubber, vulcanized or thermoplastic — Determination of rebound resilience*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

## 3 Terms, definitions and symbols

### 3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1.1

##### **pass**

application of a single roller of the polishing head, a complete revolution of which is equivalent to three passes of the roller

### 3.2 Symbols

$\mu_{FAP}$	single result of friction
$\mu_m$	friction coefficient at 60 km/h
$\mu_{km}$	mean value of the control plate before and after the friction measurement
$\mu_{ref}$	known value of the Laboratory Skid Resistance of the control plate
FAP	Friction After Polishing: average of two or more single results $\mu_{FAP}$
$\emptyset$	diameter in mm