

## **Supersulfaattsement. Koostis, spetsifikatsioonid ja vastavuskriteeriumid**

Supersulfated cement - Composition, specifications and conformity criteria

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 15743:2010 sisaldab Euroopa standardi EN 15743:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.03.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 20.01.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 15743:2010 consists of the English text of the European standard EN 15743:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.03.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 20.01.2010.

The standard is available from Estonian standardisation organisation.

ICS 91.100.10

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: +372 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

ICS 91.100.10

English Version

## Supersulfated cement - Composition, specifications and conformity criteria

Ciment sulfaté - Composition, spécifications et critères de conformité

Sulfathüttenzement - Zusammensetzung, Anforderungen und Konformitätskriterien

This European Standard was approved by CEN on 11 December 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

# Contents

Page

Foreword.....	4
Introduction.....	5
<b>1</b> <b>Scope</b> .....	<b>6</b>
<b>2</b> <b>Normative references</b> .....	<b>6</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>6</b>
<b>4</b> <b>Supersulfated cement</b> .....	<b>8</b>
<b>5</b> <b>Constituents</b> .....	<b>8</b>
<b>5.1</b> <b>Main constituents</b> .....	<b>8</b>
<b>5.1.1</b> <b>Granulated blastfurnace slag (S)</b> .....	<b>8</b>
<b>5.1.2</b> <b>Calcium sulfate (Cs)</b> .....	<b>8</b>
<b>5.2</b> <b>Additional constituents</b> .....	<b>8</b>
<b>5.2.1</b> <b>Portland cement clinker (K)</b> .....	<b>8</b>
<b>5.2.2</b> <b>Other additional constituents (A)</b> .....	<b>8</b>
<b>5.3</b> <b>Additives</b> .....	<b>9</b>
<b>6</b> <b>Composition and notation</b> .....	<b>9</b>
<b>7</b> <b>Mechanical, physical, chemical and durability requirements</b> .....	<b>10</b>
<b>7.1</b> <b>Mechanical requirements</b> .....	<b>10</b>
<b>7.1.1</b> <b>Standard strength</b> .....	<b>10</b>
<b>7.1.2</b> <b>Early strength</b> .....	<b>10</b>
<b>7.2</b> <b>Physical requirements</b> .....	<b>10</b>
<b>7.2.1</b> <b>Initial setting time</b> .....	<b>10</b>
<b>7.2.2</b> <b>Soundness</b> .....	<b>10</b>
<b>7.2.3</b> <b>Heat of hydration</b> .....	<b>10</b>
<b>7.3</b> <b>Chemical requirements</b> .....	<b>11</b>
<b>7.4</b> <b>Durability requirements</b> .....	<b>11</b>
<b>7.4.1</b> <b>General</b> .....	<b>11</b>
<b>7.4.2</b> <b>Sulfate resistance</b> .....	<b>11</b>
<b>8</b> <b>Standard designation</b> .....	<b>11</b>
<b>9</b> <b>Conformity criteria</b> .....	<b>12</b>
<b>9.1</b> <b>General requirements</b> .....	<b>12</b>
<b>9.2</b> <b>Conformity criteria for mechanical, physical and chemical properties and evaluation procedure</b> .....	<b>12</b>
<b>9.2.1</b> <b>General</b> .....	<b>12</b>
<b>9.2.2</b> <b>Statistical conformity criteria</b> .....	<b>13</b>
<b>9.2.3</b> <b>Single result conformity criteria</b> .....	<b>15</b>
<b>9.3</b> <b>Conformity criteria for cement composition</b> .....	<b>15</b>
<b>9.4</b> <b>Conformity criteria for properties of the cement constituents</b> .....	<b>16</b>
<b>Annex A</b> (informative) <b>Precautions related to the use of supersulfated cement</b> .....	<b>17</b>
<b>A.1</b> <b>Blending with other binders</b> .....	<b>17</b>
<b>A.2</b> <b>Use of additions in concrete</b> .....	<b>17</b>
<b>A.3</b> <b>Effects of weather, striking and curing</b> .....	<b>17</b>
<b>A.4</b> <b>Heat treatment</b> .....	<b>17</b>
<b>Annex ZA</b> (informative) <b>Clauses of this European Standard addressing the provisions of the EU Construction Products Directive</b> .....	<b>18</b>
<b>ZA.1</b> <b>Scope and relevant characteristics</b> .....	<b>18</b>
<b>ZA.2</b> <b>Procedure for attestation of conformity of supersulfated cements</b> .....	<b>20</b>
<b>ZA.2.1</b> <b>System of attestation of conformity</b> .....	<b>20</b>
<b>ZA.2.2</b> <b>EC Certificate and Declaration of conformity</b> .....	<b>21</b>
<b>ZA.3</b> <b>CE marking and labelling</b> .....	<b>21</b>

**ZA.3.1 General .....21**  
**ZA.3.2 Bagged cement.....22**  
**ZA.3.3 Bulk cement .....23**  
**Bibliography.....24**

This document is a preview generated by EVS

## Foreword

This document (EN 15743:2010) has been prepared by Technical Committee CEN/TC 51 "Cement and building limes", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2010, and conflicting national standards shall be withdrawn at the latest by July 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Annex A is informative.

This European Standard sets out requirements for the composition and specifications of supersulfated cement. The scheme for the evaluation of conformity of supersulfated cement is that specified in EN 197-2.

The requirements in this European Standard are based on the results of tests on cement in accordance with parts 1, 2, 3, 7, 8 and 9 of EN 196, *Methods of testing cement*.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

The basis for this European Standard has been the national standards already existing in Europe. Supersulfated cement was originally standardised in several European countries, Belgium, France, Germany, Netherlands and the United Kingdom, and has been used in concrete for foundations and massive structures. The demand for quick setting cements enabling early formwork removal caused the manufacturing of supersulfated cements to be superseded by those based on Portland cement clinker. Standards were either abandoned, as in France, or kept in the catalogue of standards but never used, as in the United Kingdom.

In discharging the mandate given to CEN, Technical Committee TC 51 considered the large number of different cements involved. It was decided to separate the "common cements", where the hardening mainly depends on the hydration of calcium silicates and setting these out in EN 197-1, from "special cements", i.e. those with additional or special properties.

Supersulfated cement hardening depends on granulated blastfurnace slag activation by calcium sulfate. A lower heat of hydration than for Portland cement clinker results in lower early compressive strength than common cements and a significantly lower early heat of hydration. In addition, it produces concrete which has resistance to chemically aggressive environments, such as sulfates.

Ongoing developments in material technology as well as in production technology again open the option to produce supersulfated cement fulfilling the demands and requirements of the market. As the principles in hydration differ from that of "common cements" covered by EN 197-1, CEN Technical Committee TC 51 decided to elaborate a separate standard for supersulfated cement.

The rate of hardening and lower early strength require that additional precautions are considered when using supersulfated cements to ensure adequate concrete curing.

## 1 Scope

This European Standard defines and gives the specifications of supersulfated cement and its constituents. The definition of supersulfated cement includes the proportions in which the constituents are to be combined to produce products in accordance with this standard. The definition also includes requirements the constituents have to meet and the mechanical, physical, chemical including heat of hydration requirements. This standard also states the conformity criteria and the related rules.

NOTE 1 In addition to the specified requirements, an exchange of additional information between the cement manufacturer and user may be helpful. The procedures for such an exchange are not within the scope of this standard but should be dealt with in accordance with national standards or regulations or may be agreed between the parties concerned.

NOTE 2 The word "cement" in this standard is used to refer only to supersulfated cement unless otherwise specified.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement — Part 1: Determination of strength*

EN 196-2, *Methods of testing cement — Part 2: Chemical analysis of cement*

EN 196-3, *Methods of testing cement — Part 3: Determination of setting times and soundness*

EN 196-7, *Methods of testing cement — Part 7: Methods of taking and preparing samples of cement*

EN 196-8, *Methods of testing cement — Part 8: Heat of hydration — Solution method*

EN 196-9, *Methods of testing cement — Part 9: Heat of hydration — Semi-adiabatic method*

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 197-2:2000, *Cement — Part 2: Conformity evaluation*

EN 459-1, *Building lime — Part 1: Definitions, specifications and conformity criteria*

EN 934 (all parts), *Admixtures for concrete, mortar and grout*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### heat of hydration

quantity of heat generated by cement hydration within a given period of time

### 3.2

#### main constituents

granulated blastfurnace slag and calcium sulfate in a proportion exceeding 90 % by mass related to the sum of all main and additional constituents