

Flexible sheets for waterproofing - Determination of thickness and mass per unit area - Part 2: Plastic and rubber sheets

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 1849-2:2010 sisaldab Euroopa standardi EN 1849-2:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 28.02.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 09.12.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 1849-2:2010 consists of the English text of the European standard EN 1849-2:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 28.02.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 09.12.2009.

The standard is available from Estonian standardisation organisation.

ICS 91.100.50

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

English Version

Flexible sheets for waterproofing - Determination of thickness and mass per unit area - Part 2: Plastic and rubber sheets

Feuilles souples d'étanchéité - Détermination de l'épaisseur et de la masse surfacique - Partie 2: Feuilles d'étanchéité de toiture plastiques et élastomères

Abdichtungsbahnen - Bestimmung der Dicke und der flächenbezogenen Masse - Teil 2: Kunststoff- und Elastomerbahnen für Dachabdichtungen

This European Standard was approved by CEN on 19 October 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Sampling	7
5 Determination of thickness	7
5.1 Principle	7
5.2 Apparatus	7
5.3 Test specimens	7
5.4 Procedure	7
5.4.1 General	7
5.4.2 Mechanical measurement	8
5.4.3 Optical measurement	8
5.5 Expression of results	8
6 Determination of mass per unit area	9
6.1 Principle	9
6.2 Apparatus	9
6.3 Test specimens	9
6.4 Procedure	9
6.5 Expression of results	9
7 Test report	9
Annex A (informative) Example of the cut cross-section of a membrane	10

Foreword

This document (EN 1849-2:2009) has been prepared by Technical Committee CEN/TC 254 “Flexible sheets for waterproofing”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2010, and conflicting national standards shall be withdrawn at the latest by June 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1849-2:2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This European Standard is intended for characterisation of plastic and rubber sheets as manufactured or supplied before use. This test method relates exclusively to products or to their components where appropriate, and not to waterproofing membrane systems composed of such products and installed in the works.

This test is intended to be used in conjunction with EN 13956, *Flexible sheet for waterproofing — Plastic and rubber sheets for roof waterproofing — Definitions and characteristics*.

1 Scope

This European Standard specifies methods for the determination of the thickness and mass per unit area of plastic and rubber sheets for roof waterproofing.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13416, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Rules for sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

surface texture

textured pattern on one or both surfaces of the sheet creating a difference between the effective and overall thickness not exceeding 0,15 mm

NOTE See Figure 2 a) and c).

3.2

surface profile (surface structure)

raised area on the surface of the sheet creating a difference between the effective and overall thickness exceeding 0,15 mm

NOTE See Figure 2 b).

3.3

internal fabric

layer of woven or non-woven fabric of synthetic or mineral fibres incorporated in the sheet. This layer may or may not constitute reinforcement

NOTE See Figure 1 c).

3.4

backing

layer of woven or non-woven fabric of synthetic or mineral fibres or other materials, fixed to the bottom of the sheet

NOTE see Figure 2 d).

3.5

overall thickness

d

thickness of the sheet excluding any surface profile