

Vask ja vasesulamid. Tõmmatud vasktoorik (valtsitud pooltoode - peenike täitevarb)

Copper and copper alloys - Copper drawing stock (wire rod)

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 1977:2013 sisaldab Euroopa standardi EN 1977:2013 ingliskeelset teksti.	This Estonian standard EVS-EN 1977:2013 consists of the English text of the European standard EN 1977:2013.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.01.2013.	Date of Availability of the European standard is 16.01.2013.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.150.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Copper and copper alloys - Copper drawing stock (wire rod)

Cuivre et alliages de cuivre - Fil machine en cuivre

Kupfer und Kupferlegierungen - Vordraht aus Kupfer

This European Standard was approved by CEN on 24 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Designations	5
4.1 Material	5
4.2 Product	6
5 Ordering information	7
6 Requirements	7
6.1 Composition	7
6.2 Elongation	7
6.3 Electrical properties	7
6.4 Annealability	12
6.5 Hydrogen embrittlement	12
6.6 Scale adhesion	13
6.7 Dimensions and tolerances	13
6.8 Surface condition	13
6.9 Joins	13
7 Sampling	13
7.1 General	13
7.2 Analysis (oxygen only) and measurement of diameter of Cu-ETP1 (CW003A) drawing stock	14
7.3 Annealability testing of Cu-ETP1 (CW003A) drawing stock	14
7.4 Analysis (other than oxygen) and measurement of elongation and electrical properties of Cu-ETP1 (CW003A) drawing stock	14
7.5 Tests on drawing stock in grades other than Cu-ETP1 (CW003A)	14
8 Test methods	15
8.1 Analysis	15
8.2 Elongation	15
8.3 Electrical resistivity	15
8.4 Annealability	16
8.5 Hydrogen embrittlement	16
8.6 Scale adhesion	16
8.7 Rounding of results	16
9 Declaration of conformity and inspection documentation	16
9.1 Declaration of conformity	16
9.2 Inspection documentation	17
10 Marking	17
Annex A (informative) Information on electrical resistivity and conductivity relationships	18
A.1 Volume resistivity	18
A.2 Standard annealed copper (IACS)	18
A.3 Commercial annealed copper	18
A.4 Nominal mass resistivity	18
A.5 Differences between measured and nominal values	19
Annex B (normative) Rapid Elongation Test method (AR-Test) for diameter 8 mm Cu-ETP1 wire rod	20
B.1 General	20
B.2 Procedure	20
B.3 Test results	22
Bibliography	23

Foreword

This document (EN 1977:2013) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2013, and conflicting national standards shall be withdrawn at the latest by July 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1977:1998.

This document is one of a series of European Standards for products manufactured from refined copper grades.

Other products are specified as follows:

- EN 1976, *Copper and copper alloys — Cast unwrought copper products*
- EN 1978, *Copper and copper alloys — Copper cathodes*
- EN 13602, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*

In comparison with EN 1977:1998, the following significant technical changes were made:

- a) Table 2, Cu-FRHC, Other elements: content has been modified and a new footnote “d” has been added;
- b) 6.4 and 8.4 “Annealability” have been modified;
- c) A.2 “Standard annealed copper (IACS)” has been modified;
- d) Annex B (normative) “Rapid Elongation Test method (AR-Test) for diameter 8 mm Cu-ETP1 wire rod” has been added.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Copper drawing stock (wire rod) is normally manufactured by one of the following process routes:

- continuous casting and hot rolling in tandem;
- continuous or semi-continuous casting and cold rolling;
- rolling of wire bar or billets; or
- extrusion.

Annex A (informative) gives information on the relationships between electrical resistivity and conductivity (of copper).

Annex B (normative) describes the rapid elongation test method (AR-Test) for diameter 8 mm Cu-ETP1 wire rod.

1 Scope

This European Standard specifies the composition, mechanical, electrical and physical properties for high conductivity copper drawing stock (wire rod) suitable for fabrication into wire by cold drawing, principally for the manufacture of electrical conductors. This European Standard covers drawing stock (wire rod), in nine grades of copper and nine silver-bearing copper grades. Normally, the cross-section is approximately circular, in a range of diameters from 6 mm.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1655, *Copper and copper alloys — Declarations of conformity*

EN 10204, *Metallic products — Types of inspection documents*

EN 12893, *Copper and copper alloys — Determination of spiral elongation number*

EN ISO 2626, *Copper — Hydrogen embrittlement test (ISO 2626)*

EN ISO 6892-1:2009, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2009)*

IEC 60468, *Method of measurement of resistivity of metallic materials*

ISO 4746, *Oxygen-free copper — Scale adhesion test*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

drawing stock

wire rod

intermediate solid wrought product, of uniform cross-section along its whole length, supplied in coils

4 Designations

4.1 Material

4.1.1 General

The material is designated either by symbol or number (see Tables 1 to 4).

4.1.2 Symbol

The material symbol designation is based on the designation system given in ISO 1190-1.

NOTE Although material symbol designations used in this standard might be the same as those in other standards using the designation system given in ISO 1190-1, the detailed composition requirements are not necessarily the same.

4.1.3 Number

The material number designation is in accordance with the system given in EN 1412.