

Aluminium and aluminium alloys - Wrought products -
Temper designations

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 515:2017 sisaldab Euroopa standardi EN 515:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 515:2017 consists of the English text of the European standard EN 515:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 08.03.2017.	Date of Availability of the European standard is 08.03.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 01.040.77, 77.120.10, 77.150.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 515

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2017

ICS 01.040.77; 77.120.10; 77.150.01

Supersedes EN 515:1993

English Version

Aluminium and aluminium alloys - Wrought products - Temper designations

Aluminium et alliages d'aluminium - Produits corroyés
- Désignation des états métallurgiques

Aluminium und Aluminiumlegierungen - Halbzeug -
Bezeichnungen der Werkstoffzustände

This European Standard was approved by CEN on 6 February 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Basis of codification	6
5 Basic temper designations	6
5.1 F - as fabricated	6
5.2 O - Annealed	6
5.3 H - Strain-hardened	6
5.4 W - Solution heat-treated	7
5.5 T - Thermally treated to produce stable tempers other than F, O or H (for heat-treatable alloys only)	7
6 Subdivision of O (annealed) temper designations	7
6.1 O ₁ - High temperature annealed and slow cooled	7
6.2 O ₂ - Thermo-mechanically processed	7
6.3 O ₃ - Homogenized	7
7 Subdivision of H (strain-hardened) temper designations	7
8 Subdivision of T (thermally treated to produce stable tempers other than F, O or H) temper designations	10
8.1 First digit after T.....	10
8.2 Additional digits added to designations T1 to T10	12
8.3 Assigned additional digits for stress-relieved T tempers	12
8.3.1 Stress-relieved by stretching	12
8.3.2 Stress-relieved by compressing.....	13
8.3.3 Stress-relieved by combined stretching and compressing.....	13
8.3.4 Assigned additional digits for stress-relieved W tempers.....	13
8.4 Assigned additional digits for variations of T7 type tempers.....	13
8.5 Demonstration of response to heat treatment.....	14
8.5.1 Temper designations for producer/supplier — Laboratory demonstration of response to heat treatment.....	14
8.5.2 Temper designations for producer/supplier — Demonstration of response to temper conversion	14
8.5.3 Temper designations for purchaser/user heat treatment	14
9 Summary	14
Annex A (informative) Recommendations for further T tempers extensions	23
A.1 Numeral 1 as a second digit after T	23
A.2 Numerals 1 and 3 to 9 as a second digit after T3, T8 or T9	23
A.3 Numerals 1 and 3 to 5 as a second digit after T5 or T6	23
A.4 Numeral 6 as a second digit after T5 or T6	23
A.5 Summary of possible uses of a second digit after T	23
Bibliography	25

European foreword

This document (EN 515:2017) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2017, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 515:1993.

The following modifications were implemented in this new version of EN 515:

- Addition of Clause 2 “Normative references”;
- new definitions and sources in Clause 3;
- new precision in Subclauses 6.1, 7 and 7.3;
- new Table 1 and modification of Table 2;
- improvement of the content of Clause 8.4;
- modification of Figure 1;
- inclusion of new tempers in Table 3: T552, T554, T72, T72510, T72511, T74511, T7452, T7454, T7752, T7754, T7852, T7854, T7952 and T7954;
- modification of new tempers in Table 3: H131, T3510;
- updating Annex A.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard establishes temper designations for all forms of wrought aluminium and aluminium alloys and for continuously cast aluminium and aluminium alloys drawing stock and strip intended to be wrought.

NOTE Some of these temper designations may be subject of patent or patent applications and their listing herein is not to be construed in any way as the granting of a license under such patent right.

Additional temper designations, conforming to this standard, may be standardized with CEN/TC 132 and AECMA/5 provided:

- the temper is used or is available for use by more than one user;
- mechanical property limits are defined;
- the characteristics of the temper are significantly different from those of all other tempers which have the same sequence of basic treatments and for which designations already have been assigned for the same alloy and product;
- the following are also defined if characteristics other than mechanical properties are considered significant:
 - a) test methods and limits for the characteristics; or
 - b) the specific practices used to produce the temper.

2 Normative references

Not applicable.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

**3.1
temper**
condition of the metal produced by mechanical and/or thermal processing, typically characterized by a certain structure and specified properties

[SOURCE: EN 12258-1:2012, 3.6.5]

**3.2
hot working**
forming of a solid metal after preheating

Note 1 to entry: Strain hardening may or may not occur during hot working.

[SOURCE: EN 12258-1:2012, 3.2.3]