

Textiles - Tests for colour fastness - Part D02: Colour fastness to rubbing: Organic solvents (ISO 105-D02:2016)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 105-D02:2016 sisaldab Euroopa standardi EN ISO 105-D02:2016 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 105-D02:2016 consists of the English text of the European standard EN ISO 105-D02:2016.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.06.2016.	Date of Availability of the European standard is 22.06.2016.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 59.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 105-D02

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2016

ICS 59.080.01

Supersedes EN ISO 105-D02:1995

English Version

Textiles - Tests for colour fastness - Part D02: Colour fastness to rubbing: Organic solvents (ISO 105-D02:2016)

Textiles - Essais de solidité des coloris - Partie D02: Solidité des coloris au frottement: Solvants organiques (ISO 105-D02:2016)

Textilien - Farbechtheitsprüfungen - Teil D02: Farbechtheit gegen Reiben: Organische Lösemittel (ISO 105-D02:2016)

This European Standard was approved by CEN on 15 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 105-D02:2016) has been prepared by Technical Committee ISO/TC 38 “Textiles” in collaboration with Technical Committee CEN/TC 248 “Textiles and textile products” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2016, and conflicting national standards shall be withdrawn at the latest by December 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 105-D02:1995.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 105-D02:2016 has been approved by CEN as EN ISO 105-D02:2016 without any modification.

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Principle.....	1
4 Apparatus and materials.....	1
5 Test specimens.....	2
6 Procedure.....	2
7 Test report.....	2
Bibliography.....	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

This fifth edition cancels and replaces the fourth edition (ISO 105-D02:1993), of which it constitutes a minor revision.

ISO 105 consists of many parts designated by a part letter and a two-digit serial number (e.g. A01), under the general title *Textiles — Tests for colour fastness*. A complete list of these parts is given in ISO 105-A01.

Textiles — Tests for colour fastness —

Part D02:

Colour fastness to rubbing: Organic solvents

1 Scope

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds and in all forms, except loose fibre, to the combined action of rubbing and of organic solvents used in spot-cleaning, localized “spotting” carried out by hand.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-F09, *Textiles — Tests for colour fastness — Part F09: Specification for cotton rubbing cloth*

3 Principle

A specimen of the textile is rubbed with rubbing cotton impregnated with solvent. The change in colour of the specimen and the staining of the rubbing cotton cloth are assessed with the grey scales.

4 Apparatus and materials

4.1 Suitable testing device for determining the colour fastness to rubbing with organic solvents. Such a device shall be equipped with a finger of 16 mm diameter moving to and fro in a straight line along a track 100 mm on the specimen, with a downward force of 9 N.

NOTE 1 A suitable apparatus is described in Reference [2], Test Method 8. Other devices can be used, provided that the same results are obtained as with the apparatus described above.

The finger of the apparatus can be replaced by a moving hollow tube ending in a grille at its base. A plug of cotton is placed in this tube. The outside of the grille is covered with a sample of wool flannel.

With apparatus modified in this way, it is no longer necessary to immerse the rubbing cotton in the solvent (see 6.1), the dry rubbing cotton cloth is placed on the wool flannel at the end of the tube and 3 ml of the solvent are dropped on to the plug of cotton on the inside of the hollow tube. Then proceed as described in 6.2.

4.2 Rubbing cotton cloth, complying with ISO 105-F09 and cut into squares measuring 50 mm × 50 mm.

4.3 Grating, of stainless steel wire of 1 mm diameter and a width of mesh of about 20 mm.