

KIVISTUNUD BETOONI KATSETAMINE. OSA 14:
POOL-ADIABAATILINE MEETOD BETOONIST
KIVISTUMISEL ERALDUVA SOOJUSE MÄÄRAMISEKS

Testing hardened concrete - Part 14: Semi-adiabatic
method for the determination of heat released by
concrete during its hardening process

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12390-14:2018 sisaldab Euroopa standardi EN 12390-14:2018 ingliskeelset teksti.	This Estonian standard EVS-EN 12390-14:2018 consists of the English text of the European standard EN 12390-14:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 08.08.2018.	Date of Availability of the European standard is 08.08.2018.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

ICS 91.100.30

English Version

Testing hardened concrete - Part 14: Semi-adiabatic method for the determination of heat released by concrete during its hardening process

Essais pour béton durci - Partie 14 : Méthode semi-adiabatique de détermination de la chaleur dégagée par le béton en cours de durcissement

Prüfung von Festbeton - Teil 14: Teiladiabatisches Verfahren zur Bestimmung der Wärme, die während des Erhärtungsprozesses von Beton freigesetzt wird

This European Standard was approved by CEN on 9 April 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope	5
2 Normative references	5
3 Terms, definitions, symbols, units and scripts	5
3.1 Terms and definitions	5
3.2 Symbols, units and scripts	6
4 Principle	7
5 Apparatus	7
5.1 Thermometers	7
5.2 Balance	7
5.3 Temperature monitoring and control system	7
5.4 Semi-adiabatic calorimeter	7
5.5 Control specimen	9
6 Procedure	9
7 Expression of results - Semi-adiabatic heat release	10
8 Report	11
9 Precision	11
Annex A (normative) Calibration of semi-adiabatic calorimeter	12
A.1 Calibration of the semi-adiabatic calorimeter	12
A.1.1 General	12
A.1.2 Determination of the total heat loss coefficient	12
A.1.3 Determination of heat capacity	13
A.2 Alternative method for the calibration of semi-adiabatic calorimeter	14
A.2.1 Calibration procedure	14
A.2.2 Determination of heat capacity and heat loss coefficient	14
Annex B (informative) Experimentation on site	16
Annex C (informative) Specific heat of concrete components	17
Bibliography	18

European foreword

This document (EN 12390-14:2018) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2019, and conflicting national standards shall be withdrawn at the latest by February 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This standard is one of a series on testing concrete.

EN 12390, *Testing hardened concrete*, consists of the following parts:

- *Part 1: Shape, dimensions and other requirements of specimens and moulds*
- *Part 2: Making and curing specimens for strength tests*
- *Part 3: Compressive strength of test specimens*
- *Part 4: Compressive strength - Specification for testing machines*
- *Part 5: Flexural strength of test specimens*
- *Part 6: Tensile splitting strength of test specimens*
- *Part 7: Density of hardened concrete*
- *Part 8: Depth of penetration of water under pressure*
- *Part 10: Determination of the carbonation resistance of concrete at atmospheric levels of carbon dioxide*
- *Part 11: Testing hardened concrete. Determination of the chloride resistance of concrete, unidirectional diffusion*
- *Part 13: Determination of secant modulus of elasticity*
- *Part 14: Semi-adiabatic method for the determination of heat released by concrete during its hardening process*
- *Part 15: Adiabatic method for the determination of heat released by concrete during its hardening process*
- *Part 16: Determination of shrinkage of concrete (in preparation)*
- *Part 17: Determination of creep of concrete in compression (in preparation)*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia,

France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies the procedure for the determination of heat released by concrete during its hardening process in semi-adiabatic conditions in a laboratory. Annex B specifies the procedure when the test is performed on site. The test is suitable for specimens having a declared value of D of the coarsest fraction of aggregates actually used in the concrete (D_{\max}) not greater than 32 mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12350-1, *Testing fresh concrete - Part 1: Sampling*

EN 12390-2, *Testing hardened concrete - Part 2: Making and curing specimens for strength tests*

3 Terms, definitions, symbols, units and scripts

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1.1

semi-adiabatic calorimeter

equipment containing a calorimetric cell where the maximum heat losses are limited

3.1.2

calorimeter coefficient of heat loss

(α)

proportionality factor between heat losses and the difference of temperature between inside and outside of the calorimeter; the coefficient of heat loss is a linear function of this difference of temperature

3.1.3

semi-adiabatic heat release

(q)

heat released by unit mass of concrete during its hydration in semi-adiabatic conditions as a function of time

3.1.4

calorimeter cell

element containing the test sample in its mould or control specimen and having an external insulated enclosure with a sealable removable cover