

# TECHNICAL SPECIFICATION



**Selection and dimensioning of high-voltage insulators intended for use in polluted conditions –  
Part 4: Insulators for d.c. systems**



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2016 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

#### IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

#### IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

generated by EVS

# TECHNICAL SPECIFICATION



**Selection and dimensioning of high-voltage insulators intended for use in polluted conditions –  
Part 4: Insulators for d.c. systems**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

ICS 29.080.10

ISBN 978-2-8322-3704-5

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references .....	7
3 Terms, definitions and abbreviated terms .....	8
3.1 Terms and definitions.....	8
3.2 Abbreviated terms.....	9
4 Principles .....	9
4.1 General.....	9
4.2 Overall design process .....	10
5 Materials .....	11
6 Site severity determination .....	12
6.1 Input data .....	12
6.2 d.c. pollution accumulation correction: $K_p$ .....	12
6.3 Chemical composition of the pollution layer (Type A pollution).....	13
6.4 Correcting for NSDD (Type A pollution).....	13
6.5 Correcting for CUR (Type A pollution, cap and pin insulators).....	14
6.6 Effect of diameter on the pollution accumulation $K_d$ .....	14
6.7 Correction for the number of similar insulators in parallel: $K_s$ .....	14
7 Determination of the reference d.c. site severity .....	15
8 Determination of the reference d.c. USCD .....	16
9 Correction of the RUSCD for each candidate insulator.....	17
9.1 Correction for the effect of diameter on pollution withstand performance $C_d$ .....	17
9.2 Correction for altitude $C_a$ .....	18
9.3 Determination of the required USCD for each candidate .....	18
10 Checking the profile parameters .....	19
10.1 General.....	19
10.2 Alternating sheds defined by shed overhang .....	19
10.3 Spacing versus shed overhang .....	20
10.4 Minimum distance between sheds.....	20
10.5 Creepage distance versus clearance.....	21
10.6 Shed angle .....	22
10.7 Creepage factor .....	22
11 Design verification .....	23
11.1 General.....	23
11.2 Operating experience.....	23
11.3 Laboratory testing.....	23
Annex A (informative) Hydrophobicity transfer materials .....	24
A.1 Qualitative flashover behaviour .....	24
Annex B (informative) Dependence of USCD on pollution severity .....	26
B.1 Pollution type A.....	26
B.2 Pollution Type B.....	28
Bibliographic References .....	29

Figure 1 – Overall design process for d.c. insulation – determination of d.c. Site Pollution Severity.....	10
Figure 2 – Overall design process for d.c. insulation – determination of the required $USCD_{dc}$ for candidate insulating solutions.....	11
Figure 3 – $RUSCD_{dc}$ as a function of d.c. site pollution severity .....	16
Figure 4 – Correction for the effect of diameter on d.c. pollution withstand performance .....	18
Figure A.1 – Dependency of specific flashover voltage over conductivity of an electrolyte (parameter: wettability of surface).....	24
Figure B.1 – d.c. overhead lines. Collected field experience on non HTM insulators (uncoated glass and porcelain insulators) .....	26
Figure B.2 – d.c. overhead lines. Collected field experience on HTM insulators (composite line insulators) .....	27
Figure B.3 – Composite insulators: Example of the influence of CF on USCD (laboratory tests), see CIGRE Brochure [1] for more details .....	28
Table 1 – Typical ranges of $K_p$ according to climatic conditions .....	13

This is a preview generated by EVS

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SELECTION AND DIMENSIONING OF HIGH-VOLTAGE  
INSULATORS INTENDED FOR USE IN POLLUTED CONDITIONS –****Part 4: Insulators for d.c. systems**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 60815-4, which is a technical specification, has been prepared by technical committee 36: Insulators.

The text of this technical specification is based on the following documents:

DTS	Report on voting
36/382/DTS	36/390/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60815 series, published under the general title *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**

generated by EVS

## INTRODUCTION

Work has been going on in CIGRE C4.303 and the IEC to produce d.c. pollution design guides that represent the current state of the art. The CIGRE work has resulted in an HV d.c. Pollution Application Guidelines brochure [1] and the IEC work in this final part of IEC 60815 – *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 4: Insulators for d.c. systems.*

The work represents a huge accumulation of pollution performance knowledge from various sources (both published and unpublished) never before collated into a single opus.

Contrary to the parts of IEC 60815 dealing with a.c., this technical specification covers both polymeric and glass and porcelain insulators for d.c. systems in a single publication. It also covers hybrid insulators (the ceramic core is fully covered by a polymer).

NOTE The present document does not apply to insulators with coatings, due to the variety of coatings to be considered. This may be reconsidered at the next revision of this technical specification, after gaining more knowledge and experience and a better definition of the coating characteristics and requirements.

The approach for d.c. insulator design and selection with respect to pollution given in this part is different to that used for a.c. The key differences are:

- A simplified approach is presented which is intended for preliminary design. However, since under d.c. pollution build-up and its effects can be more severe than under a.c., the final design should be based as much as possible on a direct pollution severity measured under d.c. for the site being studied. Equally direct evaluation of the insulators selected by this process should be considered. (A statistical design approach is available in the CIGRE guidelines for d.c. pollution [1]);
- Two approaches are considered to estimate pollution severity: one using prior d.c. site severity experience, the other using site severity measurements on a.c. or unenergised insulators;
- Correction of site severity for specific parameters that have an influence under d.c. (e.g. pollution uniformity ratio, effect of diameter on pollution accumulation, NSDD) are considered;
- Direct transfer from corrected site pollution severity to necessary USCD without any use of discrete site severity classes (as made in IEC 60815 Parts 2 and 3);
- Recognition is made of the improved performance of Hydrophobicity Transfer Materials (HTM) as a practical solution for many designs, notably at UHV, while taking into account potential hydrophobicity loss;
- Importance of the influence of altitude;
- Distinct diameter correction for flashover performance.

Although there is some positive experience with validation by testing of traditional glass and porcelain insulators, the full translation of such test results to service conditions is still under consideration. Any such experience is mainly lacking for composite insulators, since an agreed standardised testing procedure is not yet available. The problem is accentuated to porcelain/glass as well composite technology by the continuing rise in system voltages where over-design may result in unrealistic insulator lengths or heights. Hence for this first edition the verification of a chosen insulator solution by testing is entirely subject to agreement.

For polymeric, notably HTM, the pollution withstand may not be the only necessary design information. The design stress should be selected not only to avoid flashover, but also to assure a limited ageing of the insulators in service. This item is however out of the scope of the present specification.

Applications with controlled indoor environment are not included in the scope of this document.

# SELECTION AND DIMENSIONING OF HIGH-VOLTAGE INSULATORS INTENDED FOR USE IN POLLUTED CONDITIONS –

## Part 4: Insulators for d.c. systems

### 1 Scope

This part of IEC 60815, which is a Technical Specification, is applicable as first approach for the determination of the required d.c. Unified Specific Creepage Distance for insulators with respect to pollution. To avoid excessive over or under design, existing operation experience should be compared and eventually additional appropriate tests may be performed by agreement between supplier and customer.

It is applicable to:

- Glass and porcelain insulators;
- Composite and hybrid insulators with an HTM or non-HTM housing.

This part of IEC 60815 gives specific guidelines and principles to arrive at an informed judgement on the probable behaviour of a given insulator in certain pollution environments.

The structure and approach of this part of IEC 60815 are similar to those explained in Part 1, but adapted for the specific issues encountered with polluted HV d.c. insulation.

The aim of this Technical Specification is to give the user simplified means to:

- Identify issues specific to d.c. applications that can affect the choice and design process;
- Determine the equivalent d.c. Site Pollution Severity (SPS) from measurements, correcting for electrostatic effects, diameter, pollution distribution and composition;
- Determine the reference USCD for different candidate insulating solutions, taking into account materials, dimensions and risk factors;
- Evaluate the suitability of different insulator profiles;
- Discuss the appropriate methods to verify the performance of the selected insulators, if required;

This simplified process is intended to be used when comparable operational experience from existing d.c. system is incomplete or not available.

The simplified design approach might result in a solution that exceeds the physical constraints of the project. More refined approaches for such cases, e.g. using a statistical approach, are given in the CIGRE d.c. guidelines [1]. In extreme cases, e.g. for exceptionally severe site conditions, alternative solutions such as changing the line route, relocation of converter stations or using an indoor d.c. yard may need to be considered.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC TS 61245, *Artificial pollution tests on high-voltage ceramic and glass insulators to be used on d.c. systems*

IEC TS 60815-1:2008, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 1: Definitions, information and general principles*

IEC TS 60815-2, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 2: Ceramic and glass insulators for a.c. systems*

IEC TS 60815-3, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 3: Polymer insulators for a.c. systems*

IEC TS 62073, *Guidance on the measurement of hydrophobicity of insulator surfaces*

### 3 Terms, definitions and abbreviated terms

#### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-471:2007 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

##### 3.1.1

#### **Unified Specific Creepage Distance**

##### **USCD**

creepage distance of an insulator divided by the maximum operating voltage across the insulator. It is generally expressed in mm/kV

Note 1 to entry: For d.c. the maximum operating voltage is the d.c. system voltage as defined in IEC 60071-5.

##### 3.1.2

#### **Reference d.c. Unified Specific Creepage Distance**

##### **RUSCD<sub>dc</sub>**

value of Unified Specific Creepage Distance for a d.c. system at a pollution site determined from ESDD and NSDD values corrected for NSDD, CUR, etc. according to this document

Note 1 to entry: This is generally expressed in mm/kV.

##### 3.1.3

#### **Contamination Uniformity Ratio**

##### **CUR**

ratio of the pollution deposit density on the lower surface of insulators to that of the upper surface

Note 1 to entry: Referred to as Pollution Uniformity Ratio (PUR) in some countries.

Note 2 to entry: This is referred to as Contamination Uniformity Ratio in some countries.

##### 3.1.4

#### **Hydrophobicity Transfer Material**

##### **HTM**

polymer materials which exhibit hydrophobicity and the capability to transfer hydrophobicity to the layer of pollution