
**Determination of resistance to intergranular
corrosion of stainless steels —**

Part 2:

Ferritic, austenitic and ferritic-austenitic
(duplex) stainless steels — Corrosion test
in media containing sulfuric acid

*Détermination de la résistance à la corrosion intergranulaire des aciers
inoxydables —*

*Partie 2: Aciers inoxydables ferritiques, austénitiques et austéno-ferritiques
(duplex) — Essais de corrosion en milieux contenant de l'acide sulfurique*



Contents	Page
1 Scope	1
2 Purpose of the test	1
2.1 Verification of the intrinsic resistance of the steel to intergranular corrosion	1
2.2 Inspection of the efficiency of the solution treatment	2
3 Sensitization treatment	2
3.1 Sensitization heat treatment	2
3.2 Sensitization by welding	2
4 Corrosion test	2
4.1 Principle	2
4.2 Test pieces	2
4.3 Preparation of test pieces	4
5 Apparatus	5
6 Test methods	5
6.1 Method A	5
6.2 Method B	5
6.3 Method C	6
6.4 Bend test	6
7 Evaluation	7
8 Test report	7
Annex A (informative) Examples of application	8
Annex B (informative) Comparison of commonly available national standards and this part of ISO 3651	9

This document is a preview generated by EVS

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3651-2 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 7, *Methods of testing (other than mechanical tests and chemical analysis)*.

This second edition cancels and replaces the first edition (ISO 3651-2:1976), which has been technically revised.

ISO 3651 consists of the following parts, under the general title *Determination of resistance to intergranular corrosion of stainless steels*:

- *Part 1: Austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in nitric acid medium by measurement of loss in mass (Huey test)*
- *Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid*

Annexes A and B of this part of ISO 3651 are for information only.

Introduction

The term "intergranular corrosion test" denotes the corrosion test carried out by means of preferential attack of the grain boundaries.

Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels may be subject to such an attack when they are held at a temperature between about 500 °C and 1 000 °C. This heat cycle, which may provoke sensitization to intergranular corrosion, may occur during hot-forming (forging, rolling) as the result of incorrect solution treatment or during a welding operation.

NOTE — In the field of application of this test, intergranular corrosion may be connected with the presence along the grain boundaries of a chromium-depleted region due to precipitation of chromium carbides, sigma phase or other intermetallic phases.

This document is a preview generated by EVS

Determination of resistance to intergranular corrosion of stainless steels —

Part 2:

Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid

1 Scope

This part of ISO 3651 specifies methods for the determination of the resistance to intergranular corrosion of ferritic, austenitic and ferritic-austenitic (duplex) stainless steels in media containing sulfuric acid. It also specifies the purposes which may be assigned to the test. The test methods included are:

- **method A:** the 16 % sulfuric acid/copper sulfate test (Monypenny Strauss test);
- **method B:** the 35 % sulfuric acid/copper sulfate test;
- **method C:** the 40 % sulfuric acid/ferric sulfate test.

The methods are applicable to stainless steels supplied in the form of cast, rolled or forged products and tubes and intended for use in a mildly oxidizing acid medium (for example, sulfuric acid, phosphoric acid).

Unless specified in the product standard, the method to be used, A, B or C, shall form the subject of an agreement between the interested parties.

Annex A gives examples of application of the three methods on stainless steels.

NOTE — It is important to note that the result of the corrosion test is only strictly valid for the corrosive medium used in the test. It constitutes a basis for estimating the resistance to intergranular corrosion but may not be used to check resistance to other forms of corrosion (general corrosion, pitting, stress corrosion, etc.). It is necessary for the user to adapt the specified corrosion test to the use which will be made of the alloy. These test should, in no case, be considered as an absolute criterion of the quality of the metal.

2 Purpose of the test

This intergranular corrosion test may have either of the purposes given in 2.1 and 2.2.

2.1 Verification of the intrinsic resistance of the steel to intergranular corrosion

This verification applies only to low carbon steels ($C \leq 0,03 \%$) and stabilized steels specified for resistance to intergranular corrosion. The metal is inspected after having undergone a heat treatment for sensitization which can be a heat treatment or welding for sensitization (see clause 3).