

---

---

**Corrosion of metals and alloys —  
Determination of dezincification  
resistance of copper alloys with zinc —**

**Part 2:  
Assessment criteria**

*Corrosion des métaux et alliages — Détermination de la résistance à  
la dézincification des alliages de cuivre avec le zinc —*

*Partie 2: Critères d'acceptation*



This document is a preview generated by EMS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
Foreword .....	iv
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	1
4 Assessment criteria .....	1
Bibliography .....	3

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

This first edition of ISO 6509-2 cancels and replaces ISO 6509:1981, which has been technically revised.

A list of all parts in the ISO 6509 series can be found on the ISO website.

# Corrosion of metals and alloys — Determination of dezincification resistance of copper alloys with zinc —

## Part 2: Assessment criteria

### 1 Scope

This document specifies assessment criteria and provides guidance related to the corrosion type dezincification for the selection of copper alloys with a mass fraction of zinc of more than 15 %, exposed to fresh, saline waters or drinking water. The assessment criteria are based on the exposure tests in ISO 6509-1.

The materials can be in the form of a semi-finished product or in the form of a final product (fittings, valves, etc.).

This document is not applicable to complex products like flow-meters or pump-parts. In addition, other properties of the material might need to be taken into account for the intended application. This document is not intended to validate dezincification in case of failure in the application.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8044, *Corrosion of metals and alloys — Basic terms and definitions*

ISO 6509-1, *Corrosion of metals and alloys — Determination of dezincification resistance of copper alloys with zinc — Part 1: Test method*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8044 and the following apply.

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1

##### **dezincification resistant copper alloy**

copper alloys with a mass fraction of zinc more than 15 % tested according to ISO 6509-1 and fulfilling the assessment criteria in this document

### 4 Assessment criteria

The assessment criteria given in [Table 1](#) refer to dezincification depth determination using the method given in ISO 6509-1. The minimum requirement for an alloy to be classified as dezincification resistant is that both the average and the maximum depth of dezincification shall be less than the values in [Table 1](#) or in national standard documents as appropriate.