

Magnetic materials - Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN IEC 60404-16:2018 sisaldab Euroopa standardi EN IEC 60404-16:2018 ingliskeelset teksti.	This Estonian standard EVS-EN IEC 60404-16:2018 consists of the English text of the European standard EN IEC 60404-16:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 06.07.2018.	Date of Availability of the European standard is 06.07.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 17.220.20, 29.030

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Magnetic materials - Part 16: Methods of measurement of the
magnetic properties of Fe-based amorphous strip by means of a
single sheet tester
(IEC 60404-16:2018)**

Matériaux magnétiques - Partie 16: Méthodes de mesure
des propriétés magnétiques des bandes en alliage amorphe
à base de fer à l'aide de l'essai sur tôle unique
(IEC 60404-16:2018)

Magnetische Werkstoffe - Teil 16 : Verfahren zur Messung
der magnetischen Eigenschaften von eisenbasiertem,
amorphem Band unter Verwendung eines
Tafelmessgerätes
(IEC 60404-16:2018)

This European Standard was approved by CENELEC on 2018-04-12. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of document 68/570/CDV, future edition 1 of IEC 60404-16, prepared by IEC/TC 68 "Magnetic alloys and steels" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 60404-16:2018.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2019-01-12
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2021-04-12

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 60404-16:2018 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following note has to be added for the standard indicated:

IEC 60404-6:2003 NOTE Harmonized as EN 60404-6:2003 (not modified).

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050-121	-	International Electrotechnical Vocabulary (IEV) - Part 121: Electromagnetism	-	-
IEC 60050-221	-	International Electrotechnical Vocabulary (IEV) - Chapter 221: Magnetic materials and components	-	-
IEC 60404-8-11	-	Magnetic materials - Part 8-11: Specifications for individual materials - Fe-based amorphous strip delivered in the semi-processed state	EN IEC 60404-8-11 -	

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 General principles	8
4.1 Principle of the method	8
4.2 Test specimen	9
4.3 Test apparatus.....	9
4.3.1 General	9
4.3.2 Yoke	10
4.3.3 Windings	10
4.3.4 Air flux compensation	11
4.3.5 Magnetic shielding	11
4.4 Power supply	11
4.5 Measuring instruments.....	12
4.6 Digital sampling technique	12
5 Measurement procedure	13
5.1 Principle of measurement.....	13
5.2 Preparation of measurement	13
5.3 Adjustment of power supply	14
6 Determination of characteristics.....	14
6.1 Determination of the magnetic polarization	14
6.2 Determination of the magnetic field strength	15
6.3 Determination of the specific total loss	15
6.4 Determination of the specific apparent power.....	16
7 Reproducibility.....	16
Annex A (informative) Requirements of the single sheet tester for Fe-based amorphous strip	17
A.1 Shape of test specimen.....	17
A.2 H coil method.....	17
A.3 Yoke	17
A.4 Wirings	17
A.5 Non-inductive precision resistor	18
A.6 Magnetic shielding	18
A.7 Method for checking the stability of the installed H coil from time to time	18
Annex B (informative) Digital sampling technique for the determination of the magnetic properties and numerical air flux compensation	19
B.1 General.....	19
B.2 Technical details and requirements.....	19
B.3 Calibration aspects	22
B.4 Numerical air flux compensation	22
Annex C (informative) Sinusoidal waveform control of the magnetic polarization by digital means	24
Bibliography.....	26

Figure 1 – Schematic diagram of the test apparatus.....	8
Figure 2 – Circuit of the wattmeter method with H coil mode	9
Figure 3 – Yoke dimensions.....	10
Figure 4 – Circuit of the wattmeter method with H coil mode adopting the digital sampling technique	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MAGNETIC MATERIALS –

Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-16 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this International Standard is based on the following documents:

CDV	Report on voting
68/570/CDV	68/583A/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60404 series, published under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

A method of measuring the magnetic properties of Fe-based amorphous strip is required to grade what is regarded as a promising material to reduce energy loss in transformer cores and, consequently, to reduce global warming.

Fe-based amorphous strip is produced by a rapidly-solidifying, direct-casting process. The strip is intended primarily for the construction of wound cores of distribution transformers for commercial power frequency (50 Hz and 60 Hz) applications.

After appropriate heat treatment, the strip exhibits a significantly lower value of specific total loss compared to grain-oriented electrical steel strip. It is associated with low hysteresis loss due to low magnetic anisotropy and low eddy current loss due to high resistivity and reduced thickness. However, significant deterioration can occur by applying stress on the strip due to the large magnetostriction and low magnetic anisotropy characteristics of the material.

Therefore, a method of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester (SST) is required, independent of IEC 60404-3 [1]¹, which is specified for electrical steel sheets.

The almost exclusively applied wattmeter method is used also in this standard. However, the widely used version with the determination of the magnetic field strength from the magnetizing current ("MC method") is not applicable to this kind of material, because the influence of the yokes on the loss measurement is significantly greater for the thinner and magnetically softer test specimen of this material. Thus, the wattmeter method with H coil mode ("H coil method") has been included for the magnetic field determination. International round robin tests of SST and Fe-based amorphous test specimens have been carried out, resulting in a suitable configuration of the SST for amorphous material. The single-yoke concept was adopted in order to avoid the effect of the impact of the upper yoke caused by the high magneto-elastic sensitivity of the material.

¹ Numbers in square brackets refer to the Bibliography.