
**Wear of implant materials — Polymer and
metal wear particles — Isolation and
characterization**

*Usure des matériaux d'implant — Particules d'usure des polymères et
des métaux — Isolation et caractérisation*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope.....	1
2 Terms and definitions	1
3 Principle, reagents and apparatus.....	1
3.1 Principle	1
3.2 Reagents	2
3.3 Apparatus.....	2
4 Methods of sampling and analysis of polymer and metal wear particles from tissue samples	3
4.1 Storage and preparation of samples	3
4.2 Procedure for polymer particle isolation	4
4.3 Procedure for metal particle isolation.....	5
4.4 Collection of particles.....	6
4.5 Particle size and shape characterization	7
4.6 Particle identification	8
5 Methods of sampling and analysis of polymer and metal particles from joint simulator lubricants	9
5.1 General	9
5.2 Procedure for polymer materials — For example UHMWPE and polyetheretherketone (PEEK).....	9
5.3 Procedure for metal particles.....	10
5.4 Procedure for ceramic particles	13
6 Test report.....	13
Bibliography.....	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17853 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 4, *Bone and joint replacements*.

This third edition cancels and replaces the second edition (ISO 17853:2010), of which it constitutes a minor revision.

This document is a preview generated by EVS

Introduction

The biological responses to wear particles contribute to the failure of joint implants through bone resorption and consequent implant loosening. A standardized method of particle retrieval from the tissues followed by particle characterization is necessary to ensure that the investigations of wear particle effects have a uniform approach. The characterization of the particles generated from implants in joint simulators also provides valuable information on the wear properties and performance of the implant being studied.

In the protocols included in this International Standard, for isolation and characterization of particles from both tissues or test fluids from joint simulators, the particles are isolated and then dispersed using filtration or embedding in resin for scanning electron microscopy (SEM) or transmission electron microscopy (TEM) analysis. An alternative protocol for isolation and characterization of metal particles from implants tested in joint simulators has recently been developed in which the particles are deposited on to wafers for SEM analysis, without filtration or embedding^[1]. At the time of publication of this International Standard, this alternative method has not been tested for isolation and characterization of particles from tissues and no direct comparison between the different methods is available. Therefore, the latter method has not been included in detail.

This document is a preview generated by EVS

Wear of implant materials — Polymer and metal wear particles — Isolation and characterization

1 Scope

This International Standard specifies methods for sampling wear particles generated by joint replacement implants in humans and in joint simulators. It specifies the apparatus, reagents and test methods to isolate and characterize both polymer and metal wear particles from samples of tissues excised from around the joint replacement implant, obtained at revision surgery or post mortem, and from samples of joint simulator test fluids. Some of these procedures could certainly be adapted for isolation and characterization of particles from human biological fluids (e.g. synovial fluid).

The methods given in this International Standard do not quantify the level of wear the implant produces; neither do they determine the amount of wear from any particular surface. This International Standard does not cover the biological effects of wear particles or provide a method for evaluation of biological safety.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

polymer wear particle

particle generated from the wear of polymeric components of an implant

2.2

metal wear particle

particle and particulate corrosion product generated from the wear of metal components of an implant

2.3

ceramic wear particle

particle generated from the wear of ceramic components of an implant

3 Principle, reagents and apparatus

3.1 Principle

Particles of polymeric and metal wear are isolated from tissue samples and simulator lubricants by digestion. The yield of each particle species is then purified by eliminating any remaining organic debris.

NOTE The methods involved in polymer and metal particle isolation are different and are described in 4.2 and 4.3, respectively.

The particles are collected, and are characterized and counted (where applicable) using scanning electron microscopy (SEM) or transmission electron microscopy (TEM).