

**KONSTRUKTSIOONI BETOONI KATSETAMINE. OSA 1:  
PUURSÜDAMIKUD. VÕTMINE, ÜLEVAATUS JA  
SURVEKATSE**

**Testing concrete in structures - Part 1: Cored specimens  
- Taking, examining and testing in compression**

**EESTI STANDARDI EESSÕNA****NATIONAL FOREWORD**

See Eesti standard EVS-EN 12504-1:2019 sisaldab Euroopa standardi EN 12504-1:2019 ja selle paranduse AC:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12504-1:2019 consists of the English text of the European standard EN 12504-1:2019 and its corrigendum AC:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.  Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 26.06.2019.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.  Date of Availability of the European standard is 26.06.2019.
Parandusega AC lisatud või muudetud teksti algus ja lõpp on tekstis tähistatud sümbolitega $\boxed{AC}$ $\langle AC \rangle$ .	The start and finish of text introduced or altered by corrigendum AC is indicated in the text by tags $\boxed{AC}$ $\langle AC \rangle$ .
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 91.100.30

**Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

**The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation**

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN 12504-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2019

ICS 91.100.30

Supersedes EN 12504-1:2009

English Version

## Testing concrete in structures - Part 1: Cored specimens - Taking, examining and testing in compression

Essais pour béton dans les structures - Partie 1 :  
Carottes - Prélèvement, examen et essais en  
compression

Prüfung von Beton in Bauwerken - Teil 1:  
Bohrkernproben - Herstellung, Untersuchung und  
Prüfung der Druckfestigkeit

This European Standard was approved by CEN on 29 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
<b>1 Scope</b> .....	<b>4</b>
<b>2 Normative references</b> .....	<b>4</b>
<b>3 Terms and definitions</b> .....	<b>4</b>
<b>4 Principle</b> .....	<b>4</b>
<b>5 Apparatus</b> .....	<b>4</b>
<b>6 Taking cores</b> .....	<b>5</b>
6.1 General.....	5
6.2 Location.....	5
6.3 Drilling.....	5
6.4 Length of cores.....	5
6.5 Marking and identification.....	5
<b>7 Examination</b> .....	<b>6</b>
7.1 Visual inspection.....	6
7.2 Measurements.....	6
<b>8 Preparation of cores</b> .....	<b>6</b>
8.1 General.....	6
8.2 Length/diameter ratios.....	7
8.3 Tolerances.....	7
<b>9 Compression test</b> .....	<b>7</b>
9.1 Storage.....	7
9.2 Testing.....	7
<b>10 Expression of results</b> .....	<b>7</b>
<b>11 Test report</b> .....	<b>8</b>
<b>12 Precision</b> .....	<b>8</b>
<b>Annex A The effect of aggregate size and core diameter on core specimen strength</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>10</b>

## European foreword

This document (EN 12504-1:2019) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by SN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12504-1:2009.

It is recognized good practice to include measurement of density prior to the determination of compressive strength, as a check on compaction of the concrete.

In drafting the standard consideration has been given to the results of the research programme, part funded by the EC under the Measurement and Testing Programme, contract MAT1-CT94-0043.

The standard includes simple guidance on the process of taking cores, but does not consider a sampling plan. It also provides procedures for visual examination and compressive strength testing, but not the interpretation of the results.

This standard is one of a series on testing concrete.

EN 12504, *Testing concrete in structures*, consists of the following parts:

- *Part 1: Cored specimens – Taking, examining and testing in compression;*
- *Part 2: Non-destructive testing – Determination of rebound number;*
- *Part 3: Determination of pull-out force;*
- *Part 4: Determination of ultrasonic pulse velocity.*

This edition includes the following significant technical changes with respect to EN 12504-1:2009:

- a) editorial revisions;
- b) measurement of core dimensions;
- c) core samples to be tested in an *in situ* or wet conditions;
- d) procedures for preparation of specimens prior to testing.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This document specifies a method for taking cores from hardened concrete, their examination, preparation for testing and determination of compressive strength.

This document does not give guidance on the decision to drill cores or on the locations for drilling.

This document does not provide procedures for interpreting the core strength results.

For the assessment of in situ compressive strength in structures and precast concrete components, EN 13791 may be used.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12390-1, *Testing hardened concrete — Part 1: Shape, dimensions and other requirements for specimens and moulds*

EN 12390-3:2019, *Testing hardened concrete — Part 3: Compressive strength of test specimens*

EN 12390-4, *Testing hardened concrete — Part 4: Compressive strength — Specification for testing machines*

EN 12390-7, *Testing hardened concrete — Part 7: Density of hardened concrete*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Principle

Cores extracted using a core drill are carefully examined, prepared by grinding or capping and tested in compression using standard procedures.

## 5 Apparatus

**5.1 Core drill**, equipment capable of extracting cores from the hardened concrete to the dimensions set out in 6.4 to the tolerances set out in 8.3.

**5.2 Compression testing machine**, conforming to EN 12390-4 and related to the size of specimens and their expected failure load.

NOTE Concrete compression testing machines conforming to EN 12390-4 may need to be adapted to test cores (see the Foreword of EN 12390-4).

**5.3 Balance or scale**, capable of determining the mass of the core, as tested, to a maximum permissible error of 0,1 % of the mass.