

This document is a preview generated by EVS

Structural timber - Determination of characteristic values of mechanical properties and density

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 384:2016+A1:2018 sisaldab Euroopa standardi EN 384:2016+A1:2018 ingliskeelset teksti.	This Estonian standard EVS-EN 384:2016+A1:2018 consists of the English text of the European standard EN 384:2016+A1:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 21.11.2018.	Date of Availability of the European standard is 21.11.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 79.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 384:2016+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2018

ICS 79.040

Supersedes EN 384:2016

English Version

Structural timber - Determination of characteristic values of mechanical properties and density

Bois de structure - Détermination des valeurs
caractéristiques des propriétés mécaniques et de la
masse volumique

Bauholz für tragende Zwecke - Bestimmung
charakteristischer Werte für mechanische
Eigenschaften und Rohdichte

This European Standard was approved by CEN on 30 January 2016 and includes Amendment 1 approved by CEN on 8 October 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Symbols and abbreviations	6
5 Mechanical properties determined from full-size specimens	8
5.1 Sampling	8
5.2 Testing	8
5.3 Reference conditions	8
5.3.1 Moisture content	8
5.3.2 Bending strength	8
5.3.3 Tension strength	8
5.3.4 Density	8
5.4 Adjustment factors	9
5.4.1 General	9
5.4.2 Moisture content	9
5.4.3 Timber size and test length	9
5.4.4 Modulus of elasticity	10
5.4.5 Other adjustments	10
5.5 Analysis of data	10
5.5.1 Sub-sample analysis	10
5.5.2 Characteristic values	11
6 Bending strength and modulus of elasticity determined from small, clear hardwood specimens	13
7 Other mechanical properties for hardwoods and softwoods	13
8 Report	15
Annex A (normative) Requirements for reports for visual grading assignment	16
Bibliography	19

European foreword

This document (EN 384:2016+A1:2018) has been prepared by Technical Committee CEN/TC 124 “Timber structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2019, and conflicting national standards shall be withdrawn at the latest by May 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 2018-10-08.

This document supersedes A1 EN 384:2016 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

A1 Deleted text A1

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Structural design codes can only function effectively if standard methods of determining the mechanical and physical properties exist. The aim of the procedures given in this standard is to derive characteristic values that are comparable in terms of the populations they represent. The standard permits the use of as much existing test data as possible from various sampling and testing techniques.

Where methods are given to permit characteristic values to be determined from a less than ideal amount of structural size test data, reduction factors to reflect a lower degree of confidence are employed.

This document is a preview generated by EVS

1 Scope

This European Standard gives a method for determining characteristic values of mechanical properties and density, for defined populations of visual grades and/or strength classes of machine graded structural timber. Additionally it covers the stages of sampling, testing, analysis and presentation of the data.

The standard provides methods to derive strength, stiffness and density properties for structural timber from tests with defect-free specimen.

The values determined in accordance with this standard for mechanical properties and density are suitable for assigning grades and species to the strength classes of EN 338.

NOTE 1 For assigning grades and species to the strength classes in EN 338 only three properties, i.e. bending or tension strength, modulus of elasticity parallel to grain in bending or tension and density need to be determined from test data, other properties can be calculated according to Table 2.

NOTE 2 EN 1912 gives examples of established visual grades assigned to strength classes.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 338, *Structural timber — Strength classes*

EN 408, *Timber structures — Structural timber and glued laminated timber — Determination of some physical and mechanical properties*

EN 13183-2, *Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method*

EN 13183-3, *Moisture content of a piece of sawn timber — Part 3: Estimation by capacitance method*

EN 14081-1:2016, *Timber structures — Strength graded structural timber with rectangular cross section — Part 1: General requirements*

EN 14081-2, *Timber structures — Strength graded structural timber with rectangular cross section — Part 2: Machine grading; additional requirements for initial type testing*

EN 14081-3, *Timber structures — Strength graded structural timber with rectangular cross section — Part 3: Machine grading; additional requirements for factory production control*

EN 14358:2016, *Timber structures — Calculation and verification of characteristic values*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

characteristic value

representative value of a material property used for design, which is based either on 5-percentile values (e.g. strength properties and density) or mean values (e.g. modulus of elasticity)