



INTERNATIONAL STANDARD ISO 14419:1998
TECHNICAL CORRIGENDUM 1

Published 2004-09-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Oil repellency — Hydrocarbon resistance test

TECHNICAL CORRIGENDUM 1

Textiles — Oléofugation — Essai de résistance aux hydrocarbures

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 14419:1998 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee 2, *Cleansing, finishing and water resistance tests*

Page 2, Clause 6

Add to the end of the first paragraph:

“All reagents and standard test liquids have a maximum shelf life of 3 years.”

Page 2, Table 1

Change 0,014 8 (fourth column, last line), to 0,019 8.

Page 3, 7.2

Delete existing text for subclause and replace with:

“**White textile blotting paper**, textile blotting paper is an absorbent textile blotting paper with a thickness of 0,71 mm and an approximate grammage of $(385 \pm 4,5)$ g/m² and absorbent capacity of (200 ± 30) %¹.”