

INTERNATIONAL  
STANDARD

**ISO**  
**10960**

First edition  
1994-12-01

---

---

**Rubber and plastics hoses — Assessment  
of ozone resistance under dynamic  
conditions**

*Tuyaux en caoutchouc et en plastique — Évaluation de la résistance à  
l'ozone dans des conditions dynamiques*



Reference number  
ISO 10960:1994(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10960 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This document is a preview generated by EVS

# Rubber and plastics hoses — Assessment of ozone resistance under dynamic conditions

## 1 Scope

This International Standard specifies a method of assessing the resistance of hoses to the deleterious effects of atmospheric ozone under dynamic conditions. It is applicable to hoses with bore diameters up to and including 25 mm.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 471:—<sup>1)</sup>, *Rubber — Times, temperatures and humidities for conditioning and testing*.

ISO 1431-1:1989, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static strain test*.

## 3 Principle

The cover of a hose in a crescent position during reverse bending is exposed to ozone and examined periodically for cracking.

## 4 Apparatus

**4.1 Ozone cabinet**, with apparatus for generating ozone and monitoring and controlling the ozone concentration as described in ISO 1431-1.

**4.2 Test piece holder**, as shown in figure 1, with means of carrying out flexing at the required frequency.

Details given in ISO 1431-1:1989, subclause 5.6, shall be followed.

All apparatus placed in the test cabinet shall be made from materials which do not absorb or decompose ozone.

## 5 Test pieces

### 5.1 Type of test piece

The test piece shall consist of a hose sample with a free length  $L$  calculated from the formula

$$L = 20 \times d$$

where  $d$  is the outside diameter of the hose under test.

### 5.2 Number of test pieces

Two test pieces shall be tested.

## 6 Conditioning of test pieces

No test shall be carried out within 24 h of manufacture.

1) To be published. (Revision of ISO 471:1983 and ISO 1826:1981).