
**Plastics — Determination of the
ultimate aerobic biodegradability
of plastic materials in soil by
measuring the oxygen demand in
a respirometer or the amount of
carbon dioxide evolved**

*Plastiques — Détermination de la biodégradabilité aérobie ultime des
matériaux plastiques dans le sol par mesure de la demande en oxygène
dans un respiromètre ou de la teneur en dioxyde de carbone libéré*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	3
5 Test environment.....	4
6 Materials.....	4
7 Apparatus.....	4
8 Procedure.....	4
8.1 Preparation of the test material.....	4
8.2 Preparation of the reference material.....	5
8.3 Preparation of the test soil.....	5
8.3.1 Collection and sieving of soil.....	5
8.3.2 Preparation of standard soil.....	6
8.3.3 Measurement of soil characteristics.....	7
8.3.4 Adjustment of the water content and the pH of the soil.....	7
8.3.5 Handling and storage of the soil.....	7
8.4 Start-up and execution of the test.....	7
9 Calculation and expression of results.....	9
9.1 Calculation.....	9
9.1.1 Percentage biodegradation from oxygen consumption values.....	9
9.1.2 Percentage biodegradation from carbon dioxide evolved.....	9
9.2 Expression and interpretation of results.....	10
10 Validity of results.....	10
11 Test report.....	10
Annex A (informative) Principle of a manometric respirometer (example).....	12
Annex B (informative) Example of a system for measuring the amount of carbon dioxide evolved.....	13
Annex C (informative) Examples of methods for the determination of evolved carbon dioxide.....	14
Annex D (informative) Theoretical oxygen demand (ThOD).....	16
Annex E (informative) Example of a determination of the amount and the molecular mass of water-insoluble polymer remaining at the end of a biodegradation test.....	17
Annex F (informative) Examples of long-term tests.....	18
Annex G (informative) Interlaboratory test.....	22
Bibliography.....	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

This third edition cancels and replaces the second edition (ISO 17556:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- a) the unit for BOD, COD and DIC has been corrected (see [Clause 3](#));
- b) the formula for calculating the percent biodegradation has been modified (see [9.1.1](#));
- c) the test period has been revised to two years at the longest (see [Clause 4](#));
- d) the number of replicates has been corrected to three (see [9.2](#)).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

A number of plastic materials and products have been designed for applications ending up in or on soil. They have been developed for applications where biodegradation is beneficial from a technical, environmental, social or economic standpoint. Examples can be found in agriculture (e.g. mulching film), horticulture (e.g. twines and clips, flower pots, pins), funeral items (e.g. body bags), recreation (e.g. plastic “clay” pigeons for shooting, hunting cartridges), etc. In many cases, recovery and/or recycling of these plastic items is either difficult or not economically viable. Various types of biodegradable plastics have been developed which have been designed to biodegrade and disappear in situ at the end of their useful life. Several International Standards specify test methods for determining the ultimate aerobic or anaerobic biodegradation of plastic materials in aqueous or compost conditions. Considering the use and disposal of biodegradable plastics, it is important to establish a test method to determine the ultimate aerobic biodegradation of such plastic materials in soil.

Plastics — Determination of the ultimate aerobic biodegradability of plastic materials in soil by measuring the oxygen demand in a respirometer or the amount of carbon dioxide evolved

WARNING — Appropriate precautions should be taken when handling soil because it might contain potentially pathogenic organisms. Toxic test compounds and those whose properties are unknown should be handled with care.

1 Scope

This document specifies a method for determining the ultimate aerobic biodegradability of plastic materials in soil by measuring the oxygen demand in a closed respirometer or the amount of carbon dioxide evolved. The method is designed to yield an optimum degree of biodegradation by adjusting the humidity of the test soil.

If a non-adapted soil is used as an inoculum, the test simulates the biodegradation processes which take place in a natural environment; if a pre-exposed soil is used, the method can be used to investigate the potential biodegradability of a test material.

This method applies to the following materials:

- natural and/or synthetic polymers, copolymers or mixtures of these;
- plastic materials which contain additives such as plasticizers or colorants;
- water-soluble polymers.

It does not necessarily apply to materials which, under the test conditions, inhibit the activity of the microorganisms present in the soil. Inhibitory effects can be measured using an inhibition control or by another suitable method. If the test material inhibits the microorganisms in the soil, a lower test material concentration, another type of soil or a pre-exposed soil can be used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10390, *Soil quality — Determination of pH*

ISO 10694, *Soil quality — Determination of organic and total carbon after dry combustion (elementary analysis)*

ISO 11274, *Soil quality — Determination of the water-retention characteristic — Laboratory methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>