



**International  
Standard**

**ISO 17544**

**Carbonaceous materials used in  
the production of aluminium —  
Cold and tepid ramming pastes —  
Determination of rammability of  
unbaked pastes**

*Produits carbonés utilisés pour la production de l'aluminium —  
Pâtes de brasquage froides et tièdes — Détermination de  
l'aptitude au brasquage des pâtes non cuites*

**Second edition  
2024-08**

This document is a preview generated by EMS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Symbols</b> .....	<b>1</b>
<b>5 Principle</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Sampling</b> .....	<b>2</b>
<b>8 Procedure</b> .....	<b>3</b>
<b>9 Expression of results</b> .....	<b>3</b>
9.1 Calculation of the density.....	3
9.2 Interpretation of the curve.....	3
9.3 Determination of $N_2$ .....	3
9.3.1 Fitting the data to a Weibull function.....	3
9.3.2 Calculation of $N_2$ .....	4
9.4 Determination of $\rho(50)/\rho(100)$ .....	4
<b>10 Precision</b> .....	<b>4</b>
<b>11 Test report</b> .....	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

This second edition cancels and replaces the first edition (ISO 17544:2004), which has been technically revised.

The main changes are as follows:

- the mass of the falling weight and the ramming rate have been corrected.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The bottom of aluminium electrolysis cells is lined with cathode blocks that are sealed with a ramming paste to avoid any leakage. When lining a cell, the green paste is directly rammed between the cathode blocks and baked in situ during the start-up of the pot by the process heat. The quality of the paste is of primary importance as to ensure long operation without disturbance.

This document is a preview generated by EVS



# Carbonaceous materials used in the production of aluminium — Cold and tepid ramming pastes — Determination of rammability of unbaked pastes

## 1 Scope

This document describes a method of producing a compaction curve indicating the rammability of carbonaceous ramming pastes used to line cathodes utilized in the production of aluminium.

Determination of the rammability enables a ramming paste with the optimum density to be selected.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

ISO 14422, *Carbonaceous materials used in the production of aluminium — Cold-ramming pastes — Methods of sampling*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Symbols

$h$	measured height of test specimen, in cm
$m$	mass of paste placed in cylinder, in g
$N$	number of impacts
$N_2$	minimum value of second derivative of $\rho(N)$
$r$	inner radius of rammer cylinder, in cm
$\alpha$	scaling or normalization parameter describing the steepness of the compaction curve (which decreases as $\alpha$ increases)
$\gamma$	location parameter which shifts the origin of the distribution
$\rho_{\max}$	maximum value of density, in $\text{g}\cdot\text{cm}^{-3}$