



**International
Standard**

ISO 16834

**Welding consumables — Wire
electrodes, wires, rods and deposits
for gas shielded arc welding of high
strength steels — Classification**

*Produits consommables pour le soudage — Fils-électrodes, fils,
baguettes et dépôts pour le soudage à l'arc sous flux gazeux des
aciers à haute résistance — Classification*

**Third edition
2025-02**

This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
4.1 General.....	2
4.2 Classification systems.....	2
5 Symbols and requirements	3
5.1 Symbols for the product/process.....	3
5.2 Symbols for strength and elongation properties of all-weld metal.....	3
5.2.1 Classification by yield strength and 47 J impact energy – System A.....	3
5.2.2 Classification by tensile strength and 27 J impact energy – System B.....	3
5.3 Symbol for impact properties of all-weld metal.....	3
5.3.1 Classification by yield strength and 47 J impact energy – System A.....	3
5.3.2 Classification by tensile strength and 27 J impact energy – System B.....	4
5.4 Symbol for shielding gas.....	4
5.5 Symbol for the chemical composition of wire electrodes, wires and rods.....	5
5.6 Symbol for condition of post-weld heat treatment.....	5
5.6.1 Classification by yield strength and 47 J impact energy – System A.....	5
5.6.2 Classification by tensile strength and 27 J impact energy – System B.....	5
6 Mechanical tests	10
7 Preheating and interpass temperatures	10
8 Welding conditions and pass sequence	10
8.1 General.....	10
8.2 Post-weld heat-treated condition.....	11
8.2.1 Classification by yield strength and 47 J impact energy – System A.....	11
8.2.2 Classification by tensile strength and 27 J impact energy – System B.....	11
9 Chemical analysis	11
10 Rounding procedure	11
11 Retest	12
12 Technical delivery conditions	12
13 Examples of designation	12
13.1 General.....	12
13.2 Example 1 – Classification by yield strength and 47 J impact energy – System A.....	12
13.3 Example 2 – Classification by tensile strength and 27 J impact energy – System B.....	13
13.4 Example 3 – Classification by yield strength and 47 J impact energy – System A.....	13
13.5 Example 4 – Classification by tensile strength and 27 J impact energy – System B.....	13
13.6 Example 5 – Classification by yield strength and 47 J impact energy – System A.....	14
13.7 Example 6 – Classification by tensile strength and 27 J impact energy – System B.....	14
Annex A (informative) Description of composition designations for electrodes in the classification system based upon tensile strength and average impact energy of 27 J – System B	16
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 16834:2012), which has been technically revised.

The main changes are as follows:

- document has been reformatted in single column showing System A and System B in tables and separate clauses and subclauses, some which are new;
- In [Clause 4](#), clarification that System A and System B are independent of each other and can produce different results;
- [Table 2](#) – addition of a new system A symbol 96 for strength and elongation properties of all weld metal;
- [Table 3](#) - addition of new symbols 7 and 8 for impact properties of all-weld metal;
- [Table 4](#) – some classifications have been revised and new classifications, N2M31, N2CM2, N3CM2, N4CM3, N6C1M41 have been added, and footnotes have been revised;
- [Tables 5, 7 and 8](#) – content has been added to the table and has been revised;
- [Clause 13](#) has been updated to reflect changes.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

Introduction

This document recognizes that there are two somewhat different approaches in the global market to classifying a given wire electrode, wire, rod or deposit, and allows for either or both to be used to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this document.

The classification in accordance with system A was originally based on EN 12534:1999 which has been withdrawn and replaced by this document. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim. Future revisions will aim to merge the two systems into a single classification system.

This document provides a classification for the designation of wire electrodes, wires, rods and deposits in terms of their chemical composition and, where required, in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield to tensile strength of weld metal is generally higher than that of the parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Thus, where the application requires matching tensile strength, selection of the consumable should be made by reference to [Table 2](#) System A or System B, as appropriate.

Welding consumables — Wire electrodes, wires, rods and deposits for gas shielded arc welding of high strength steels — Classification

1 Scope

This document specifies requirements for classification of wire electrodes, wires, rods and all-weld metal deposits in the as-welded condition and in the post-weld heat-treated (PWHT) condition for gas shielded metal arc welding and tungsten inert-gas welding of high-strength steels with a minimum yield strength greater than 500 MPa, or a minimum tensile strength greater than 570 MPa. One wire electrode can be tested and classified with different shielding gases.

This document is a combined specification providing for classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- a) Clauses, subclauses and tables which carry the suffix “System A” are applicable only to wire electrodes, wires, rods and deposits classified according to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal under this document.
- b) Clauses, subclauses and tables which carry the suffix “System B” are applicable only to wire electrodes, wires, rods and deposits classified according to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal under this document.
- c) Clauses, subclauses and tables which do not have either the suffix “System A” or “System B” are applicable to all wire electrodes, wires, rods and deposits classified under this document.

[Annex A](#) gives information on the description of composition designations for electrodes in the classification system based upon tensile strength and average impact energy of 27 J – System B.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 13916, *Welding — Measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175:2008, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2020, *Welding consumables — Test methods — Part 1: Preparation of all-weld metal test pieces and specimens in steel, nickel and nickel alloys*

ISO 80000-1:2022, *Quantities and units — Part 1: General*