

Plastics - Differential scanning calorimetry (DSC) -
Part 6: Determination of oxidation induction time
(isothermal OIT) and oxidation induction temperature
(dynamic OIT) (ISO 11357-6:2025)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 11357-6:2025 sisaldab Euroopa standardi EN ISO 11357-6:2025 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 18.06.2025.</p> <p>Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 11357-6:2025 consists of the English text of the European standard EN ISO 11357-6:2025.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 18.06.2025.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 11357-6

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2025

ICS 83.080.01

Supersedes EN ISO 11357-6:2018

English Version

Plastics - Differential scanning calorimetry (DSC) - Part 6:
Determination of oxidation induction time (isothermal
OIT) and oxidation induction temperature (dynamic OIT)
(ISO 11357-6:2025)

Plastiques - Analyse calorimétrique différentielle (DSC)
- Partie 6: Détermination du temps d'induction à
l'oxydation (OIT isotherme) et de la température
d'induction à l'oxydation (OIT dynamique) (ISO 11357-
6:2025)

Kunststoffe - Dynamische Differenzkalorimetrie (DSC)
- Teil 6: Bestimmung der Oxidations-Induktionszeit
(isothermische OIT) und Oxidations-
Induktionstemperatur (dynamische OIT) (ISO 11357-
6:2025)

This European Standard was approved by CEN on 16 June 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 11357-6:2025) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2025, and conflicting national standards shall be withdrawn at the latest by December 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11357-6:2018.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 11357-6:2025 has been approved by CEN as EN ISO 11357-6:2025 without any modification.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 General.....	2
4.2 Oxidation induction time (isothermal OIT).....	2
4.3 Oxidation induction temperature (dynamic OIT).....	2
5 Apparatus and materials	2
5.1 General.....	2
5.2 DSC instrument.....	3
5.3 Crucibles.....	3
5.4 Flowmeter.....	3
5.5 Oxygen.....	3
5.6 Air.....	3
5.7 Nitrogen.....	3
5.8 Gas-selector switch and regulators.....	3
6 Test specimens	4
6.1 General.....	4
6.2 Specimens from compression-moulded plates.....	4
6.3 Specimens from injection-moulded plates or melt flow extrudates.....	4
6.4 Specimens from finished parts.....	4
7 Test conditions and specimen conditioning	5
8 Calibration	5
8.1 Oxidation induction time (isothermal OIT).....	5
8.1.1 General.....	5
8.1.2 Dynamic temperature calibration.....	5
8.1.3 Isothermal stepwise temperature calibration.....	5
8.2 Oxidation induction temperature (dynamic OIT).....	5
9 Procedure	6
9.1 Setting up the instrument.....	6
9.2 Loading the test specimen into the crucible.....	6
9.3 Insertion of crucibles.....	6
9.4 Nitrogen, air and oxygen flow.....	6
9.5 Sensitivity adjustment.....	6
9.6 Performance of measurement.....	6
9.6.1 Oxidation induction time (isothermal OIT).....	6
9.6.2 Oxidation induction temperature (dynamic OIT).....	7
9.7 Cleaning.....	8
10 Expression of results	8
11 Precision and bias	10
12 Test report	10
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 11357-6:2018), which has been technically revised.

The main changes are as follows:

- the isothermal stepwise temperature calibration has been added for isothermal OIT.

A list of all parts in the ISO 11357 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The measurement of oxidation induction time or temperature described in this document provides a tool to assess the conformity of the material tested to a given formulation of plastics compounds. However, it is not intended to provide the concentration of antioxidant. Different antioxidants can have different oxidation induction times or temperatures. Due to interaction of the antioxidant with other substances in the formulation, different oxidation induction times or temperatures can result even with products having the same type and concentration of antioxidant.

This document is a preview generated by EVS

Plastics — Differential scanning calorimetry (DSC) —

Part 6:

Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)

1 Scope

This document specifies methods for the determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) of polymeric materials by means of differential scanning calorimetry (DSC). It is applicable to polyolefin resins that are in a fully stabilized or compounded form, either as raw materials or finished products. It can be applicable to other plastics.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 17855-2, *Plastics — Polyethylene (PE) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

ISO 19069-2, *Plastics — Polypropylene (PP) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

ISO 21302-2, *Plastics — Polybutene-1 (PB-1) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 11357-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

oxidation induction time isothermal OIT

relative measure of a stabilized material's resistance to oxidative decomposition, determined by the calorimetric measurement of the time interval to the onset of exothermic oxidation of the material at a specified temperature in an oxygen or air atmosphere, under atmospheric pressure

Note 1 to entry: It is expressed in minutes (min).