

**Plastics - Determination of flexural properties
(ISO 178:2010)**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 178:2010 sisaldab Euroopa standardi EN ISO 178:2010 ingliskeelset teksti.</p> <p>Standard on kinnitatud Eesti Standardikeskuse 31.12.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.12.2010.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 178:2010 consists of the English text of the European standard EN ISO 178:2010.</p> <p>This standard is ratified with the order of Estonian Centre for Standardisation dated 31.12.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p> <p>Date of Availability of the European standard text 15.12.2010.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

ICS 83.080.01

Standardite reprodutseerimis- ja levitamisoigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

English Version

Plastics - Determination of flexural properties (ISO 178:2010)

Plastiques - Détermination des propriétés en flexion (ISO
178:2010)Kunststoffe - Bestimmung der Biegeeigenschaften (ISO
178:2010)

This European Standard was approved by CEN on 14 December 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 178:2010) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2011, and conflicting national standards shall be withdrawn at the latest by June 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 178:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 178:2010 has been approved by CEN as a EN ISO 178:2010 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Principle	5
5 Test machine	5
5.1 General	5
5.2 Test speed	5
5.3 Supports and loading edge	6
5.4 Force- and deflection measuring systems	6
5.5 Equipment for measuring the width and thickness of the test specimens	7
6 Test specimens	8
6.1 Shape and dimensions	8
6.2 Anisotropic materials	9
6.3 Preparation of test specimens	9
6.4 Specimen inspection	10
6.5 Number of test specimens	10
7 Atmosphere for conditioning and testing	10
8 Procedure	10
9 Calculation and expression of results	13
9.1 Flexural stress	13
9.2 Flexural strain	13
9.3 Flexural modulus	14
9.4 Statistical parameters	14
9.5 Significant figures	14
10 Precision	15
11 Test report	15
Annex A (informative) Precision statement	16
Annex B (informative) Influence of changes in test speed on the measured values of flexural properties	18
Bibliography	19

Plastics — Determination of flexural properties

1 Scope

1.1 This International Standard specifies a method for determining the flexural properties of rigid (see 3.12) and semi-rigid plastics under defined conditions. A standard test specimen is defined, but parameters are included for alternative specimen sizes for use where appropriate. A range of test speeds is included.

1.2 The method is used to investigate the flexural behaviour of the test specimens and to determine the flexural strength, flexural modulus and other aspects of the flexural stress/strain relationship under the conditions defined. It applies to a freely supported beam, loaded at midspan (three-point loading test).

1.3 The method is suitable for use with the following range of materials:

- thermoplastic moulding, extrusion and casting materials, including filled and reinforced compounds in addition to unfilled types; rigid thermoplastics sheets;
- thermosetting moulding materials, including filled and reinforced compounds; thermosetting sheets.

In agreement with ISO 10350-1^[5] and ISO 10350-2^[6], this International Standard applies to fibre-reinforced compounds with fibre lengths $\leq 7,5$ mm prior to processing. For long-fibre-reinforced materials (laminates) with fibre lengths $> 7,5$ mm, see ISO 14125^[7].

The method is not normally suitable for use with rigid cellular materials or sandwich structures containing cellular material. In such cases, ISO 1209-1^[3] and/or ISO 1209-2^[4] can be used.

NOTE For certain types of textile-fibre-reinforced plastic, a four-point bending test is preferred. This is described in ISO 14125.

1.4 The method is performed using specimens which may be either moulded to the specified dimensions, machined from the central section of a standard multipurpose test specimen (see ISO 20753) or machined from finished or semi-finished products, such as mouldings, laminates or extruded or cast sheet.

1.5 The method specifies the preferred dimensions for the test specimen. Tests which are carried out on specimens of different dimensions, or on specimens which are prepared under different conditions, can produce results which are not comparable. Other factors, such as the test speed and the conditioning of the specimens, can also influence the results.

NOTE Especially for semi-crystalline polymers, the thickness of the oriented skin layer, which is dependent on the moulding conditions, also affects the flexural properties.

1.6 The method is not suitable for the determination of design parameters but can be used in materials testing and as a quality control test.

1.7 For materials exhibiting non-linear stress/strain behaviour, the flexural properties are only nominal. The equations given have been derived assuming linear elastic behaviour and are valid for deflections of the specimen that are small compared to its thickness. With the preferred specimen (which measures 80 mm \times 10 mm \times 4 mm) at the conventional flexural strain of 3,5 % and a span-to-thickness ratio, L/h , of 16, the deflection is $1,5h$. Flexural tests are more appropriate for stiff and brittle materials showing small deflections at break than for very soft and ductile ones.

1.8 Contrary to the previous editions of this International Standard, this edition specifies two methods, method A and method B. Method A is identical to the method in previous editions of this International Standard, i.e. it uses a strain rate of 1 %/min throughout the test. Method B uses two different strain rates: 1 %/min for the determination of the flexural modulus and 5 %/min or 50 %/min, depending on the ductility of the material, for the determination of the remainder of the flexural stress-strain curve.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1:1996, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometers used in uniaxial testing*

ISO 10724-1, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles, and moulding of multipurpose test specimens*

ISO 16012, *Plastics — Determination of linear dimensions of test specimens*

ISO 20753, *Plastics — Test specimens*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 test speed

v
rate of relative movement between the specimen supports and the loading edge

NOTE It is expressed in millimetres per minute (mm/min).

3.2 flexural stress

σ_f
nominal stress at the outer surface of the test specimen at midspan

NOTE It is calculated from the relationship given in 9.1, Equation (5), and is expressed in megapascals (MPa).