
**Timber structures — Joints made with
mechanical fasteners — Quasi-static
reversed-cyclic test method**

*Structures en bois — Joints réalisés avec des connecteurs
mécaniques — Méthode d'essai cyclique réversible quasi statique*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Symbols and definitions	1
4 Test specimens	2
4.1 Conditioning	2
4.2 Form and dimension	2
4.3 Sampling	2
4.4 Number of replicates	2
5 Apparatus	2
6 Test procedure	2
6.1 Properties from static (monotonic) tests	2
6.2 Cyclic displacement schedule	3
7 Test results	5
7.1 Hysteresis data	5
7.2 Envelope curves	5
7.3 Joint properties	5
8 Test report	5
Annex A (informative) Additional information	6
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16670 was prepared by Technical Committee ISO/TC 165, *Timber structure*.

This document is a preview generated by EVS

Introduction

Evaluation of the structural performance of joints under reversed-cyclic loading has become a requirement in seismic design. The objective of this International Standard is to provide a cyclic test procedure as a basis for the development of characteristics of joints for use in seismic design. The cyclic displacement schedule was developed in consultation with a group of international experts with the intention that the cyclic displacement schedule shall produce

- a) data that sufficiently describes the elastic and inelastic properties of the joint, and
- b) representative demands imposed on joints by earthquakes.

Supplementary information is given in Annex A to provide the rationale behind the cyclic displacement schedule, recommendations for cases for which a modified schedule would be more appropriate, and typical test results obtained on a joint by following this cyclic displacement schedule.

This document is a preview generated by EVS

Timber structures — Joints made with mechanical fasteners — Quasi-static reversed-cyclic test method

1 Scope

This International Standard is intended to provide a cyclic test method as a basis for the derivation of parameters which are required in seismic design of timber structures. The method includes procedures to develop the envelope curves (backbone or skeleton curves; an example is given in Clause A.5.) for joints subjected to a cyclic displacement schedule which produces representative demands imposed on the joints by earthquakes. It does not include criteria for parameters which are, at times, stipulated in national standards or building codes.

This standard is intended for joints subjected to lateral load and is not applicable to joints subjected to withdrawal forces.

This International Standard is applicable to joints made with mechanical fasteners used in timber structures loaded under seismic action.

NOTE 1 In the context of this Standard, the term "joint" means "connection" in present-day North-American English.

NOTE 2 It is recognized that, for some special types of joints, modification of the test method may be necessary provided the test objectives in this clause and the principles in Clause 6 are achieved. See Clause A.2 for details.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 3131, *Wood — Determination of density for physical and mechanical tests*

ISO 8970, *Timber structures — Testing of joints made with mechanical fasteners — Requirements for wood density*

ISO 6891, *Timber structures — Joints made with mechanical fasteners — General principles for the determination of strength and deformation characteristics*

3 Symbols and definitions

F Applied load, in newtons, or newton-millimetres in the case of joint rotation

F_{\max} Maximum load, in newtons, or newton-millimetres in the case of joint rotation (as defined in Figure 1)

k Joint stiffness, in newtons per millimetre, or newton-millimetres per radian in the case of joint rotation

v Joint displacement, in millimetres, or radians in the case of joint rotation

v_u Ultimate joint displacement, in millimetres, or radians in the case of joint rotation (as defined in Figure 1)