
**Metallic materials — Brinell hardness
test —**

Part 1:
Test method

*Matériaux métalliques — Essai de dureté Brinell —
Partie 1: Méthode d'essai*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Principle.....	1
4 Symbols and abbreviated terms.....	1
5 Apparatus.....	3
6 Test piece.....	3
7 Procedure.....	4
8 Uncertainty of the results.....	6
9 Test report.....	6
Annex A (normative) Procedure for periodic checking of the testing machine by the user.....	8
Annex B (normative) Minimum thickness of the test piece in relation to the mean diameter of indentation.....	9
Annex C (informative) Uncertainty of the measured hardness values.....	11
Bibliography.....	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

This third edition cancels and replaces the second edition (ISO 6506-1:2005), which has been technically revised.

ISO 6506 consists of the following parts, under the general title *Metallic materials — Brinell hardness test*:

- *Part 1: Test method*
- *Part 2: Verification and calibration of testing machines*
- *Part 3: Calibration of reference blocks*
- *Part 4: Table of hardness values*

Metallic materials — Brinell hardness test —

Part 1: Test method

1 Scope

This part of ISO 6506 specifies the method for the Brinell hardness test for metallic materials. It is applicable to both fixed location and portable hardness testing machines.

For some specific materials and/or products, particular International Standards exist (e.g. ISO 4498) and make reference to this International Standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4498, *Sintered metal materials, excluding hardmetals — Determination of apparent hardness and microhardness*

ISO 6506-2:2014, *Metallic materials — Brinell hardness test — Part 2: Verification and calibration of testing machines*

ISO 6506-3:2014, *Metallic materials — Brinell hardness test — Part 3: Calibration of reference blocks*

ISO 6506-4, *Metallic materials — Brinell hardness test — Part 4: Table of hardness values*

3 Principle

An indenter (tungsten carbide composite ball with diameter, D) is forced into the surface of a test piece and, after removal of the force, F , the diameter of the indentation, d , left in the surface is measured.

The Brinell hardness is proportional to the quotient obtained by dividing the test force by the curved surface area of the indentation. The indentation is assumed to take the shape of the unloaded ball indenter, and its surface area is calculated from the mean indentation diameter and the ball diameter, using the formula given in [Table 1](#).

4 Symbols and abbreviated terms

4.1 See [Figure 1](#) and [Table 1](#).