

KONSTRUKTSIOONITERASEST KUUMVALTSITUD
TOOTED. OSA 4: TERMOMEHAANILISELT VALTSITUD
KEEVITATAVATE PEENTERATERASTE TEHNILISED
TARNETINGIMUSED

Hot rolled products of structural steels - Part 4:
Technical delivery conditions for thermomechanical
rolled weldable fine grain structural steels

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 10025-4:2019 sisaldab Euroopa standardi EN 10025-4:2019 ingliskeelset teksti.	This Estonian standard EVS-EN 10025-4:2019 consists of the English text of the European standard EN 10025-4:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 14.08.2019.	Date of Availability of the European standard is 14.08.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.140.10, 77.140.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 10025-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2019

ICS 77.140.10; 77.140.50

Supersedes EN 10025-4:2004

English Version

Hot rolled products of structural steels - Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels

Produits laminés à chaud en aciers de construction -
Partie 4 : Conditions techniques de livraison pour les
aciers de construction soudable à grains fins obtenus
par laminage thermomécanique

Warmgewalzte Erzeugnisse aus Baustählen - Teil 4:
Technische Lieferbedingungen für thermomechanisch
gewalzte schweißgeeignete Feinkornbaustähle

This European Standard was approved by CEN on 16 June 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	8
4 Classification and designation	8
4.1 Classification	8
4.1.1 Main quality classes	8
4.1.2 Grades and qualities	8
4.2 Designation	9
5 Information to be supplied by the purchaser	9
5.1 Mandatory information	9
5.2 Options	9
6 Manufacturing process	9
6.1 Steel making process	9
6.2 Deoxidation and grain structure	10
6.3 Delivery conditions	10
7 Requirements	10
7.1 General	10
7.2 Chemical composition	10
7.3 Mechanical properties	11
7.3.1 General	11
7.3.2 Impact properties	11
7.3.3 Improved deformation properties perpendicular to the surface	11
7.4 Technological properties	12
7.4.1 Weldability	12
7.4.2 Formability and flame straightening	12
7.4.3 Hot-dip zinc-coating	13
7.5 Surface properties	13
7.5.1 Strip	13
7.5.2 Plates and wide flats	13
7.5.3 Sections	13
7.5.4 Bars and rods	13
7.6 Internal soundness	13
7.7 Dimensions, tolerances on dimensions and shape, mass	14
8 Inspection	14
8.1 Type of inspection and inspection document	14
8.2 Content of inspection document	14
8.3 Tests to be carried out	15
9 Frequency of testing and preparation of samples and test pieces	15
9.1 Frequency of testing	15
9.1.1 Chemical analysis	15
9.1.2 Mechanical tests	15
9.2 Preparation of samples and test pieces	15
9.2.1 Selection and preparation of samples for chemical analysis	15
9.2.2 Location of samples and orientation of test pieces for mechanical tests	16

9.2.3	Preparation of test pieces for mechanical tests	16
9.3	Identification of samples and test pieces.....	17
10	Test methods.....	17
10.1	Chemical analysis	17
10.2	Mechanical tests.....	17
10.2.1	Tensile test.....	17
10.2.2	Impact test.....	17
10.3	Ultrasonic testing.....	18
10.4	Retests	18
11	Marking, labelling, packaging	18
12	Complaints	18
13	Options	19
Annex A (normative)	Location of samples and test pieces.....	25
Annex B (informative)	List of Options of EN 10025-2 to -6	28
Bibliography	30

European foreword

This document (EN 10025-4:2019) has been prepared by Technical Committee CEN/TC 459/SC 3 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2020 and conflicting national standards shall be withdrawn at the latest by February 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document will supersede EN 10025-4:2004

This document consists of the following parts, under the general title *Hot rolled products of structural steels*:

- *Part 1: General technical delivery conditions*
- *Part 2: Technical delivery conditions for non-alloy structural steels*
- *Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*
- *Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*
- *Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*
- *Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*

For a short transition period there will be a coexistence of EN 10025-1:2004 with EN 10025-2:2019 to EN 10025-6:2019, since the new EN 10025-1 has to fulfil the requirements of the CPR and will therefore be published later. For this short transition period up-to-the publication of the next edition of part 1 the following is to be taken into account for EN 10025-1:2004:

- a) all dated and undated references to EN 10025-1:2004 to EN 10025-6:2004 are unchanged to this version with following exception: In 9.2.2.1 the references are 8.3.1 and 8.3.2 instead of 8.4.1 and 8.4.2,
- b) Clauses 5, 12 and 13 of EN 10025-1:2004 are no longer relevant.

The main changes with respect to the previous edition are listed below:

- a) part 4 is now a stand-alone standard for technical delivery conditions including the preparation of samples and test pieces, the test methods, the marking, labelling and packaging and the drawings;
- b) for applications under the CPR this document and part 1 are used together;
- c) requirements for elements not defined were added to 7.2.1 and 7.2.2;
- d) Option 33 was added, Option 3 was renumbered to Option 24 and Option 9 was deleted;
- e) Si-content in 7.2.4 was changed;
- f) 7.4.3 concerning hot-dip zinc coating was modified;
- g) key to Figure A.1 was updated;

- h) steel grade S500M was added;
- i) Annex B concerning the corresponding EURONORMS deleted;
- j) references were updated and document editorial revised.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Republic of North Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies technical delivery conditions for flat and long products of hot rolled weldable fine grain structural steels in the thermomechanical rolled condition in the grades and qualities given in Tables 1 to 3 (chemical composition) and Tables 4 to 6 (mechanical properties) in thickness ≤ 150 mm.

The steels specified in this document are especially intended for use in heavily loaded parts of welded structures such as, bridges, flood gates, storage tanks, water supply tanks, etc., for service at ambient and low temperatures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-2, *Welding — Recommendations for welding of metallic materials — Part 2: Arc welding of ferritic steels*

EN 10017, *Steel rod for drawing and/or cold rolling — Dimensions and tolerances*

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10024, *Hot rolled taper flange I sections — Tolerances on shape and dimensions*

EN 10025-1, *Hot rolled products of structural steels — Part 1: General technical delivery conditions*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10029, *Hot-rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10034, *Structural steel I and H sections — Tolerances on shape and dimensions*

EN 10048, *Hot rolled narrow steel strip — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled strip and plate/sheet cut from wide strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

EN 10055, *Hot rolled steel equal flange tees with radiused root and toes — Dimensions and tolerances on shape and dimensions*

EN 10056-1, *Structural steel equal and unequal leg angles — Part 1: Dimensions*

EN 10056-2, *Structural steel equal and unequal leg angles — Part 2: Tolerances on shape and dimensions*

EN 10058, *Hot rolled flat steel bars and steel wide flats for general purposes — Dimensions and tolerances on shape and dimensions*

EN 10059, *Hot rolled square steel bars for general purposes — Dimensions and tolerances on shape and dimensions*

- EN 10060, *Hot rolled round steel bars for general purposes — Dimensions and tolerances on shape and dimensions*
- EN 10061, *Hot rolled hexagon steel bars for general purposes — Dimensions and tolerances on shape and dimensions*
- EN 10067, *Hot rolled bulb flats — Dimensions and tolerances on shape, dimensions and mass*
- EN 10079, *Definition of steel products*
- EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*
- EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*
- EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*
- EN 10163-3, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 3: Sections*
- EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*
- EN 10168, *Steel products — Inspection documents — List of information and description*
- EN 10204, *Metallic products — Types of inspection documents*
- EN 10279, *Hot rolled steel channels — Tolerances on shape, dimensions and mass*
- EN 10306, *Iron and steel — Ultrasonic testing of H beams with parallel flanges and IPE beams*
- EN 10308, *Non destructive testing — Ultrasonic testing of steel bars*
- EN 10315, *Routine method for analysis of high alloy steel by X-ray Fluorescence Spectrometry (XRF) by using a near by technique*
- CR 10320, *Optical emission analysis of low alloy steels (routine method) — Method for determination of C, Si, S, P, Mn, Cr, Ni and Cu*
- CEN/TR 10347, *Guidance for forming of structural steels in processing*
- EN 10363, *Continuously hot-rolled patterned steel strip and plate/sheet cut from wide strip — Tolerances on dimensions and shape*
- EN 10365, *Hot rolled steel channels, I and H sections — Dimensions and masses*
- EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*
- EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*
- EN ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*
- EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 9443, *Surface quality classes for hot-rolled bars and wire rod (ISO 9443)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 14713-2:2009, *Zinc coatings — Guidelines and recommendations for the protection against corrosion of iron and steel in structures — Part 2: Hot dip galvanizing (ISO 14713-2:2009)*

EN ISO 15350, *Steel and iron — Determination of total carbon and sulfur content — Infrared absorption method after combustion in an induction furnace (routine method) (ISO 15350)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10079 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

thermomechanical rolling

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition with certain properties which cannot be achieved or repeated by heat treatment alone

Note 1 to entry: Thermomechanical rolling can include processes with an increasing cooling rate with or without tempering including self-tempering but excluding direct quenching and quenching and tempering.

Note 2 to entry: In some publications the word TMCP (Thermomechanical Control Process) is also used.

3.2

fine grain steels

steels with fine grain structure with an equivalent index of ferritic grain size ≥ 6

Note 1 to entry: For the determination of grain sizes see EN ISO 643.

4 Classification and designation

4.1 Classification

4.1.1 Main quality classes

All steel grades specified in this document shall be classified as alloy special steels according to EN 10020 except grade S275 which is a non-alloy quality steel.

4.1.2 Grades and qualities

This document specifies five steel grades S275, S355, S420, S460 and S500. All steel grades may be supplied in the following qualities as specified at the time of the order:

- with specified minimum values of impact energy at temperatures not lower than -20 °C , designated as M;
- with specified minimum values of impact energy at temperatures not lower than -50 °C , designated as ML.