

This document is a preview generated by EVS

## **Tsemendi katsetamine. Osa 6: Peenuse määramine**

Methods of testing cement - Part 6: Determination of fineness

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 196-6:2010 sisaldab Euroopa standardi EN 196-6:2010 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.03.2010 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 27.01.2010.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 196-6:2010 consists of the English text of the European standard EN 196-6:2010.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.03.2010 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 27.01.2010.

The standard is available from Estonian standardisation organisation.

ICS 91.100.10

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: +372 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

English Version

## Methods of testing cement - Part 6: Determination of fineness

Méthodes d'essai des ciments - Partie 6: Détermination de  
la finessePrüfverfahren für Zement - Teil 6: Bestimmung der  
Mahlfeinheit

This European Standard was approved by CEN on 21 December 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

**Contents**

Page

Foreword.....	3
<b>1</b> <b>Scope</b> .....	<b>5</b>
<b>2</b> <b>Normative references</b> .....	<b>5</b>
<b>3</b> <b>Sieving method</b> .....	<b>5</b>
3.1 <b>Principle</b> .....	<b>5</b>
3.2 <b>Apparatus</b> .....	<b>5</b>
3.3 <b>Material for checking the sieve</b> .....	<b>6</b>
3.4 <b>Procedure</b> .....	<b>6</b>
3.5 <b>Expression of results</b> .....	<b>7</b>
<b>4</b> <b>Air permeability method (Blaine method)</b> .....	<b>7</b>
4.1 <b>Principle</b> .....	<b>7</b>
4.2 <b>Apparatus</b> .....	<b>7</b>
4.3 <b>Materials</b> .....	<b>10</b>
4.4 <b>Test conditions</b> .....	<b>10</b>
4.5 <b>Compacted cement bed</b> .....	<b>10</b>
4.6 <b>Air permeability test</b> .....	<b>11</b>
4.7 <b>Calibration of apparatus</b> .....	<b>12</b>
4.8 <b>Special cements</b> .....	<b>14</b>
4.9 <b>Simplification of the calculations</b> .....	<b>15</b>
4.10 <b>Expression of results</b> .....	<b>16</b>
<b>5</b> <b>Air-jet sieving method</b> .....	<b>16</b>
5.1 <b>Principle</b> .....	<b>16</b>
5.2 <b>Apparatus</b> .....	<b>17</b>
5.3 <b>Procedure</b> .....	<b>18</b>
5.4 <b>Checking the sieve</b> .....	<b>18</b>
5.5 <b>Expression of results</b> .....	<b>18</b>
5.6 <b>Repeatability and reproducibility</b> .....	<b>18</b>

## Foreword

This document (EN 196-6:2010) has been prepared by Technical Committee CEN/TC 51 "Cement and building limes", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2010, and conflicting national standards shall be withdrawn at the latest by July 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 196-6:1989.

EN 196, *Methods of testing cement*, consists of the following parts:

- *Part 1: Determination of strength*
- *Part 2: Chemical analysis of cement*
- *Part 3: Determination of setting times and soundness*
- *Part 5: Pozzolanicity test for pozzolanic cement*
- *Part 6: Determination of fineness*
- *Part 7: Methods of taking and preparing samples of cement*
- *Part 8: Heat of hydration — Solution method*
- *Part 9: Heat of hydration — Semi-adiabatic method*
- *Part 10: Determination of the water-soluble chromium (VI) content of cement*

NOTE A previous part, EN 196-21, *Methods of testing cement — Determination of the chloride, carbon dioxide and alkali content of cement*, has been revised and incorporated into EN 196-2.

Another document, ENV 196-4, *Methods of testing cement — Quantitative determination of constituents*, has been published as CEN/TR 196-4, *Methods of testing cement — Part 4, Quantitative determination of constituents*.

This edition introduces the following technical changes based on comments received by the Secretariat:

- a) A method to determine the residue on sieving by air-jet equipment is included;
- b) The method for calibration of the air permeability equipment has been clarified and an alternative method, avoiding the use of mercury, added;
- c) The factors used in the air permeability (Blaine) method have been corrected for errors introduced in the conversion to SI units.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech

Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

This document is a preview generated by EVS

## 1 Scope

This European Standard describes three methods of determining the fineness of cement.

The sieving method serves only to demonstrate the presence of coarse cement particles. This method is primarily suited to checking and controlling the production process.

The air-jet sieving method measures the retention on sieving and is suitable for particles which substantially pass a 2,0 mm test sieve. It may be used to determine the particle size distribution of agglomerates of very fine particles. This method may be used with test sieves in a range of aperture sizes, e.g. 63  $\mu\text{m}$  and 90  $\mu\text{m}$ .

The air permeability method (Blaine) measures the specific surface (mass related surface) by comparison with a reference cement sample. The determination of the specific surface serves primarily to check the consistency of the grinding process of one and the same plant. This method only enables a limited assessment to be made of the properties of the cement in use.

NOTE The air permeability method may not give significant results for cements containing ultrafine materials.

The methods are applicable to all the cements defined in EN 197.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

ISO 383:1976, *Laboratory glassware — Interchangeable conical ground joints*

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 4803, *Laboratory glassware — Borosilicate glass tubing*

## 3 Sieving method

### 3.1 Principle

The fineness of cement is measured by sieving it on standard sieves. The proportion of cement of which the grain sizes are larger than the specified mesh size is thus determined.

A reference sample having a known proportion of material coarser than the specified mesh size is used for checking the specified sieve.

### 3.2 Apparatus

**3.2.1 Test sieve**, comprising a firm, durable, non-corrodible, cylindrical frame of 150 mm to 200 mm nominal diameter and 40 mm to 100 mm depth, fitted with, e.g. 90  $\mu\text{m}$ , mesh sieve cloth of woven stainless steel, or other abrasion-resisting and non-corrodible metal wire.