
**Rubber, raw — Determination of bound
acrylonitrile content in acrylonitrile-
butadiene rubber (NBR) —**

Part 1:
Combustion (Dumas) method

*Caoutchouc brut — Détermination du contenu en acrylonitrile lié dans le
caoutchouc acrylonitrile-butadiène (NBR) —*

Partie 1: Méthode par combustion (Dumas)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents and materials	2
5 Apparatus	2
6 Sampling and preparation of the sample for the determination	3
7 Procedure	3
8 Calculation of bound acrylonitrile content	4
9 Precision	4
10 Test report	4
Annex A (informative) Examples of automatic analysers based on the Dumas combustion method .	5
Annex B (informative) Precision	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 24698-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

ISO 24698 consists of the following parts, under the general title *Rubber, raw — Determination of bound acrylonitrile content in acrylonitrile-butadiene rubber (NBR)*:

- Part 1: *Combustion (Dumas) method*
- Part 2: *Kjeldahl method*

Rubber, raw — Determination of bound acrylonitrile content in acrylonitrile-butadiene rubber (NBR) —

Part 1: Combustion (Dumas) method

WARNING — Persons using this part of ISO 24698 should be familiar with normal laboratory practice. This part of ISO 24698 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

CAUTION — Certain procedures specified in this part of ISO 24698 may involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This part of ISO 24698 specifies a method for the determination of the bound acrylonitrile content in NBR by an automatic analyser which uses a combustion process. The method is also applicable to NBR latex.

NOTE Parts 1 and 2 of this International Standard may not necessarily give the same result for any given rubber sample.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 1407:1992, *Rubber — Determination of solvent extract*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Principle

The nitrogen in a sample of raw rubber is converted into oxides of nitrogen in an atmosphere of high-purity oxygen in the combustion unit of the analyser. The oxides of nitrogen are then converted into elemental nitrogen by a catalyst in the reduction unit. The carbon dioxide and water vapour produced are removed by absorption or another means of separation. Finally, the resultant gas is passed, with a carrier gas, into a thermal conductivity detector (TCD) to determine the nitrogen content.